



Sikafloor[®] 2530 W

Water Dispersed Coloured Epoxy Coating

Technical Data Sheet

DESCRIPTION

Sikafloor 2530 W is a solvent free two component water dispersed coloured epoxy coating. It provides a protective surface treatment for concrete floors and walls exposed to light and medium use.

USES

- * Industrial areas.
- * Abattoirs.
- * Car parks.
- * Water treatment plants.
- * Workshops.
- * Food processing areas.
- * Manufacturing areas.
- * Laboratories.
- * Storage areas.
- * Breweries.
- * Tunnel walls.
- * Decontaminable areas.
- * Tunnel walls.
- * Cleanrooms.

ADVANTAGES

- * Solvent free.
- * Vapour permeable.
- * Excellent carbonation barrier.
- * Prevents dusting.
- * Easy to clean.
- * Low odour.
- * Quick drying.
- * Non-flammable.
- * Water based.

FLOOR COATING SYSTEM:

Light exposure

Base coat: 1 x **Sikafloor 2530 W**
 Top coat: 1 x **Sikafloor 2530 W**

Medium exposure

Base coat: 1 x **Sikafloor 155W**
 Intermediate coat: 1 x **Sikafloor 2530 W**
 Top coat: 1 x **Sikafloor 2530 W**

Material consumption: Approx 0.15 - 0.3 kg/m² per coat

Technical Data (typical)

Colour: Refer to colour chart and current price list for availability and minimum order quantities.

Density (SG): Approx 1.2 kg/litre

Volume solids: Approx 55%

Application temperatures & humidity conditions: +10°C min, +30°C max (Substrate and ambient) RH 80% max

Substrate M.C. & RH: ≤4% by wt or ≤75% RH

MECHANICAL PROPERTIES:

Abrasion resistance: 65 mg (Taber)

Heat resistance: Continuous exposure 50°C
 Short term exposure 100°C

CHEMICAL RESISTANCE: Refer to chart (Consult Sika Ltd for additional information)

Additional application information:

	+10°C	+20°C	+30°C
Pot life:	2 hrs	1.5 hrs	0.5 hrs
Waiting time between coats:			
min	24 hrs	12 hrs	10 hrs
max	3 days	2 days	2 days
Final drying times:			
Foot traffic:	48 hrs	24 hrs	24 hrs
Lightly serviceable:	5 days	3 days	2 days
Fully serviceable:	10 days	7 days	5 days

All above values are approximate.

SURFACE PREPARATION

The cementitious substrate should be sound and of sufficient compressive strength. (Min 25 N/ mm²) . Minimum pull off strength 1.5 N/mm².

The surfaces must be dry and free of all contaminants eg oils, grease, surface treatments and coatings etc. The substrate must be prepared mechanically to achieve an open textured fine gripping surface, free of cement laitance. Weak concrete should be removed and surface defects such as blowholes and voids must be fully exposed.

All dust, loose and friable material must be completely removed from all surfaces before application of the coating preferably by brush and vacuum.

Repairs to cementitious substrate and filling of blowholes levelling of irregularities etc should be carried out using an appropriate product from the **SikaDur**[®], **Sikafloor**[®] or **SikaGard**[®] range of materials.

MIXING

Prior to mixing, stir component A (resin), add all of component B (Hardener) and mix both components thoroughly with a low speed electric stirrer (300 - 400 rpm) for a minimum of 3 minutes until a uniform mix has been achieved.

APPLICATION

Prior to application, confirm substrate moisture content and RH. If >4% by wt or >75% RH. **Sikafloor**[®] **EpoCem**[®] may be applied as a D.P.M. system

Apply **Sikafloor 2530 W** by brush or roller or spray. Observe the waiting time between coats.

Coats that exceed the maximum waiting time can be recoated after roughening surface with fine sandpaper to remove gloss.

The first coat can be thinned with clean water (5-10%) to aid penetration with dense concretes.

IMPORTANT CONSIDERATIONS

- * Do not apply **Sikafloor 2530 W** on substrates in which significant vapour pressure may occur.
- * Always ensure good ventilation when using **Sikafloor 2530 W** in a confined space.
- * Quartz silica sand can be sprinkled on to **Sikafloor 2530 W** then sealed to form a slip resistant surface
- * Freshly applied **Sikafloor 2530 W** should be protected from damp, condensation and water for at least 24 hours.
- * Avoid puddles on surface.
- * In low temperature (<13°C) ensure adequate ventilation otherwise curing may be affected.
- * **Sikafloor 2530 W** should not be applied to surfaces which have been treated with "water repellent" chemicals.
- * When applying onto very absorbent surfaces it is recommended to seal surface with **Sikafloor 155W** before applying **Sikafloor 2530 W**.

CLEANING

Use soap and water. Hardened material may have to be mechanically removed.

PACKAGING

Refer to latest price list.

CONSUMPTION

Approximately 0.15 - 0.3 kg/m² (These figures do not allow for surface texture or wastage).

Maximum yield per pack - see current price list.

STORAGE AND SHELF LIFE

Minimum 1 year in sealed containers stored in dry warehouse conditions (+5°C - +25°C).



Handling Precautions

Sika products are generally harmless provided that certain precautions normally taken when handling chemicals are observed. The materials must not, for instance, be allowed to come in contact with foodstuffs or food utensils and measures should also be taken to prevent the uncured materials from coming in contact with the skin, since people with particularly sensitive skin may be affected. The use of protective clothing, goggles, barrier creams and rubber gloves is required. The skin should be thoroughly cleaned at the end of each working period either by washing with soap and warm water or by using a resin-removing cream - the use of powerful solvents is to be avoided. Disposable paper towels - not cloth towels - should be used to dry the skin. Adequate ventilation of the working area is recommended. In case of accidental eye or mouth contact, flush with water - consult a doctor immediately. Health and Safety information on Sika Products is available and we strongly advise that this is read prior to their use. Sika products are for professional use and should be stored in sealed containers away from the reach of children.

Important Note

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users should always refer to the most recent issue of the Technical Data Sheet for the product concerned, copies of which will be supplied on request.

Please consult our Technical Sales Department for further information

SIKA IRELAND LIMITED

Unit 3, Ballymun Industrial Estate, Ballymun, Dublin 11, Ireland

Tel: +353 1 862 0709 Email: info@sika.ie

Fax: +353 1 862 0707 www.sika.ie

