

Tile Adhesive

Tilefast 6

On concrete, screed and render/ plaster

Tilefast 6 audited in accordance with DIN EN12004 complies with the Euro Norm C1T

Uses

- For indoor and outdoor use.
- For walls and floors.
- For laying non-vitrified and vitrified tiles in the thin-bed method.
- For laying ceramic coverings in permanently wet areas such as swimming pools, (Tilefast 6 + Admix only) indoor and out, health spas as well in wet areas such as showers, toilets, bathrooms and cold storage rooms.
- On cement screeds, ground anhydrite and/or gypsum based floated screeds, renders, concrete, heated screeds, mastic asphalt (indoors only), plaster boards, gypsum fibre boards, plaster slabs and plaster.
- For adhesive bed thicknesses from 3 to 6 mm.
- Tilefast 6 White especially suitable for porcelain mosaics (addition of PCI-Grout / Adhesive admix is necessary).

Features and benefits

- Excellent non-sag properties, no need for spacers. The bedded tiles have an immediate adhesion, but can still be aligned.
- Resilient, therefore easy to apply.
- Resistant to frost and permanent water, multi-purpose use indoor and out, even swimming pools and cold storage rooms.
- Good adhesion without pre-wetting and priming on concrete, cement screeds and renders.

TECHNICAL DATA

Material

Material basis	Cement mortar mixture with additives. Does not contain asbestos or other mineral fibres. No injurious silica dust during the application.
----------------	---

Components	1 part
Colour	grey

Identification according to - Regulation for Hazardous Goods /Road - Regulation for Hazardous Material <i>For further information refer to paragraph Safety.</i>	non hazardous irritating, contains cement
---	--

Shelf life	approx. 12 months
------------	-------------------

Storage	cool and dry
---------	--------------

Packaging	20 kg PE lined paper bag 10 kg bag
-----------	---------------------------------------

Application

Consumption - installation of ceramic and natural stone tiles	approx. 1.2 to 14 kg powder/m ² per mm adhesive bed
--	--

Gauging water for 20kg bag approx 6.4 ltr
Gauging water for 1kg approx 0.3 ltr

Yield

Tile format	Required notch size	20 kg bag is sufficient for approx.
- small mosaics	3 to 4 mm	11 - 13 m ²
- 10 x 10 cm	4 to 6 mm	9 - 13 m ²
- 10 x 10 cm to 20 x 20 cm	6 to 8 mm	7 - 9 m ²
- 20 cm to 30 x 30 cm	8 to 10 mm	5.5 - 7 m ²
- From 30 x 30 cm	minimum 10 mm	4 - 5.5 m ²

Thickness of adhesive bed	1 to 6mm
---------------------------	----------

Open time*	approx. 20 minutes
------------	--------------------

Slake time	approx. 3 minutes
------------	-------------------

Working time*	approx. 4 hours
---------------	-----------------

Working temperature	+5°C to +30°C (substrate temperature)
---------------------	---------------------------------------

Curing times*	
- walkable after	approx. 24 hours
- groutable after	approx. 24 hours
- fully load-bearing after	approx. 7 days

* The required notch size and thus also the consumption of Tilefast 6, besides the tile format to be installed, also dependent on the back profile of the ceramic tile, the surface structure of the substrate and the application method.

The data mentioned above are based on experienced figures and may deviate.

If a flexibly adjustable adhesive bed is required.

* At +23°C and 50 % relative humidity. Higher temperatures reduce and lower temperatures increase these times.

SUBSTRATE PREPARATION

Minimum age of the substrate

- Novoment plus screed - 24 hours
- Cement screed - 28 days
- Concrete - 6 weeks

The substrate must be solid, clean and load-bearing. Oil stains, bond-inhibiting surfaces and contaminations must be thoroughly removed. The substrate must be flush and plumb according to BS 5385. Irregularities on walls are to be

levelled with Polycrete 5 or with the repair mortar Polycrete 20. Concrete floors are to be levelled with the self-smoothing screed leveller Periplan. Very absorbent cement based substrates and aerated concrete are to be primed with Primer G, diluted 1 : 1 with water. Prime ground anhydrite and/or gypsum based pourable screeds as well as gypsum based substrates and mastic asphalt screeds indoors with undiluted Primer G. Allow primer to dry. Freshly installed cement screeds must not have a residual moisture content above 4%, anhydrite and/or gypsum based screeds not more than 0.5% (measured with a CM-moisture meter). Ground anhydrite screeds require two coats of Primer G, the first coat diluted 1:1 with clean water and the second coat neat.

APPLICATION

Mixing

1. Place gauging water (see table "Technical Data/Application") in a clean mixing vessel.
2. Add powder and mix with a suitable stirrer or mixer mounted on an electric drill until a plastic, lump-free consistency is achieved.

Tiling

3. Apply a thin bond coat to the substrate with the straight edge of the trowel.
4. Then comb mortar onto the fresh bond coat with the notched edge of the trowel working in one direction, if possible. Only apply as much mortar as can be covered with tiles within the open time. Check the open time by touching the adhesive bed with your fingertip.
5. Position tiles in the adhesive bed and align with a slightly pushing motion.

GROUTING

Product	joint width
Groutfast Grey	3-10 mm
Groutfast White	1-3 mm
Wall & Floor Grout	2-18 mm

Camel Beige, Bahama Beige, Cement Grey No 31, Sandstone, Anthracite, Grey No 21 and Jasmine.

■ PCI-Aquafug	Joint width	1-8 mm
---------------	-------------	--------

■ Fast Track Grey Grout	joint width	3 - 20 mm
Colour		
No 22 Sandgrey		

■ PCI-Durafug NT	3 - 20 mm
No 31	

■ PCI Epoxy Grout Dark Grey	3 - 15mm
■ PCI Epoxy Grout Light Grey	3 - 15 mm
■ PCI Epoxy Grout Black	3 - 15 mm
■ PCI Epoxy Grout White	3 - 15 mm



The Chemical Company

PLEASE NOTE

- Do not apply at temperatures below +5°C and above +30°C and under exposure to strong wind and sunlight.
- For installations on gypsum-based substrates the instructions of the gypsum manufacturer must be followed. Primer G must be applied prior to cementitious products.
- The open time reduces with absorbent substrates.
- Stiffened mortar must not be re-tempered.
- Clean tools with water immediately after use; once the product has cured it can only be removed by mechanical means.

SAFETY

Tilefast 6 contain cement. Contact with moisture or gauging water sets off an alkaline reaction which may cause skin irritation and/or caustic burns to mucous membranes (e.g. eyes). Risk of severe eye injury, therefore avoid contact with eyes and prolonged skin contact. In case of eye contact, thoroughly rinse with water and get prompt medical attention. In case of skin contact remove soaked, contaminated clothing immediately and thoroughly wash affected area with plenty of water and soap. Wear suitable protective gloves. Keep out of reach of children.

For further information refer to the PCI Material, Safety Data Sheet.

BASF Construction Chemicals (UK) Ltd
Albany House, Swinton Hall Road,
Swinton, Manchester,
M27 4DT, England.
Tel: + 44 (0) 161 794 7411
Fax: + 44 (0) 161 727 8547
E-mail: pci.uk@basf.com
Website: pci.uk.com

In view of widely varying site conditions this data sheet is meant to provide general application guidelines only. Any recommendation or information issued by us constitutes a preliminary and accessory contractual obligation only. Users must satisfy themselves regarding the applicability of the content to their own particular requirements. Please contact our Advisory Service for special requirements. Liability is accepted for incomplete or incorrect particulars in our information material only in the event of intent or gross negligence, without prejudice to claims under product liability laws. All transactions are subject to our Terms of Sale and Supply. Any subsequent publication supersedes this edition. **Edition December 2006.**