

ANCHORSET RED 380P

Colour	Product Code	Pack Size	Box Qty
Grey			10

Product Description

Anchorset is a rapid curing "one shot" two-part chemical anchoring cartridge system based on an unsaturated polyester resin in Styrene. Applied in one single action to produce a cost effective, tough, chemical resistant fixing. Anchorset is ideal for close-to-edge applications (unlike expansion anchors) as no stress is placed on the surrounding substrate. Versatile in use, Anchorset is suitable for fixing wall ties, starter bars, studs, bolts or large screws in a wide range of substrates including brickwork, concrete, masonry, stone and PFA blocks. Hollow base materials can be securely fastened into by using Anchorset in conjunction with a sleeve or sieve.

Surface Preparation

1. Drill hole to the correct diameter and depth (see chart for guide), ideally using a rotary percussion machine. For optimum results the hole must be coarse sided. If the holes are produced by diamond drilling, the surfaces should be thoroughly roughened.
2. Remove all dust and debris from the hole using a hand air pump or a stiff rotary brush.
3. All bars should be clean and free from oil or grease and all flaking rust should be removed. Threaded rod or studs should be chisel-ended to prevent them being unscrewed from the cured resin.

Application

1. Attach the mixing nozzle to the cartridge (*screw down hand tight*).
2. Place cartridge into the Anchorset dispensing gun.
3. Open the cartridge by pressing the green end of the colour coded valve. Gradually pressurize the Cartridge by activating the hand trigger a few times until material passes through the mixing nozzle. Stop pressurizing and allow the material to flow until an even colour is obtained (approximately 5-6 inches of extruded material should be adequate).
4. Press the red end to close the valve. Insert the nozzle into the base of the hole. Open valve again by pressing the green end and activate the trigger, withdraw the nozzle slowly as the hole fills.
5. Once the required fill is achieved shut off the valve and wipe off excess material. Insert the fixing slowly with a rotating action to the desired depth. Once all applications have been carried out, release the pressure by pressing the slide release arm on the back of the trigger stop and pulling back the slide rail.

NB Once material has started to extrude through the nozzle over pressurizing the system will not increase flow rate, and can cause leakage from the rear of the cartridge.

Specific Data

Compressive Strength (ASTM 695)	48 N/mm ²
Tensile Strength (ASTM 638)	< 10 N/mm ²
Flexural Strength (ASTM 790)	20 N/mm ²
Elastic Modulus	4206 N/mm ²
Flexural Modulus	3238 N/mm ²
Mixed Density	1.65 g/cm ³
Mixing Ratio	10:1 by volume as supplied in cartridge

ANCHOR SIZE (mm)	HOLE DIAMETER (mm)	HOLE DEPTH (mm)	TENSION (kN) (Ultimate pull out)	FIXINGS PER UNIT (Holes filled 2/3 full) 380ml
8	10	80	22.56	86
10	12	90	29.40	53
12	14	110	31.72	32
16	18	125	72.45	17
20	22	170	78.76	8
24	26	210	106.06	5
30	32	280	179.54	2

Tension Figures quoted are tested independently in accordance with B.S. 5080 PART 1 in approximately 30 N/mm² concrete.

The ultimate pull out strength is varied by:

1. The strength of both the substrate and bar/stud
2. The length of the resin bond to bar
3. Hole preparation
4. Anchor separation

Safety factors should be considered depending on the strength and nature of the substrate.

Due to the inconsistent nature of hollow blocks and bricks, tension figures may vary. Site testing should be carried out where necessary to establish particular suitability. In order to achieve maximum performance the distance between the centres of the anchors should be a minimum of 2.0 x the embedment depth, and 1.25 x the embedment depth for the minimum distance from edges.

Health & Safety

Consult MSDS for full list of hazards.

Storage

Store in a dry area between 5°C and 25°C. Do not expose to direct sunlight. Storage at higher temperatures will reduce the shelf life.

Shelf Life

12 months from date of manufacture.

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.