

Product Data Sheet

Data Sheet Ref:SEWB 04/05 Page 1 of 2

DESCRIPTION

RESUSEAL water based floor coatings are coloured, two-pack, easy to apply resin systems with excellent adhesion to concrete, wood and other surfaces providing attractive, hard wearing dust-free finishes. Floors become easier to clean and substantially more resistant to damage by fork-lift trucks, chemicals, fuels and lubricants etc.

RESUSEAL WB STANDARD can act as a curing membrane to increase hardness of concrete by allowing full hydration of cement. RESUSEAL WB STANDARD can be applied to new (green) concrete, 7 days after being poured.

ADVANTAGES

- 1 Low odour
- 2 Overnight cure
- 3 Can be applied onto concrete, wood and asphalt etc. Metal surfaces may also be treated, in conjunction with a compatible, solvent-based metal primer - RX66
- 4 Anti-slip finishes can be created by applying a scatter of fine grade bauxite aggregate onto the middle coat of a three coat application.
- 5 Resistant to most fuels and lubricants.
- 6 Available in a range of colours.

WHERE TO USE

RESUSEAL WB (all grades) being low-odour, is ideal for use in the food industry, dairies, breweries, bakeries etc. where solvent based products are prohibited. The hardwearing, chemical/oil resistant properties also make RESUSEAL WB ideal for garage showrooms, workshops, warehouses, supermarkets and general industrial usage:

NOTE 1 - In order to achieve the best results from this product, it is recommended that the product be used only when temperatures in excess of 10°C are present with good ventilation.

NOTE 2 - Variations in temperature and humidity during the cure period can significantly affect the rate of drying and surface finish.

GRADES AVAILABLE

RESUSEAL WB STANDARD - A general purpose epoxy resin finish suitable for use in most industrial environments, which dries from a semi-gloss to a semi-matt finish depending on temperature and humidity.

RESUSEAL WB FLOOR GLOSS - A coating which dries to a uniform gloss finish for flooring use.

RESUSEAL WB CLEAR - A clear coating for sealing concrete or for use where a primer is required prior to application of all grades of RESUSEAL WB and other products, including RESUTOP, RESUCOAT HB, RESUTILE and RESUDECK. A primer is required for porous surfaces, high build and anti-slip finishes.

Product Data Sheet

Data Sheet Ref:SEWB 04/05 page2 of 2

CHEMICAL RESISTANCE

RESUSEAL WB has excellent resistance to fuels, oils and lubricants. All grades possess good resistance to dilute acids, alkalis, detergents, salt and sugar solutions.

Chemical spillages should always be wiped up as quickly as possible and not allowed to evaporate. For further information, please consult our Technical Department.

PHYSICAL PROPERTIES AT 20°C

Pack Size

5 kg and 10 kg units

Coverage rate

6-8 square metres per kg.

Pot life

1 – 1.5 hrs

Recoat time

24 - 48 hours

Full Chemical Cure

7 days

Shelf Life

12 Months

PREPARATION

All surfaces to be coated with any grade of **RESUSEAL WB** should be dry, clean and free from laitance, oil, grease or other contaminants. Ideally concrete surfaces should be vacuum shotblasted or mechanically abraded to both clean and open the surface to provide a good mechanical key. The separate base and hardener components must be thoroughly mixed together before application.

APPLICATION

One or two coats of **RESUSEAL WB** can be applied with a roller or brush. Slip resistance can be achieved by specifying a three coat system. The first coat of **RESUSEAL WB CLEAR** being followed by one coat of **RESUSEAL WB STANDARD**, lightly scattered with anti-slip aggregates whilst still wet, at a rate of 50/100 gms per sq.m. When dry a second **RESUSEAL WB STANDARD** coat can be applied.

MAINTENANCE

RESUSEAL WB coatings can be mopped with water, scrubbed with **R.S. INDUSTRIAL FLOOR CLEANER** or other good quality detergent or just brushed out. **RESUSEAL WB** coated floors should not be subject to hot water above 60°C or steam cleaning.

HYGIENE

RESUSEAL WB products are formulated from materials, which are designed to achieve the highest levels of performance as safely as possible. However specific components require proper handling and suitable equipment. This information is given in the relevant safety data sheets.

In all cases spillage's or skin contamination should be cleared as soon as possible by dry wiping the affected area and then thoroughly washing with soap and water.

Consult Safety Data Sheets **HSRS** for **RESUSEAL WB STANDARD** and **RESUSEAL WB CLEAR**.

Consult Safety Data Sheets **Ref. HSSG** for **RESUSEAL WB FLOOR GLOSS**.

Consult Safety Data Sheet **Ref. HSSM** for **RESUSEAL WB MATT**.

Consult Safety Data Sheet Ref. **HSCS**.

The information given in this data sheet is derived from tests which are believed to be reliable. The information is offered without guarantee to enable purchasers to decide more readily by their own tests, the suitability of the product for their particular application. Any specification or advice given by the company is based on the information supplied by the purchaser. Resin Surfaces cannot be held accountable for errors or omissions as a result of that information being incorrect or incomplete. No undertaking can be given against infringement of patents.