

Dekguard W



Dekguard W
CI/SfB: Vu6
September 2000

Water-based acrylic copolymer protective and decorative coating for concrete and masonry

Uses

To protect atmospherically exposed reinforced concrete structures, cementitious substrates and masonry from aggressive elements, weathering and rain. Dekguard W is suitable for use on all types of structures, including those in coastal environments. It is equally suitable for new and existing structures. Dekguard W is a component of Fosroc's Renderoc system of concrete reinstatement.

Advantages

- Excellent barrier to carbon dioxide, chloride ions, oxygen and water
- Allows water vapour to escape from the structure
- High resistance to the effects of long-term weathering and durable in all climatic conditions
- Water-based
- Wide range of decorative colours
- Range of primers
- One or two coat application

Standards compliance

Fire tested to BS 476, Pt 7: 1987. Spread of flame — Class 1.

Description

The Dekguard W system comprises a single component, penetrating silane-siloxane primer and a single component pigmented coating, both ready for immediate site use.

A range of reactive primers are available to suit substrate porosity and site conditions and inhibit the passage of water and waterborne contaminants.

Properties

The values obtained are for the Dekguard W system applied in two coats at the minimum recommended application rate.

Volume solids	
Dekguard W:	41%
Carbon dioxide diffusion resistance (Taywood method). Equivalent thickness of air —	
Initial:	> 50 metres
After 2000 hours QUV:	> 50 metres

Equivalent thickness of

30 N/mm² concrete cover

(Taywood method): > 125 mm

Water vapour diffusion resistance S_D 0.066 m @

(Taywood method): 50 microns dft

Reduction in chloride ion

penetration (Aston University

Diffusion Cell method): > 84%

Fire testing (BS 476, Pt 7: 1987)

Spread of flame: Class 1

Application instructions

Preparation

All surfaces should be dry and free from any contamination and all traces of mould release oils and curing compounds. This is best achieved by lightly grit-blasting the surface. Where moss, algae or similar growths have occurred, treatment with a proprietary biocide should be carried out after the grit-blasting process.

Note: it is not necessary to remove Nitobond AR curing membrane prior to the application of Dekguard W.

Where application over existing sound coatings is required, trials should be conducted to ensure compatibility and retention of the bond between the underlying coating and the substrate. For advice, consult the local Fosroc office.

It is essential to produce an unbroken coating of Dekguard W. Surfaces containing blow-holes or areas of pitting should first be filled using Renderoc FC, a cementitious fairing coat. Rougher substrates can be levelled using Renderoc RP252, a cementitious reprofiling and protection mortar. Separate data sheets **must** be referred to.

Application

In order to obtain the protective properties of the Dekguard W system, it is important that the correct rates of application and overcoating times are observed.

Any areas of glass should be masked. Plants, grass, joint sealants, asphalt and bitumen-painted areas should be protected during application.

Dekguard Primer should be applied in one or more coats to achieve the recommended application rate. This is best accomplished by using portable spray equipment of the knapsack type. Porous surfaces may require the application of Nitoprime DG as a 'film forming' primer, or may require other special treatment. Nitoprime DG should be applied at the recommended application rate in continuous, multiple coats as necessary. If in doubt about the condition of the substrate, consult the local Fosroc office.



The primer should be allowed to dry for a minimum of 12 hours (at 20°C) before continuing. Under no circumstances should any primer be overcoated with Dekguard W until the surface is properly dry.

Where chloride resistance is not relevant, a reduced specification may be adopted: omit Dekguard Primer and use either Nitobond AR or dilute the first coat of Dekguard W with 10% v/v water. If the total recommended minimum film thickness is maintained, the anti-carbonation and weathering properties will be maintained.

Dekguard W may be applied by the use of suitable brushes, rollers or spray equipment.

All primed substrates should be treated with two coats of Dekguard W. Stir material before use. The first coat should be applied to achieve a uniform coating with a wet film thickness not less than 180 microns. This coat should be allowed to dry until firm to the touch. Typically, this will be after 16 hours in dry weather at 20°C.

The second coat of Dekguard W should be applied as detailed above, again achieving a wet film thickness not less than 180 microns, and a total dry film thickness not less than 150 microns.

Used as a primerless single coat aesthetic finish, Dekguard W should be applied to achieve a uniform coating of wet film thickness not less than 220 microns, dry film thickness 90 microns.

Cleaning

Dekguard W should be removed from tools and equipment with clean water immediately after use.

Limitations

When applied over existing coatings or paints, the performance characteristics of Dekguard W may be impaired and its fire rating invalidated. For further advice, consult the local Fosroc office.

The application of the primer should not commence if the temperature of the substrate is below 2°C. Application of

Dekguard W should not commence if the temperature of the substrate is below 5°C.

Dekguard W should not be applied where there is a likelihood of exposure to frost within 48 hours of the application. The product should not be applied in windy conditions where early-age dust adhesion may occur, or where rain is likely within 2 hours at 20°C or 20 hours at 5°C (up to 80% RH) or when the prevailing relative humidity exceeds 90%.

Dekguard W should not be considered for areas subjected to exposure to ponded water. Dekguard S should be considered where occasional ponded water is anticipated.

Estimating

Dekguard W is supplied in 15 litre drums which covers 2.75 m² per litre (2 coats), 4.4m² per litre (single coat).

The coverage figures given are theoretical — due to wastage factors and the variety and nature of possible substrates, practical coverage figures will be reduced.

Storage

Dekguard W has a shelf life of 12 months if kept in a dry store in the original, unopened packs. Store in cool, dry conditions, away from sources of heat and naked flames. If stored at high temperatures and/or high humidity conditions the shelf life may be reduced. Dekguard W should be protected from frost.

Precautions

Health and safety

Dekguard W should not come in contact with the skin and eyes, or be swallowed. Ensure adequate ventilation and avoid inhalation of vapours. Some people are sensitive to resins, hardeners and solvents. Wear suitable protective clothing, gloves and eye protection. If working in confined areas, suitable respiratory protective equipment must be used. In case of contact with skin, rinse with plenty of clean water, then cleanse with soap and water. Do not use solvent. In case of contact with eyes, rinse immediately with plenty of clean water and seek medical advice. If swallowed, seek medical attention immediately — **do not** induce vomiting.

Fire

Dekguard W is non-flammable.

Dekguard is the trade mark of Fosroc International Limited



Fosroc Limited
Coleshill Road
Tamworth
Staffordshire B78 3TL
Tel 01827 262222
Fax 01827 262444
www.FosrocUK.com

Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation or information given by it.