

Conbextra UW

constructive solutions

Non-shrink cementitious grout for underwater installations

Uses

Conbextra UW is used for free flow or pumped grouting applications underwater or in tidal zones. There will be no significant 'wash-out' of the cement phase. Applications include bridge columns, quay pillars, concrete piling, slipways and dams.

Advantages

- No risk of significant 'wash-out' of cement phase when placed underwater
- Displaces water effectively
- Gaseous expansion system compensates for shrinkage and settlement in the plastic state
- High early and ultimate strength and exceptional resistance to freeze-thaw cycling ensure durability of the hardened grout
- Chloride free
- Pre-packaged needing only on-site addition of water

Description

Conbextra UW is supplied as a ready to use powder. The addition of a controlled amount of clean water produces a free flowing grout. The grout exhibits exceptional resistance to 'washing-out' of the cement phase when placed in stationary or moving water.

Conbextra UW is a blend of cement, graded fine aggregate and chemical additives which impart controlled expansion, water reduction and non 'wash-out' characteristics. The aggregate grading minimises segregation and bleeding whilst assisting the flow characteristics.

Properties

The following results were obtained at a water : powder ratio of 0.22.

Test method for	Typical result	
	5°C	20°C
Compressive strength (BS 4550, Part 3: 1978) —		
1 day:	6 N/mm ²	25 N/mm ²
3 days:	24 N/mm ²	38 N/mm ²
7 days:	36 N/mm ²	44 N/mm ²
28 days:	50 N/mm ²	53 N/mm ²
Setting time (BS 5075, Part 1: 1982) —		
Initial:	13 hours	4.5 hours
Final:	16.5 hours	5.5 hours
Density of hardened grout:	2050 kg/m ³	

Expansion characteristics: Controlled expansion occurs in the unset material to ensure that the grout, when cured, will continue to occupy its original volume within the confines of the void in which it was placed.

Application instructions

Preparation

The substrate surface must be free from oil, grease or any loosely adherent material. If the concrete surface is defective or has laitance, it must be cut to a sound base.

Substrates which are permanently immersed should be grit-blasted or cleaned with a high pressure water jet. Non-immersed or intermittently immersed substrates can be prepared using these techniques. Alternatively scabbling or bush hammering may be appropriate.

Formwork

The formwork should be constructed to be leakproof as Conbextra UW is a free flowing grout. This can be achieved by using foam rubber strip or Silicone Sealant 33 beneath the constructed formwork and between joints.

Mixing and placing

Mixing

For best results a mechanically powered grout mixer should be used.

It is essential that machine mixing capacity and labour availability is adequate to enable the grouting operation to be carried out continuously. This may require the use of a holding tank with provision for gentle agitation to maintain fluidity.

Measure accurately 5.5 litres of water for each 25 kg bag into the mixer. Slowly add the Conbextra UW whilst mixing continuously. When all the powder is added mix continuously for 5 minutes ensuring a smooth even consistency is obtained. (Fluidity will increase with increased mixing.)

Placing

Place the grout within 20 minutes of mixing to gain the full benefit of the expansion process. Continuous grout flow is essential.

The mixed grout should be poured or pumped through a flexible tube, having a minimum diameter of 50 mm, to the lowest point in the form.

Care must be taken at the start of the grouting operation to restrict the grout flow so that water is not entrapped.

The tube may be raised as necessary to reduce any back pressure. It should not be raised above the surface level

Conbextra UW

of the grout.

Conbextra UW can be placed in thicknesses up to 75 mm in one pour when used above water. When used underwater, the heat sink effect in this environment will allow thicknesses of up to 150 mm to be placed.

For thicker sections, up to 200 mm above water and 400 mm underwater, it is necessary to fill out Conbextra UW using a clean rounded well graded aggregate ranging from 2 to 10 mm. The ratio of aggregate added to Conbextra UW should not exceed 1:1 by weight. For such mixes a concrete mixer should be used. Unrestrained surface area should be kept to a minimum.

Curing

Curing will not be required in intermittently or totally submerged situations. However, when cast above water, exposed areas should be thoroughly cured with Concure curing membrane, continuous application of water and/or wet hessian.

Cleaning

Because of its water resisting properties, equipment used for Conbextra UW will be difficult to clean. The use of hot water for cleaning purposes will assist. Cured material can be removed mechanically or with Fosroc Acid Etch.

Limitations

Conbextra UW must not be applied below 5°C.

Estimating

Supply

Conbextra UW is supplied in 25 kg moisture resistant bags.

Yield

Allowance should be made for wastage when estimating quantities required. The approximate yield of a 25 kg bag when mixed with 5.5 litres of water is 14.5 litres.

Storage

Store in unopened bags in cool dry internal conditions. The product has a shelf life of 12 months from the date of manufacture if kept in a dry storage in the original, unopened bags. If stored at high temperatures and/or high humidity conditions the shelf life may be reduced to less than 6 months.

Precautions

Health and safety

For further information refer to appropriate Product Safety Data Sheet.

Fire

Conbextra UW is non-flammable.



Fosroc Limited

Drayton Manor Business Park
Coleshill Road, Tamworth,
Staffordshire B78 3TL. UK

www.fosroc.com

Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification of information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it.

Conbextra is the trade mark of Fosroc International Limited

telephone:
+44 (0) 1827 262222

fax:
+44 (0) 1827 262444

email:
uk@fosroc.com



Certificate number FM 610