

100 NEWTON GROUT

Product code

TG 102 packaging listed overleaf

Description

100 Newton Grout is an ultra high strength grout specially formulated using a Portland cement powder mix. The mix design consists of a blend of fine and ultra-fine cements, high quality graded sands and a set of synergistic admixtures. The mix design includes special shrinkage compensating components, which give a non-shrink grout in both the plastic and hardened states. Powerful plasticising agents produce a highly flowing grout at low water content.

The product is pre-packaged in 15kg pails ready for on site mixing, only requiring measured water addition. The material readily mixes with water to produce the ultra high strength grout that is easily placed to give exceptional structural support and vibration resistance.

100 Newton Grout is chloride free and can be safely used in contact with reinforcing steel and structural steel elements. The specialised mix design enables placement at low water content leading to good freeze-thaw stability, low water absorption plus resistance to oil, sea water and mild alkali attack.

Placement thickness may be in the nominal range of 10mm to 100mm.

- Uses include:**
- Ultra high strength grout and support systems for:
 - Crane rail tracks.
 - Stanchion bases.
 - Machine bed plates for reciprocating, rotational and impact machinery.
 - Ground anchors.
 - Bridge bearing seats.

Typical Grout Properties @ 20°C

Compressive Strength

Water addition 2.7 litres per 15kg of 100 Newton Grout

3 Day	70N/mm ₂
7 Days	85N/mm ₂
28 Days	105N/mm ₂

Mechanical Properties

Density	2250kg/m ³
Coefficient of Thermal Expansion	11 x 10 ⁻⁶ /°C
Compressive Modulus	30kN/mm ₂
Initial Set	260 minutes
Final Set	290 minutes

Specification Outline

Grouting shall be carried out using 100 Newton Grout as manufactured by Tecroc Products Ltd. The product must be stored, handled and placed in accordance with the manufacturer's instructions.

Quality Assurance

Tecroc Products Ltd is a firm of Assessed Capability. The Company's quality system conforms to BS EN ISO 9001:2000 and is assessed by SGS Ltd Systems and Services Certification.

Standards

100 Newton Grout has been tested in accordance with the appropriate parts of the following standards:

- BS 1881.
- Corps of Engineers Specification for Non-Shrink Grout CRD C621
- Specification for Highway Works Clause 2601.



Grouts



Structural Support Mortars



Concrete Repair Products



Construction Adhesives



Resin & Cementitious Anchors



Highway Products



Coatings



Waterproofing



Ground Engineering

Head Office
Holly Lane Industrial Estate
Atherstone
Warwickshire
CV9 2RN
Tel: 01827 711755
Fax: 01827 711330

Irish Distributor
Construction Chemical Supplies
Unit 219
JFK Road JFK Industrial Est
Dublin 12
Tel: 00 353 1 450 3896
Fax: 00 353 1 450 3298

Web site: www.tecroc.co.uk

E-mail: enquiries@tecroc.co.uk



100 NEWTON GROUT

Instructions For Use

Preparation

Formwork should be erected and made grout-tight. The formwork must be designed with sufficient hydrostatic head to ensure grout flow into and across the grouting area. Saturate the grouting area with water. Leave for 1 hour and then blow out any surplus water.

Mixing

Pour the required quantity of clean water 2.7litres per 15kg pail into the mixing vessel for each complete unit of 100 Newton Grout to be used. Slowly add the powder to the water whilst continually mixing. Mechanical mixing should be carried out using either a high torque slow speed drill with a Grout Stirrer or a grout mixer set on slow speed. (High speed or colloidal mixing will cause thixotropy leading to loss of flow). **This material is not suitable for mixing by hand.** It is of utmost importance that the product is mixed thoroughly enough that a grout consistency is obtained **without** the addition of further water.

Placing

Grout should be placed within 10 minutes of mixing. Continuous placing is important, pouring from one side of the formwork until the grout appears at the opposite side of the grouting area. Do not disturb once grouting has been completed. 100 Newton Grout may be placed at temperatures between 5°C and 45°C. For placing at temperatures outside this range contact the Technical Service Department.

Curing

Placed grout, which is exposed, should be cured in accordance with good concrete practice including water spray and the spray applied curing membrane Polycure.

Precautions

Health and Safety

100 Newton Grout is alkaline when mixed with water and should not come into contact with skin or eyes. Avoid inhalation of dust during mixing and wear safety glasses, dust mask and gloves. If skin contact occurs wash thoroughly with clean water. Should eye contact occur rinse immediately with plenty of clean water and seek medical advice. Full health and safety data are given in Product Safety Data Sheet.

Fire

100 Newton Grout is non-flammable.

Yield

15kg pail will yield approximately 7.8 litres of mixed grout.

Storage And Shelf Life

100 Newton Grout will have a storage life of 12 months in unopened bags when kept in dry conditions at a temperature between 5°C and 45°C. Storage at higher temperatures or high humidity may reduce shelf life.

Packaging And Ordering

100 Newton Grout is supplied in 15kg pails.
15kg Pail Product Code TG 102

For further information and sales please contact your local Tecroc Products office as listed below.

Tecroc Products Ltd products are guaranteed against defective materials and manufacture. Products are sold subject to the Tecroc Products Ltd Terms and Conditions of Sale, copies of which are forwarded on invoice and are available on request. Tecroc Products Ltd endeavours to ensure that the above data and any further advice is correct, however, it cannot accept any direct or indirect liability for the use of its products as such usage is beyond its control.

Head Office
Holly Lane Industrial Estate
Atherstone
Warwickshire
CV9 2RN
Tel: 01827 711755
Fax: 01827 711330

Irish Distributor
Construction Chemical Supplies
Unit 219
JFK Road JFK Industrial Est
Dublin 12
Tel: 00 353 1 450 3896
Fax: 00 353 1 450 3298

Web site: www.tecroc.co.uk

E-mail: enquiries@tecroc.co.uk



Grouts

Structural Support
MortarsConcrete Repair
ProductsConstruction
AdhesivesResin Et
Cementitious
AnchorsHighway
Products

Coatings



Waterproofing

Ground
Engineering