



Specialist Construction Supplies for Repair, Maintenance, Building & Infrastructure

## Pumaprime TC Data Sheet

### Specification notes

Product: **Pumaprime TC**

Supplier:

**Arcon Construction Supplies**  
**19-20 Prestwood Court**  
**Leacroft Road**  
**Warrington**  
**WA3 6SB**

Tel: **01925 852225**

Email: [mail@arconsupplies.co.uk](mailto:mail@arconsupplies.co.uk)

Web: [www.arconsupplies.co.uk](http://www.arconsupplies.co.uk)

Call **01925 852225** or visit [Arcon Construction Supplies](http://www.arconconstruction.com)  
... for more information on our flooring and construction products

[Industrial Flooring](#) | [Concrete Repairs](#) | [Protective and Waterproof Coatings](#)  
[Jointing and Paving Mortars](#) | [Anti-slip Floor Paints](#) | [Concrete Repair Mortars](#)

# Pumadur Primer TC

Polyurethane tack coat primer



## Description

**Pumadur Primer TC** is a three-component solvent free polyurethane resin adhesive primer for use as a bonding aid for polyurethane resin based screed compositions including Pumadur WR, CG, SC and Pumabulk.

**Pumadur Primer TC** is designed to be tacky to enable trowel applied resin screeds to be applied wet on wet giving a monolithic bond.

## Suitable Substrates

Thoroughly prepared concrete, polymer modified sand and cement screeds, brickwork and block work.

## Typical Properties, 28 days at 20 °C

Adhesion to concrete (BS EN 1504-2) > 1.5 MPa (concrete failure)

The typical physical properties given above are derived from testing in a controlled laboratory environment. Results derived from testing field-applied samples may vary dependent upon site conditions.

## Cure Schedule at 20 °C

Working life of full packs \* 15 minutes

\* Usable working life of material following mixing and immediate spreading as per the application instructions.

The topping must be applied when **Pumadur Primer TC** is still tacky. At 20 °C this will be between 1.5 hours and 2 hours after the primer has been mixed. Work should be organised around this window. Colder temperatures will reduce the rate of cure and warmer temperatures will increase the rate of cure. Do not use below 10 °C. If the primer is allowed to become tack free, a further coat of **Pumadur Primer TC** must be applied within 24 hours. If the over coating interval is exceeded, the first coat should be abraded to ensure inter-coat adhesion.

## Pack Size

2.1 kg units

## Coverage\*

Coverage varies widely due to the porosity and profile of different substrates. As a guide, a coverage rate of 2.5 - 4 m<sup>2</sup>/kg should be estimated per coat depending on substrate quality.

\* Coverage figures given are theoretical. Practical coverage rates may vary due to wastage factors and the type, condition, profile and porosity of the substrate.

## Application Conditions

Resin products should not be mixed and laid outside of the range 10 °C to 25 °C. Localised heating or cooling equipment may be required outside this range to achieve ideal temperature conditions. To reduce the risk of "blooming" caused by condensation, the climate above the uncured floor should be maintained at least 3 °C above the dew point until subsequent toppings are applied.

## Surface Preparation

The concrete substrate must be at least 28 days old, sound with a minimum compressive strength of 25 N/mm<sup>2</sup> and a minimum pull off strength of 1.5 N/mm<sup>2</sup>. The substrate must be clean, dry with a moisture content less than 5% (75% RH) and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc. The substrate should be free from rising damp and ground water pressure and contain a functional damp proof membrane. Inadequate preparation will lead to loss of adhesion and failure. Grinding, vacuum-contained shot-blasting or planing is recommended depending on the final finish to be applied. Percussive scabbling or acid etching is not recommended. Refer to the **Resdev Guide to Surface Preparation** for further information.

## Application Instructions

Prior to mixing, the temperature of the three components must be between 15 and 25 °C. Pre-mix the resin component before use. Add the hardener component to the coloured resin component and mix using a low speed electric mixer (300 - 400 rpm) for 1 - 2 minutes until homogeneous. Add the full contents of the filler bag slowly and mix for a further 1-2 minutes until a lump free consistency is obtained. Care should be taken to ensure that any material adhering to the sides and bottom of the mixing vessel is thoroughly mixed in otherwise uncured patches may result.

Once mixed the primer should be applied immediately in a continuous film. Work the primer into the surface using a stiff brush, roller or trowel avoiding pooling. On porous surfaces **Pumadur Primer TC** will be absorbed leaving dry patches. A second coat should be applied to these dry areas to ensure good adhesion and reduce the possibility of air release from the substrate causing bubbles or pin holing in the final topping.

## Resdev Limited

Pumafloor House, Ainleys Industrial Estate  
Elland, West Yorkshire, HX5 9JP, England  
Tel: +44 (0) 1422 379131  
fax: +44 (0) 1422 370943  
info@resdev.co.uk  
www.resdev.co.uk



Resin Development

## Pumadur Primer TC

Polyurethane tack coat primer  
Page 1 of 2  
12/12/13

## Health and Safety

Refer to product Safety Data Sheet before use.

## EU Directive 2004/42/EC

Complies with category j type SB (< 500 g/l VOC content).

## Storage

Materials should be kept dry and stored in a weatherproof building maintained at 15 °C to 20 °C on pallets and away from walls. Consignments should be used in order of batch number. Protect from frost.

## Shelf Life \*

12 months if stored in accordance with the above recommendations.

## Limitations

Do not proceed with application if atmospheric relative humidity is, or is anticipated to be >85% or if the surface temperature is <3 °C above the dew point. Application should not commence when the substrate temperature or the ambient temperature is, or is anticipated to be <10°C during the application or within the curing period.

The information contained in this document, and all further technical advice given is based on our present knowledge and experience. However, it implies no liability or legal responsibility on our part. In particular, no warranty or guarantee of product performance in the legal sense is intended or implied as the conditions of use and the competence of any labour involved in the application are beyond our control. Properties listed are for guidance purposes only. We reserve the right to make any changes according to technological progress or further developments.

Resdev Limited, Pumaflor House, Ainleys Industrial Estate Elland, West Yorkshire, HX5 9JP, England			
CE	13	DOP RV0024	
EN 13813 SR-B2,0 Synthetic resin screed material for use internally in buildings not subject to reaction to fire regulations			
Reaction to fire	NPD	Impact resistance	NPD
Release of corrosive substances	SR	Sound insulation	NPD
Water permeability	NPD	Sound absorption	NPD
Wear resistance	NPD	Thermal resistance	NPD
Bond strength	B2,0	Chemical resistance	NPD

## Resdev Limited

Pumaflor House, Ainleys Industrial Estate  
Elland, West Yorkshire, HX5 9JP, England  
Tel: +44 (0) 1422 379131  
fax: +44 (0) 1422 370943  
info@resdev.co.uk  
www.resdev.co.uk



Resin Development

## Pumadur Primer TC

Polyurethane tack coat primer  
Page 2 of 2  
12/12/13