



REF : RSFO 2011 05

Resufloor 2000

DESCRIPTION

Resufloor 2000 is a self-smoothing epoxy resin seamless floor finish designed to provide a flat hard wearing gloss finish 2 - 3 mm in thickness following the profile of the existing floor.

The system gives aesthetically pleasing results with chemical resistance and durability.

ADVANTAGES

- Seamless
- Hard wearing durable floor for industrial use
- Ease of application
- Hygienic
- Decorative - available in an attractive range of colours
- Excellent abrasion and impact resistance
- Good chemical resistance
- Smooth finish for precise operating equipment

RECOMMENDED USES

- Pharmaceutical production
- Printing and packaging areas
- Television studios
- Automotive production
- Nightclubs
- Domestic studios
- Industrial workshops

PRODUCT INFORMATION

System Thickness (dry)	Solids Content	Pack Size	Pack Make Up	Shelf life	Storage
2 mm to 3 mm	100%	14 kg. & 28 kg.	14 kg. - 1 X Base 1 X Hardener 1 X Aggregate bag 28 kg. - as above, 2 X Aggregate bag	12 Months (Base & Hardener) 12 Months (Aggregate)	Keep out of direct Sunlight. Store in a Dry Place

DRYING TIMES & COVERAGE RATES at 20 ° C

Coverage rate	Pot life	Recoat time	Light traffic	Full traffic	Full chemical cure
7.5 sq m per 28 kg. unit @ 2mm thickness	Including Aggregate 30 Mins	For non-slip seal coats 12-16 Hours (Depending on Temperature)	24 Hours	72 Hours	7 Days



www.resinsurfaces.co.uk

Specification

Product : Resuflor 2000

Finish : Smooth coloured proffile

Thickness : 2 - 3 mm

Colour : Available in a Range Colours

Products required for this system

Prime : Resuprime / R.S Dampshield

System : Resuflor 2000 at Required Thickness

Surface Seal : Not Required

(Except for Resupen WB Matt for a matt finish or Resucoat HB with aggregate for a non-slip finish)

Preparation

To achieve the best performance from **Resuflor 2000** the correct surface preparation is essential. Substrates must be clean, sound, dry and free of surface laitance with a minimum strength of 25N/mm². All surfaces must be prepared by vacuum blasting or mechanical abrasion.

Priming

Resuflor 2000 should be applied onto a cured coat of **Resuprime** solvent free epoxy resin primer, normally applied at 4 sq.m. per kg. Rough or porous surfaces may require an extra coat of **Resuprime** which should be allowed to dry before a second coat is applied. It is essential the primer coat seals the substrate so no air pockets or cavities remain.

If substrates have moisture levels above 75% RH prime the surface with **R.S.Dampshield** (number of coats dependent on moisture content).

Application

Mixing : Pre-mix the coloured component to a uniform colour then mix the entire contents of the base with the hardener. If a separate mixing bucket is being used ensure all contents of both components are removed from the buckets supplied. Mix using a slow speed electric mixer for approximately one to two minutes or until the two components have fully combined then add the aggregate bag or bags.

The mixed unit should be applied immediately.

Resuflor 2000 should be worked with a trowel or float to achieve an even smooth finish. This is best achieved by the application of a smooth even pressure with the compound poured over the correct coverage rate after fixing any stop ends to control the flow of the material.

After 10 - 20 minutes roll the area with a spiked roller to achieve an even smooth surface and remove entrapped air. Do not re-roll the area later.

The surface should be protected from temperatures of less than 10°C and moisture in the early stages of cure, otherwise a loss of gloss or retarded finish could occur.

Optional Anti-Slip Finish

An anti-slip finish can be created by applying one coat of **Resutop** to the cured surface, and then scattering a fine aggregate onto the surface whilst wet. This can then be sealed with a top coat of **Resutop**.

Resutile is recommended as a top coat in areas where very high chemical resistance is required. Please see Data Sheets for **Resutile** and **Resutop**.

Category Guide

FeRFA Category : 5

Technical Information

The following figures are obtained from laboratory tests and our experience with this product .

Slip Resistance Dry > 65
Method BS7976 pt1-3 2002 Wet > 23

The slip resistance of a floor surface can vary as a result of the installation process, conditions at the time of application and subsequent traffic. Inappropriate cleaning or maintenance can adversely affect the performance. For further advice on potential wet areas please consult RSL.

Abrasion Resistance n/a
Method BS8204 /ASTM D4060

Temperature Resistance Tolerant of sustained
temperatures of up to 60 °C

Chemical Resistance Good.
Consult RSL for Further details

Compressive Strength 70 N/mm

Flexural Strength 23 N/mm

Tensile Strength 18 N/mm

VOC 104 g/l

Calculation based on a full mixed unit

Life Expectancy 5 years plus

Subjected to Industrial Traffic

Ease of De-contamination Good
Tested to BS 4247 Part 1

Maintenance and Cleaning

RSL recommend that **Resuflor 2000** should be cleaned with a regular industrial cleaning regime with a floor scrubber utilising **R.S. Industrial Floor Cleaner** or similar with dirty water being removed. Isolated localised cleaning can be carried out using **R.S. Tyre Mark Remover**, **R.S. Fats and Grease Remover** & **R.S. Oil Remover**. All surfaces should be thoroughly rinsed with clean water after the use of chemical cleaners.

Please refer to RSL Data Sheet CLNG for Cleaning Advice

Health and Safety

Resuflor 2000 is formulated from materials designed to achieve the highest level of performance as safely as possible. However, specific components require proper handling and suitable equipment, this information is given in the relevant safety data sheets. In all cases, spillages or skin contamination should be cleaned as soon as practically possible, by dry wiping of the affected area, and thorough washing with soap and water.

The information given in this data sheet is derived from tests and experience with the products and is believed to be reliable. The information is offered without guarantee to enable purchasers to determine for themselves the suitability of the product for their particular application. Any specification or advice given by Resin Surfaces Limited or its agents is based on the information supplied by the purchaser. Resin Surfaces Limited cannot be held accountable for errors or omissions as a result of that information being incorrect or incomplete. No undertakings can be given against infringement of patents. Some materials are derived from natural sources. As such some variation may occur. Site conditions may also contribute to variation in finish and colour.

Resin Surfaces Ltd
Titan House, Lowick, Close
Newby Road Industrial Estate
Stockport
Cheshire
SK7 5ED

Tel : + 44 (0) 161 483 1232 Fax: + 44 (0) 161 483 2565
Email : info@resinsurfaces.co.uk Web : www.resinsurfaces.co.uk
Registered in England : 1659941 Vat No : GB 373 485 624