



Specialist Construction Supplies for Repair, Maintenance, Building & Infrastructure

Epoxy Thixo Inj. Grout Data Sheet

Specification notes

Product: **Epoxy Thixo Inj. Grout**

Supplier:

Arcon Construction Supplies
19-20 Prestwood Court
Leacroft Road
Warrington
WA3 6SB

Tel: **01925 852225**

Email: mail@arconsupplies.co.uk

Web: www.arconsupplies.co.uk

Call **01925 852225** or visit [Arcon Construction Supplies](http://www.arconconstruction.com)
... for more information on our flooring and construction products

[Industrial Flooring](#) | [Concrete Repairs](#) | [Protective and Waterproof Coatings](#)
[Jointing and Paving Mortars](#) | [Anti-slip Floor Paints](#) | [Concrete Repair Mortars](#)

EPOXY THIXOTROPIC INJECTION GROUT

Product Codes

TG89, TG90 Packaging listed overleaf.

Description

Epoxy Thixotropic Injection Grout is a thixotropic two part epoxy resin system. The base resin component is thixotropic plus a low viscosity liquid hardener. Epoxy Thixotropic Injection Grout may be placed using a Tecgrip Gun and Tecgrip Cartridge or may be injected using a suitable hand or mechanical pump. Grouting of gap dimensions 0.1mm to 10mm may be achieved without the use of grout tight shuttering. The two part system gives rapid strength gain obtaining mechanical properties several times those of high quality concrete. The product is non shrink enabling complete fill of the grouting area. The hardened grout is resistant to most chemicals, stable to sea water, petroleum products and resists freeze thaw cycles.

Uses include: Filling and bonding of cracked concrete where grout leakage may occur. Structural support where thin section grouting is required without the use of shuttering

Typical Grout Properties @ 20°C

Useable Times For Grout After Mixing

Temperature °C	5	10	20	30
Useable Time (mins)	80	45	25	10

Compressive Strength N/mm²

Age (Days)	1	3	7
Compressive Strength	50	60	70

Additional Properties

Flexural Strength	58 N/mm ²
Tensile Strength	26 N/mm ²
Slant Shear Strength	55N/mm ²
Elastic Modulus	3.6kN/mm ²
Density	1100kg/m ³
Mixed Grout Viscosity	Thixotropic

Standards

Epoxy Thixotropic Injection Grout has been tested in accordance with the relevant parts of:
BS 6319

Specification Outline

Grouting and filling shall be carried out using Epoxy Thixotropic Injection Grout as manufactured by Parex Ltd.

The product shall be stored, handled and used strictly in accordance with the manufacturer's instructions.

Quality Assurance

Parex Ltd is a firm of Assessed Capability. The Company's quality system conforms to BS EN ISO 9001:2008 and is assessed by UK CARES LTD.

Instructions For Use

Preparation

Ensure that grouting surfaces are free from dust and oily contamination. Small gaps may be blown out using clean dry compressed air. Steel should be free of rust and flaking mill scale. All work surfaces must be essentially dry.

Mixing

Pour all of the hardener from the small bottle into the base container which has sufficient volume to act as the mixing vessel. Thoroughly mix the two components until a homogenous thixotropic product is achieved.

Placing

Supporting Structures

The use of a shutter is recommended although the shutter need not be completely grout tight. The Epoxy Thixotropic Injection Grout will "stay" once the placing pressure is released. The shutter may be constructed from timber and sealed using Rapid Mortar or a suitable silicone sealant. Apply a silicone based release agent to the formwork surfaces which will effect release after the grout has hardened. Alternatively use thick polyethylene sheet.

EPOXY THIXOTROPIC INJECTION GROUT

Instructions For Use

Crack Injection

Drill and fix suitable injection tubes at approximately 300mm centres along the crack-line using Tecgrip CAS Cartridge for fixing the tubes and facing up the crack. Allow prepared crack system to harden, approximately 6 hours at 20°C. Use a Tecgrip Gun or a low pressure pump to inject mixed grout starting at the lowest point of the crack and work upwards to the highest point sealing off each injection point in turn.

Place the mixed grout within the useable time as given in Useable Time data. At the end of the useable time the mix will start to generate a great deal of heat. At this time any unused material should be mixed with sand to reduce the heat output and discarded.

Allow grout to cure for at least 24 hours. Cut off external parts of injection tubes and make good with Polyester Putty. Tools and equipment should be cleaned with Solvent prior to grout setting.

Curing

No special curing practice is required

Precautions

Health and Safety

Epoxy Thixotropic Injection Grout is a resin based product. Resins and solvents may cause allergic reactions in some people. Wear gloves, use barrier cream on unprotected skin areas and wear eye protection when mixing, using and cleaning. Ensure adequate ventilation to prevent inhalation of vapours. If skin contact occurs remove resin immediately with cleansing cream and wash with soap and water. Do not use Solvent. Should eye contact occur rinse immediately with plenty of clean water and seek medical advice. If swallowed do not induce vomiting. Seek medical advice immediately.

Full health and safety data are given in Product Safety Data Sheet.

Fire

Epoxy Thixotropic Injection Grout is classified as non-flammable. Solvent is flammable. Should fire occur extinguish with CO₂ or foam.

Storage And Shelf Life

Epoxy Thixotropic Injection Grout will have a storage life of 12 months in unopened packs when kept in dry conditions at a temperature of between 5°C and 45°C. Storage at higher temperatures and high humidity may reduce shelf life.

Yield

Each 0.30kg pack will yield approximately 250ml of mixed material.

Each 1.19kg pack will yield approximately 1 litre of mixed material.

Packaging And Ordering

Epoxy Thixotropic Injection Grout is supplied in:

0.30kg packs	Product code TG89
1.19kg packs	Product Code TG90

Tecgrip CAS Cartridge is supplied in:

380 ml packs	Product Code TGR 29
--------------	---------------------

Polyester Putty is supplied in:

14.50kg packs	Product Code TP 42
---------------	--------------------

Solvent is supplied in:

5.00 litre tins	Product code TM02
1 litre tins	Product code TM08

For further information and sales please contact your local Parex office as listed below.

Parex Ltd products are guaranteed against defective materials and manufacture. Products are sold subject to the Parex Ltd Terms and Conditions of Sale, copies of which are forwarded on invoice and are available on request. Parex Ltd endeavours to ensure that the above data and any further advice is correct, however, it cannot accept any direct or indirect liability for the use of its products as such usage is beyond its control.