



Specialist Construction Supplies for Repair, Maintenance, Building & Infrastructure

Lokfix Data Sheet

Specification notes

Product: **Lokfix**

Supplier:

Arcon Construction Supplies
19-20 Prestwood Court Leacroft
Road
Warrington
WA3 6SB

Tel: **01925 852225**

Email: mail@arconsupplies.co.uk

Web: www.arconsupplies.co.uk

Call 01925852225 or visit [Arcon Construction Supplies](http://www.arconconstruction.com) website

...for technical, specification & application advice;

or

...for more information on our other repair, maintenance,
engineering and construction specialist products.

[Industrial Flooring](#) | [Concrete Repairs](#) | [Protective and Waterproof Coatings](#)

[Jointing and Paving Mortars](#) | [Anti-slip Floor Paints](#) | [Non-shrink Grouts & Mortars](#)

Lokfix Data Sheet

Polyester resin anchoring grout meeting requirements of BS EN 1504-6: Anchoring of reinforced steel bars.



Uses

Lokfix mix and place anchoring grouts are used for anchoring of steel bars into concrete, brickwork, masonry and rock. Recommended applications include:

- Installation of starter bars
- Base plate bolts
- MOT Bolts
- Installation of balustrades
- Installation of barriers and safety fences
- Installation of tie bars

Advantages

- Easy to mix and apply
- Rapid strength gain
- Vibration resistant
- Corrosion resistant
- Non-expansive
- Can be placed underwater
- Increased flowability
- Two grades specifically for vertical and horizontal / overhead use

Description

Lokfix is a two component polyester anchoring grout supplied in pre-measured quantities. The material cures quickly to give consistent, high performance anchorages. The two versions of Lokfix are available :

Lokfix S25 - Blue lid

Pourable grade, 25 minute gel time at 20°C for use in vertical down holes where the hole is 8 to 40 mm greater in diameter than the bar.

Lokfix P25 - Yellow lid

Thixotropic grade, 25 minute gel at 20°C for use in overhead or horizontal holes where the hole is up to 25 mm greater in diameter than the bar. The thixotropic nature of Lokfix P25 reduces flow of grout out of the hole.


Specification Clause

The anchor grout should be Lokfix S25 pourable grout in vertical downwards holes or Lokfix P25 in horizontal and overhead holes. The anchor grout should comply with the requirements of BS EN1504-6 and have a compressive strength of 100 MPa at 28 days.

Standards compliance

Lokfix S and Lokfix P complies with the requirements of BS EN 1504-6 : Anchoring of reinforced steel bar.

Lokfix S and Lokfix P conforms to the requirements of Highways Agency Interim Advice Note 104/07: The anchorage of reinforcement and fixings in hardened concrete.

 0370	
Fosroc Ltd Drayton Manor Business Park, Coleshill Road, Tamworth, B78 3TL, UK 09 DoP: UK9-07 (Lokfix S25) DoP: UK9-33 (Lokfix P25) 0370-CPR-0845	
Lokfix S25 and Lokfix P25	
EN1504-6: Anchoring of reinforcing steel bar	
Testing of anchoring products by pull out method	≤ 0.6 mm at 75 kN
Chloride ion content	≤ 0.05%
Glass transition temperature	
Lokfix S25:	74 °C
Lokfix P25:	67 °C
Creep under tensile load	≤ 0.6mm
Fire Classification	B
Dangerous substances	Conforms to 5.3

Fosroc® Lokfix

Properties

The following results were obtained at a temperature of 20°C unless otherwise stated.

Test method	Standard	EN 1504-6	Result		
			LokfixS25		Lokfix P25
Testing of anchoring products by pull out method	EN 1881:2006	Displacement < 0.6mm @ 75KN bad	Dry 0.40 mm Wet 0.44 mm		Dry 0.34 mm Wet 0.43 mm
Determination of creep under sustained tensile load	EN 1544:2006	Displacement < 0.6mm after 3 months of continuous 50KN bad	0.47 mm		0.41 mm
Chloride ion content:	EN 1015-17:2000	≤ 0.05%	0.00%		.000%
Determination of glass transition Temperature	EN 12614:2006	> 45°C or > 20°C above ambient	73.5°C		67.2°C
Compressive Strength	EN 12190	-	100 MPa	28 days	100MPa
Tensile Strength	BS 6319 Pt.7	-	11MPa	28 days	11 MPa
Flexural Strength	BS 6319 Pt. 3	-	20 MPa	28 days	19 MPa
Gel time / minimum loading time	-	-	Temp °C	Gel Time	Min loading time (hrs)
			5	130	12
			10	65	5
			20	25	2
			30	10	1
Chemical resistance	-	-	The cured resin is resistant to fresh and salt water, petrol, oils, grease and most acids, alkalis and solvents. Consult Fosroc Technical Services for specific chemical resistance		
Minimum annular gap	-	-	4 mm		
Maximum annular gap	-	-	20 mm		

Clarification of property values: The typical properties given above are derived from laboratory testing. Results derived from field applied samples may vary.

Fosroc® Lokfix

Design Criteria

Selection of grout version

The version of Lokfix grout chosen will depend on anchor conditions (see 'Description').

Parameters of anchor design

The high strength of the cured resin permits strong anchors to be created. Ultimate strength is varied by:


- Strength of host material
- Length of resin bond to bar
- Hole preparation and formation
- Type and dimension of bar

Typical loads attained

Concrete: 20 N/mm² unreinforced.

Bar: Deformed rebar to BS 4449.

Hole: Air-flushed rotary percussive drilled.



Note: The graph illustrates typical failure loads. Minimum safety factors of 1.5 in non-critical and 2 in critical cases should be considered for design purposes. Where relevant, the local codes of practice or standards must also be considered in relation to anchorage length.

Application instructions

Hole preparation and formation

Optimum performance of Lokfix grouts requires rough sided, dust-free holes. Use of rotary percussive drills with air or water flushing is recommended.

Diamond drilled holes should be under-reamed or the surface roughened with a drill steel.

Cast holes should preferably be of inverse dovetail configuration. If parallel sided holes are cast they should be rough to provide adequate keying.

Bar preparation

All bars should be deformed. They should preferably be degreased and all flaky rust removed.

Mixing

A complete pack of resin and catalysed filler should be mixed in one operation. Mixing may be carried out manually or mechanically. When a smooth, even consistency is achieved the grout is ready for use and should be placed well within the gel time of the grout.

Packs have been designed to produce practical and economic volumes of grout.

DO NOT attempt to mix partial pack components.

Installation

Lokfix S25

Using the calculated volume of grout based on the estimating guide table, the grout should be poured steadily into the prepared holes. The anchor bar is then pressed into the hole to the required depth; slight agitation will assist in achieving a complete bond. The bar should be left undisturbed in the required position until the resin is set.

Lokfix P25

The grout should be injected to the rear of the hole to avoid air entrapment. The thixotropic nature of Lokfix P25 will prevent significant flow of resin out of the hole.

Cleaning

Any mixing drums, pumps, etc., should be cleaned with Fosroc Solvent 105 within the pot life of the grout. Cured material can only be removed mechanically.

Supply

Lokfix S25 - Blue Lid

Lokfix P25 - Yellow Lid

The pack consists of a can of resin and a plastic bag of hardener contained in a plastic mixing pail with a snap-on lid. Volume of mixed components: 2.5 litres.

Storage

Store in accordance with the Highly Flammable Liquids and Liquefied Petroleum Gases Regulations 1972. Shelf life of 12 months at 20°C will be reduced at higher temperatures.

Limitations

Fire resistance

Resin anchors should not be used where structural load bearing performance has to be maintained in anchors subjected to fire

Fosroc® Lokfix

conditions. Conbextra GP or Conbextra HF would be suitable in this case. Contact Fosroc Technical Service for advice.

Precautions

Health and safety

For further information see appropriate Product Safety Data Sheet available from www.fosroc.com

Fire

Lokfix products and Fosroc Solvent 105 are flammable. Do not expose to naked flames or other sources of ignition. No Smoking. Containers should be tightly sealed when not in use. In the event of fire, extinguish with CO₂ or foam.

Flash points

Lokfix S25:	29°C
Lokfix P25:	29°C
Fosroc Solvent 105:	43°C

Estimating guide

To find the quantity of material required

The table below indicates the quantity of material in litres required for each 100 mm of hole depth.

Example

- 100 fixings, each using a 20 mm diameter bolt into a 38 mm diameter hole which is 300 mm deep.
- From the table: 20 mm diameter bolt and 38 mm diameter hole gives **0.082 litre** per 100 mm depth of hole therefore **0.082 litre** x 3 (300 mm deep hole) equals **0.246 litre** per hole/fixing.
- As 100 fixings are required: 100 x 0.246 litre = **24.6 litres total.**
- Lokfix S25 and Lokfix P25 are supplied in 2.5 litre packs therefore $24.6/2.5 = 9.84$ 10 packs required

NB: This example and the table below quotes net quantities and makes no allowance for overdrilling the hole or for any wastage. A typical allowance to cover these factors is approximately 10%.

To determine the quantity of material per 100 mm of hole depth

Hole diameter	Bolt diameter								
	12 mm	16 mm	20 mm	25 mm	32 mm	38 mm	44.5 mm	51 mm	57 mm
20 mm	0.020 litre	—	—	—	—	—	—	—	—
25 mm	0.038 litre	0.029 litre	—	—	—	—	—	—	—
32 mm	0.069 litre	0.060 litre	0.049 litre	0.031 litre	—	—	—	—	—
38 mm	—	0.093 litre	0.082 litre	0.064 litre	—	—	—	—	—
45 mm	—	—	0.128 litre	0.110 litre	0.079 litre	0.046 litre	—	—	—
51 mm	—	—	—	0.155 litre	0.124 litre	0.091 litre	—	—	—
57 mm	—	—	—	0.206 litre	0.175 litre	0.142 litre	0.100 litre	—	—
64 mm	—	—	—	0.273 litre	0.241 litre	0.208 litre	0.166 litre	0.117 litre	—
76 mm	—	—	—	—	—	0.340 litre	0.298 litre	0.249 litre	—

Fosroc and Lokfix are trademarks of Fosroc International Limited



Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification of information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it.

Fosroc Limited

Drayton Manor Business Park
Coleshill Road, Tamworth,
Staffordshire B78 3TL. UK

www.fosroc.com

telephone:
+44 (0) 1827 262222

fax:
+44 (0) 1827 262444

email:
enquiryuk@fosroc.com



Certificate number FM 610