



Specialist Construction Supplies for Repair, Maintenance, Building & Infrastructure

## Nulease WB Data Sheet

### Specification notes

Product: **Nulease WB**

Supplier:

**Arcon Construction Supplies**  
**19-20 Prestwood Court**  
**Leacroft Road**  
**Warrington**  
**WA3 6SB**

Tel: **01925 852225**

Email: [mail@arconsupplies.co.uk](mailto:mail@arconsupplies.co.uk)

Web: [www.arconsupplies.co.uk](http://www.arconsupplies.co.uk)

Call 01925852225 or visit [Arcon Construction Supplies](http://www.arconconstruction.com) website

...for technical, specification & application advice;

or

...for more information on our other repair, maintenance,  
engineering and construction specialist products.

[Industrial Flooring](#) | [Concrete Repairs](#) | [Protective and Waterproof Coatings](#)

[Jointing and Paving Mortars](#) | [Anti-slip Floor Paints](#) | [Non-shrink Grouts & Mortars](#)

**Nulease WB Data Sheet**

## Nulease WB

### Water Based Formwork Coating

#### Description

A water based acrylic urethane clear sealer designed for applications onto wood and concrete formwork. This environmentally friendly product is characterised by its rapid drying, hard wearing, non-yellowing properties which gives maximum protection to timber formwork and moulds and helps ensure reproduction of high quality concrete finishes.

#### Advantages

- Non-flammable, low odour formulation.
- Economical in use and equipment may be cleaned with water.
- Fine particle size ensures excellent penetration.
- Easily applied by brush or roller.

#### Technical Information

Drying Time	40-45 min @ 20°C
S.G.	1.04
Coverage	6-8M <sup>2</sup> per litre*
Solids content	30%
Typical dry film thickness	0.05mm

\*Coverage dependant upon timber porosity.

#### Surface Preparation

All surfaces should be clean and free of all contaminants and should not have been previously treated with paints or oils.

#### Application Instructions

Nulease W.B. should be applied at the correct coverage rate using a brush, applicator or roller, thinning should not be necessary. Two coats are normally applied but on very porous surfaces or where a high build is required a third coat may be applied. Subsequent coats may be applied as soon as the previous coat is dry. If more than 24 hours passes in between applications then a light sanding over the area to be coated is recommended. All equipment should be cleaned immediately after use with clean water. Formwork should be allowed to dry for at least 48 hours prior to the application of a release agent and the placing of concrete.

#### Packaging

Nulease W.B. is available in 5 and 25 litre polythene bottles.

#### Health & Safety

Nulease W.B. is non-flammable and is non-hazardous. However normal precautions when handling chemicals must be observed including good skin care and the wearing of goggles. Splashes should be washed from the skin with soap and water before it dries.

#### Storage

Nulease W.B. should be stored at room temperature, protected from frost and kept out of the reach of children. Shelf life is limited to 12 months.



## Limitations

Do not use on concrete which is to be submerged in water. Do not apply below 5°C or in damp or wet conditions or when rain is expected.

## Technical Support

Through our technical department and laboratories we can offer a comprehensive service to specifiers and contractors. Technical representatives are available to provide further information and arrange demonstrations.

## Technical Note

Nulease W.B., when used in accordance with the manufacturers recommendations, does not cause staining. Concrete 'staining' can be caused by a number of factors on which our Technical Department can advise.

