



Specialist Construction Supplies for Repair, Maintenance, Building & Infrastructure

## Renderoc Plug 20 Data Sheet

### Specification notes

Product: **Renderoc Plug 20**

Supplier:

**Arcon Construction Supplies**  
**19-20 Prestwood Court**  
**Leacroft Road**  
**Warrington**  
**WA3 6SB**

Tel: **01925 852225**

Email: [mail@arconsupplies.co.uk](mailto:mail@arconsupplies.co.uk)

Web: [www.arconsupplies.co.uk](http://www.arconsupplies.co.uk)

Call 01925852225 or visit [Arcon Construction Supplies](http://www.arconsupplies.co.uk) website

...for technical, specification & application advice;

or

...for more information on our other repair, maintenance,  
engineering and construction specialist products.

[Industrial Flooring](#) | [Concrete Repairs](#) | [Protective and Waterproof Coatings](#)

[Jointing and Paving Mortars](#) | [Anti-slip Floor Paints](#) | [Non-shrink Grouts & Mortars](#)

**Renderoc Plug 20 Data Sheet**

# Fosroc® Renderoc Plug

constructive solutions

## Rapid setting cement-based, water-stopping mortars conforming to the requirements of BS EN 1504 Class R1

### Uses

For the rapid patching and plugging of concrete segments, concrete and brick tunnel linings, sewage systems, below ground access chambers, pipes, basements, foundations and mines.

### Advantages

- Emergency water-stopping capability
- Single component
- Excellent bond to the substrate
- Low exotherm minimises thermal cracking
- Pre-bagged to overcome variations in site batching
- Chloride-free
- Renderoc Plug 20: Approved for use in public water supplies
- Renderoc Plug 20 : BS6920 listed product.

### Description

Renderoc Plug are rapid setting mortars which are easy to apply to horizontal, vertical or overhead surfaces at a wide range of thicknesses.

There are two grades available: Renderoc Plug 1 with an initial set time of approximately 1 minute, and Renderoc Plug 20 with an initial set time of approximately 20 minutes. (Set times are based on ambient/substrate temperatures of 20°C.)

### Properties

Material tested at a water:powder ratio of 1:3 by volume and temperature at 20°C

| Test method                 | Standard        | EN1504 R1 Requirement | Test result Renderoc Plug 1                           | Test result Renderoc Plug 20                          |
|-----------------------------|-----------------|-----------------------|---|---|
| Compressive Strength        | EN 12190:1999   | ≥ 10 MPa              | @ 1 hour 10 MPa<br>@ 1 day 10 MPa<br>@ 28 days 23 MPa | @ 6 hours 7 MPa<br>@ 1 day 11 MPa<br>@ 28 days 45 MPa |
| Bond strength by pull off   | EN 1542:1999    | ≥ 0.8MPa              | 0.8 MPa @ 28 days                                     | 1.1 MPa @ 28 days                                     |
| Chloride ion content        | EN 1015-17:2000 | ≤ 0.05%               | 0.01%   | 0.01%   |
| Fire rating                 | EN 13501-1      | -                     | Class A1 non-combustible                              | Class A1 non-combustible                              |
| Initial setting time @ 20°C | -               | -                     | Approximately 1 minute                                | Aproximately 20 minutes                               |

**Clarification of property values:** The typical properties given are derived from laboratory testing. Results derived from field applied samples may vary.

## Standards compliance

Renderoc Plug 1 and Renderoc Plug 20 comply with class R1 according to BS EN 1504-3 repair principle 3.1

Renderoc Plug 20: Conforms to:

Regulation 31 of the Water Supply (Water Quality) Regulations 2000

Regulation 31 of the Water Supply (Water Quality) Regulations 2001 in Wales

Regulation 27 of the Water Supply (Water Quality)(Scotland) Regulations 2001

Regulation 30 of the Water Supply (Water Quality) Regulations (Northern Ireland) 2007

|  |                                 |
|--|---------------------------------|
| <br><b>0370</b>                           |                                 |
| <b>Fosroc Ltd</b><br>Drayton Manor Business Park, Coleshill Road, Tamworth, B78 3XN, UK<br><b>09</b><br><b>0370-CPR-0845</b> |                                 |
| <b>DOP: UK9-15</b>   | <b>DOP: UK9-23</b>              |
| <b>Fosroc® Renderoc Plug 1</b>   | <b>Fosroc® Renderoc Plug 20</b> |
| EN1504-3:<br>Structural and non-structural repair method 3   |                                 |
| Compressive strength   | Class R1 ≥ 10 MPa               |
| Chloride ion content   | ≤ 0.05%                         |
| Adhesive bond  | ≥ 0.8 MPa                       |
| Reaction to fire   | Class A1                        |
| Dangerous substance  | Complies with 5.4               |



# Fosroc® Renderoc Plug

## Application instructions

### Preparation

Areas to be patched should be cut back to a depth of 15 mm and given a good mechanical key. Feather-edges must not be allowed. Surface should be brushed clean to remove loose material, dust and laitance. Grease, slime or mould growth should be removed by steam cleaning or high-pressure water jetting. A proprietary degreasing agent should be used for removal of light oil or grease contamination.

To seal leaks, crack openings must be chased out to approximately 20 mm square. The chase should always be undercut to avoid leaving a v-section. All loose material and debris should be removed.

### Mixing

Renderoc Plug should be added to clean water in the following proportions: One part clean water to three parts Renderoc Plug (by volume).

Mix to a stiff consistency in a suitable mixing vessel, using a trowel or gloved hand. Due to the rapid set characteristics of the product, only prepare a quantity of mortar which can be placed within the prescribed set time.

### Application

Trowel apply or hand-knead the mixed mortar in place, ensuring maximum contact with the substrate before the material sets. No priming system is required but the substrate must be in a saturated surface dry state before application.

If being used to plug running water, Renderoc Plug 1 should be used and held in place until the initial set is reached.

The minimum application thickness of Renderoc Plug products is 15 mm.

When using Renderoc Plug 20 as a patch repair product, a maximum bay size of 0.06m<sup>2</sup> is permitted. Linear sections should not exceed 0.25 metres.

### Low temperature working

In cold conditions down to 1°C, the use of warm water (up to 20°C) is advisable to accelerate strength development. Normal precautions for winter working with cementitious materials should be adopted. The material should not be applied when the substrate and/or air temperature is 1°C and falling. At 1°C static temperature or at 1°C and rising, the application

may proceed. Set and cure times will be increased at low temperatures. If in doubt contact the local Fosroc office.

### High temperature working

At ambient temperatures above 35°C, the material should be stored in the shade and cooler water (down to 20°C) used for mixing. Set and cure times will be reduced at high temperatures.

### Curing

For UK wholesome water purposes where contracts require DWI or WRAS certifications, Renderoc Plug 20 should be mixed, applied and cured in accordance with the manufacturer's Instructions For Use sheet (contact Fosroc Technical Helpdesk).

### Cleaning

Renderoc Plug products should be removed from equipment with clean water prior to the initial set. Cured material can only be removed mechanically.

### Estimating

Renderoc Plug 1 is supplied in 6 kg bags each yielding 3 litres.

Renderoc Plug 20 is supplied in 25 kg bags each yielding 12.5 litres.

### Storage

The product has a shelf life of 12 months from the date of manufacture if kept in dry storage in the original, unopened bags. If stored at high temperatures and/or high humidity conditions the shelf life may be reduced to less than 6 months.

### Precautions

#### Health and safety

For further information, refer to the Safety Data Sheets available at [www.fosroc.com](http://www.fosroc.com).

#### Fire

Renderoc Plug products are non-flammable.

Fosroc and Renderoc are trademarks of Fosroc International Limited



#### Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification of information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it.

## Fosroc Limited

Drayton Manor Business Park  
Colleshill Road, Tamworth,  
Staffordshire B78 3XN. UK

[www.fosroc.com](http://www.fosroc.com)

telephone:  
+44 (0) 1827 262222

fax:  
+44 (0) 1827 262444

email:  
[uk@fosroc.com](mailto:uk@fosroc.com)

