



Specialist Construction Supplies for Repair, Maintenance, Building & Infrastructure

Resucoat HB Safety Data Sheet

Safety Data Sheet

Product: **Resucoat HB**

Supplier:

Arcon Construction Supplies
19-20 Prestwood Court
Leacroft Road
Warrington
WA3 6SB

Tel: **01925 852225**

Email: mail@arconsupplies.co.uk

Web: www.arconsupplies.co.uk

Call **01925 852225** or visit [Arcon Construction Supplies](http://www.arconconstruction.com)
... for more information on our flooring and construction products

[Industrial Flooring](#) | [Concrete Repairs](#) | [Protective and Waterproof Coatings](#)
[Jointing and Paving Mortars](#) | [Anti-slip Floor Paints](#) | [Concrete Repair Mortars](#)



RESIN SURFACES LIMITED

SAFETY DATA SHEET, RESUCOAT HB & HBSB

1: IDENTIFICATION OF THE SUBSTANCE/PREPARATION AND OF THE COMPANY:

NAME OF PRODUCT: RESUCOAT HB & HBSB High-build 2-pack epoxy resin floor finish (coloured).

MANUFACTURERS: Resin Surfaces Ltd, Titan House, Lowick Close, Newby Road Industrial Estate, Hazel Grove, Cheshire, SK7 5ED, England

EMERGENCY TELEPHONE: 0161-483 1232.

2: COMPOSITION/INFORMATION ON INGREDIENTS:

A 2-pack system comprising base and hardener which are supplied in separate containers to be mixed together at the site of application.

	% by weight	CAS No.	Hazard Symbols	R-phrases
Composition of base:				
Epoxy resin	20-40%	25068-38-6	Xi	R36/38,43,51,53
Epoxy resin	10-30%	28064-14-4	Xi	R36/38,43
Non-toxic pigments & additives	30-50%			
Benzyl alcohol	5-10%	100-51-6 Xn		R20/22
Xylene (HBSB only)	1-3%	1330-20-7Xn		R10,20/21,38
1-methoxy 2-propanol (HBSB only)	1-3%	107-98-2		R10
Composition of hardener:				
44-isopropylidenediphenol	5-10%	80-05-7	Xi	R36/37/38,43
Benzyl alcohol	25-50%	100-51-6	Xn	R20/22
3-aminomethyl-3,5,5-trimethylcyclohexylamine	25-50%	2855-13-2C		R21/22,34,43 52/53
m-phenylenebis(methylamine)	<10%	1477-55-0C		R22,34
Salicylic acid	<5%	69-72-7	Xn	R22,37/38-41

3: HAZARDS IDENTIFICATION:

Base: Irritating to eyes and skin.
Dangerous to the environment
May cause sensitisation by skin contact.
Toxic to aquatic organisms.
May cause long-term adverse effects in the aquatic environment.

Hardener: Causes burns.
Harmful by inhalation, in contact with skin, and if swallowed.
Causes burns, May cause sensitisation by skin contact.
Harmful to aquatic organisms may cause long term adverse effects in the aquatic environment

4: FIRST AID MEASURES:

Eye contact: Rinse immediately with water, continuing for 15 minutes. Seek medical attention.
Skin contact: Rinse immediately with plenty of soap and water. Remove contaminated clothing. In case of persistent irritation, or if a rash develops, seek medical attention.
Inhalation: Remove the affected person to fresh air and allow to rest.
In case of breathing difficulty, or distress, seek medical attention.
Ingestion: Immediately rinse mouth with water and seek medical attention.
If this is not immediately available, drink 1 or 2 pints of water.

5: FIRE FIGHTING MEASURES:

Special hazards: If involved in a fire, may generate noxious or toxic vapours.
Protective equipment: Fire fighters wear self-contained breathing apparatus.
Extinguishing agents: Foam, dry powder, CO₂ or waterspray.
Disposal: See section 13.

6: ACCIDENTAL RELEASE MEASURES:

Personal precautions: Wear full protective clothing when dealing with a spillage.
Environmental precautions: Prevent from entering sewer system, surface water, or soil.
Methods for cleaning up: Absorb with earth, sand or other absorbent materials.

7: HANDLING AND STORAGE:

Handling: Wear goggles or a face shield, impervious gloves and protective clothing.

Storage: Store in a cool, well ventilated place away from foodstuffs.
Keep containers sealed until mixing.

8: EXPOSURE CONTROLS/PERSONAL PROTECTION:

During application: Wear goggles or a face shield, impervious gloves and protective clothing, and barrier cream. Apply in a well ventilated area. Keep away from food stuffs and feed wash hands before breaks and at the end of working.

9: PHYSICAL AND CHEMICAL PROPERTIES:

Base: Physical state: pigment dispersion in liquid resin.
Colour: varies according to shade of finish required.
Odour: weak odour.
Vapour pressure: <0.01 kPa at 20 °C.
Boiling point: >150 °C
Flash point: >100 °C.
Density: about 1.55 g/cm³ at 20 °C.
Solubility: immiscible with water.
Viscosity: <1 Pa.s at 25 °C.

Hardener: Physical state: free-flowing liquid.
Colour: pale yellow.
Odour: ammoniacal, irritating.
Vapour pressure: about 0.13 kPa at 20 °C.
Boiling point: 205 °C.
Flash point: 105 °C.
Density: about 1.05 g/cm³ at 20 °C.
Solubility: partially miscible with water.
Viscosity: <1 Pa.s at 25 °C.

10: STABILITY AND REACTIVITY:

Base: May react exothermally with amines and mercaptans, also with acids. In case of a fire, carbon monoxide carbon dioxide and other harmful gases may be formed.

Hardener: Reacts exothermally with acids. Liberates ammonia when heated. In case of a fire, toxic fumes of nitrogen oxides, amines and carbon monoxide may be formed. Nitrogen oxide can react with water vapours to form corrosive nitric acid.

11: TOXICOLOGICAL INFORMATION:

Base: LD₅₀ oral, rat: >5000 mg/kg. Epoxy resins such as contained in this product have been shown to cause irritation in humans on skin and eyes. Sensitisation by skin contact may also occur.

Hardener: LD₅₀ oral, not determined for this blend of materials
LD₅₀ benzyl; alcohol 1230 oral LD₅₀ m-phenylenebis(methylamine) 1040 oral .
The amine/diamine constituents of this product are corrosive to skin and irritant to eyes, and may cause sensitisation.

12: ECOLOGICAL INFORMATION:

Environmental precautions: Prevent from entering sewer system, surface water, or soil.
Epoxy resins such as contained in this product have been shown to be toxic to fish and are not readily biodegradable.

13: DISPOSAL CONSIDERATIONS:

Waste: Burn in a hazardous waste incinerator. Do not re-use containers.
Disposal of waste must be in accordance with local / national regulations

14: TRANSPORT INFORMATION:

Base: Hazard labels: Xi Irritant. Contains epoxy constituents, see information supplied by the manufacturer.
ADR, class 9 IMO, IATA: Non classifiable. UN No: 3082 environmentally hazardous liquid n.o.s..

Hardener: ADR/RID: 2735 Corrosive Liquid, NOS (polyamines contains isophoronediamine and m-phenylenebis(methylamine))
8,(C7)iii

IMDG corrosive Liquid, NOS (Polyamines contains Isophoronediamine and m-phenylenebis(methylamine)); 8 UN 2735;

III;

ICAO/IATA: Corrosive Liquid, NOS (polyamines containing Isophoronediamine and m-phenylenebis(methylamine)); 8;
UN 2735; III; FP 105C;

15: REGULATORY INFORMATION:

Base: Hazard labels: Xi Irritant, contains epoxy constituents, see information supplied by the manufacturer.

N Dangerous to the environment

R-phrases: R36/38 Irritating to eyes and skin.

R43 May cause sensitisation by skin contact.

R51/53 Toxic to aquatic organisms, may cause long-term adverse effects in the aquatic environment.

S-phrases: S26 In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.

S28 After contact with skin, wash immediately with plenty of soap and water.

S36 Wear suitable protective clothing.

S61 Avoid release to the environment. Refer to special instructions/safety data sheet.

Hardener: Hazard labels: C Corrosive.

R-phrases: R20/21/22 Harmful by inhalation, in contact with skin and if swallowed.

R34 Causes burns.

R43 May cause sensitisation by skin contact.

R52/53 Harmful to aquatic organisms, may cause long term effects to the aquatic environment

S-phrases: S9 Keep container in well ventilated place

S20 When using do not eat or drink

S26 In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.

S36/37/39 Wear suitable protective clothing, gloves and eye/face protection.

S45 In case of accident or if you feel unwell, seek medical advice immediately (show the label where possible)

S61 Avoid release to the environment (refer to special instructions / datasheet)

16: OTHER INFORMATION:

Liquid epoxy resins are classified as dangerous to the environment under a voluntary agreement by the Association of Plastic Manufacturers Europe (APME) based on available data. Resin Surfaces Limited have adopted this practice as part of their duty of care under the Environmental Protection Act 1992.

The base and hardener are mixed together in the approximate ratio as follows:

base: 80-90% by weight

hardener: 10-20% by weight

All the foregoing information should be regarded as being applicable to the finished paint as well as to the individual base and hardener components.

Revision Major components 10/01

Hardener 07/03