



Specialist Construction Supplies for Repair, Maintenance, Building & Infrastructure

## Resucove LW Data Sheet

### Specification notes

Product: **Resucove LW**

Supplier:

**Arcon Construction Supplies**  
**19-20 Prestwood Court**  
**Leacroft Road**  
**Warrington**  
**WA3 6SB**


Tel: **01925 852225**

Email: [mail@arconsupplies.co.uk](mailto:mail@arconsupplies.co.uk)

Web: [www.arconsupplies.co.uk](http://www.arconsupplies.co.uk)

Call **01925 852225** or visit [Arcon Construction Supplies](http://www.arconconstruction.com)  
... for more information on our flooring and construction products

[Industrial Flooring](#) | [Concrete Repairs](#) | [Protective and Waterproof Coatings](#)  
[Jointing and Paving Mortars](#) | [Anti-slip Floor Paints](#) | [Concrete Repair Mortars](#)



REF : CVLW 2011 05

# Resucove LW

## DESCRIPTION

Resucove LW is a lightweight epoxy screed designed for the formation of coving and surface rendering to vertical surfaces. The sealing of the surface is recommended to provide an impervious finish and improve cleanability. Resucove LW is normally installed at 4mm thickness on vertical applications.

## ADVANTAGES

- Lightweight for coving and render
- Low Odour, safe for to install into Food Production areas
- Durable
- Ease of application
- Can be feather edged
- Decorative - available in an attractive range of colours
- Can be used for localised repairs
- Good chemical resistance

## RECOMMENDED USES

- Food production and storage
- Printing and packaging areas
- Engineering facilities
- Automotive industry
- Aerospace production areas
- Industrial workshops
- Chemical production facilities

## PRODUCT INFORMATION

System thickness (dry)	Solids content	Pack sizes	Pack make up	Shelf life	Storage
4 mm	100%	24 Kg.	24 kg. unit - 1 X Base 1 X Hardener 1 X Aggregate bag	12 Months (Base & Hardener) 12 Months (Aggregate)	Keep out of direct Sunlight Store in a Dry Place

## DRYING TIMES & COVERAGE RATES at 20 ° C

Coverage rate	Pot life	Recoat time	Light use	Full use	Full chemical cure
1.7 kg. will cover 1 sq m @ 1mm	Including Aggregate 30 Mins	For Seal Coats 8 Hours (Depending on Temperature)	24 Hours	72 Hours	Up to 7 Days



## Specification

Product : Resucove LW

Finish : Light Textured Coloured Finish

Thickness : 4 mm

Colour : Available in a Range Colours

## Products required for this system

Prime : R.S. Tack Primer

System : Resucove LW at required thickness

Surface Seal : Resucoat HB and or Resupen WB

## Preparation

To achieve the best performance from **Resucove LW** the correct surface preparation is essential. Substrates must be clean, sound, dry and free of surface laitance. Surfaces can be prepared by light mechanical abrasion.

When applying as a cove consideration should be given to the fixing of any profile and cutting a toe-in in the floor to improve anchorage and the visual appearance of the cove. This should be undertaken prior to the priming and dust etc. removed.

## Priming

**Resucove LW** can be applied onto a tack coat of **R.S. Tack Primer** solvent free epoxy resin primer, normally applied at 4 sq.m. per kg. Apply **R.S. Tack Primer** and allow to become 'tacky' (but not cured). See **R.S. Tack Primer** Data sheet for the instructions for the use of this product.

## Application Method

**Resucove LW** is a three component mix. The base and hardener components should first be mixed for one minute, then the aggregate added and mixed for a further two minutes until a homogeneous mix is achieved. This is then applied into the tacky **R.S. Tack Primer** with a float or coving trowel and worked to compress the material and form a uniform dense finish. The surface should be protected from temperatures of less than 10°C and moisture in the early days of cure. Sealing is necessary to ensure an impervious surface; typically **Resucoat HB** for coving and **Resupen WB** for wall render applications.

All coving can be sealed using a variety of seal coats listed in the RSL range such as **Resutop**, **Resucoat HB** and **Resuthane T100**.

## Category Guide

FeRFA Category : n/a

## Technical Information

The following figures are obtained from laboratory tests and our experience with this product .

Slip Resistance	Dry n/a
Method BS7976 pt1-3 2002	Wet n/a

The slip resistance of a floor surface can vary as a result of the installation process, conditions at the time of application and subsequent traffic. Inappropriate cleaning or maintenance can adversely affect the performance. For further advice on potential wet areas please consult RSL.

Abrasion Resistance	n/a
Method BS8204 /ASTM D4060	

Temperature Resistance	Tolerant of sustained temperatures of up to 60 °C
------------------------	---

Chemical Resistance	Good. Consult RSL for Further details
---------------------	--

Compressive Strength	N/mm <sup>2</sup>
----------------------	-------------------

Flexural Strength	N/mm <sup>2</sup>
-------------------	-------------------

Tensile Strength	N/mm <sup>2</sup>
------------------	-------------------

VOC	1 g/l
-----	-------

Calculation based on a full mixed unit

Life Expectancy	6 years plus
-----------------	--------------

Subjected to Industrial use  
RSL terms and conditions will apply  
Coatings may need to be re applied

## Maintenance and Cleaning

RSL recommend that **Resucove LW** should be cleaned with a regular industrial cleaning regime with a floor scrubber utilising **R.S. Industrial Floor Cleaner** or similar with dirty water being removed. Isolated localised cleaning can be carried out using **R.S. Tyre Mark Remover**, **R.S. Fats and Grease Remover** & **R.S. Oil Remover**. All surfaces should be thoroughly rinsed with clean water after the use of chemical cleaners.

**Please refer to RSL Data Sheet CLNG for Cleaning Advice**

## Health and Safety

**Resucove LW** is formulated from materials designed to achieve the highest level of performance as safely as possible. However, specific components require proper handling and suitable equipment, this information is given in the relevant safety data sheets. In all cases, spillages or skin contamination should be cleaned as soon as practically possible, by dry wiping of the affected area, and thorough washing with soap and water.

The information given in this data sheet is derived from tests and experience with the products and is believed to be reliable. The information is offered without guarantee to enable purchasers to determine for themselves the suitability of the product for their particular application. Any specification or advice given by Resin Surfaces Limited or its agents is based on the information supplied by the purchaser. Resin Surfaces Limited cannot be held accountable for errors or omissions as a result of that information being incorrect or incomplete. No undertakings can be given against infringement of patents. Some materials are derived from natural sources. As such some variation may occur. Site conditions may also contribute to variation in finish and colour.

Resin Surfaces Ltd  
Titan House, Lowick, Close  
Newby Road Industrial Estate  
Stockport  
Cheshire  
SK7 5ED

Tel : + 44 (0) 161 483 1232 Fax: + 44 (0) 161 483 2565  
Email : info@resinsurfaces.co.uk Web : www.resinsurfaces.co.uk  
Registered in England :1659941 Vat No : GB 373 485 624