



Specialist Construction Supplies for Repair, Maintenance, Building & Infrastructure

Resupatch Data Sheet

Specification notes

Product: **Resupatch**

Supplier:

Arcon Construction Supplies
19-20 Prestwood Court
Leacroft Road
Warrington
WA3 6SB

Tel: **01925 852225**

Email: mail@arconsupplies.co.uk

Web: www.arconsupplies.co.uk

Call 01925852225 or visit [Arcon Construction Supplies](http://www.arconconstruction.com) website

...for technical, specification & application advice;

or

...for more information on our other repair, maintenance,
engineering and construction specialist products.

[Industrial Flooring](#) | [Concrete Repairs](#) | [Protective and Waterproof Coatings](#)

[Jointing and Paving Mortars](#) | [Anti-slip Floor Paints](#) | [Non-shrink Grouts &](#)

[Mortars](#)

Resupatch Data Sheet



Resupatch

Revised 12/2017—Issue 1: REF : PAST 2016 06

DESCRIPTION

Resupatch is a two-pack easy to use epoxy resin mortar, with excellent mechanical properties. This makes it ideal for rapid repair of concrete surfaces in heavy duty environments.

ADVANTAGES

- Hard wearing durable repairs for Industrial Use
- Ease of application
- Minimum surface preparation
- Can be feather edged
- Excellent abrasion and impact resistance
- Concrete like in appearance
- Dust-free

RECOMMENDED USES

- Any sound concrete requiring repairs
- Warehouse areas
- Chemical production and storage
- Printing and packaging areas
- Engineering facilities
- Automotive industry
- Aerospace production areas
- Industrial workshops

PRODUCT INFORMATION

System thickness (DFT)	Dependent upon Requirement
Solids Content by weight	100%
Pack Sizes	5kg & 10kg
Pack make up	1 x Base 1 x Hardener 1 x Aggregate
Shelf Life	12 months (Base, Hardener & Aggregate)
Storage	Keep out of direct sunlight. Store in a dry place, not below 15°C

DRYING TIMES & COVERAGE RATES at 20°C

Coverage rate (Theoretical)	5kg will cover 0.5m ² at 5mm thickness (This is only a guide and coverage will depend on the type and size of repairs being carried out)
Pot life	30 Minutes
Recoating intervals	For Seal Coats, 12 - 16 Hours
Light traffic	24 hours
Full traffic	72 hours
Full chemical cure	Up to 7 days



