



Specialist Construction Supplies for Repair, Maintenance, Building & Infrastructure

## Resuprime ZP Data Sheet

### Specification notes

Product: **Resuprime ZP**

Supplier:

**Arcon Construction Supplies**  
**19-20 Prestwood Court**  
**Leacroft Road**  
**Warrington**  
**WA3 6SB**

Tel: **01925 852225**

Email: [mail@arconsupplies.co.uk](mailto:mail@arconsupplies.co.uk)

Web: [www.arconsupplies.co.uk](http://www.arconsupplies.co.uk)

Call **01925 852225** or visit [Arcon Construction Supplies](http://www.arconconstruction.com)  
... for more information on our flooring and construction products

[Industrial Flooring](#) | [Concrete Repairs](#) | [Protective and Waterproof Coatings](#)  
[Jointing and Paving Mortars](#) | [Anti-slip Floor Paints](#) | [Concrete Repair Mortars](#)



REF : PRZP 2011 05

# Resuprime ZP

## DESCRIPTION

Resuprime is a two-pack solvent-free epoxy resin zinc phosphate priming coat, designed for easy application, with good surface wetting properties.

Resuprime ZP is principally designed to bond thin section resin based screeds and toppings to steel and ferrous structures.

## ADVANTAGES

- Excellent adhesion to prepared metal
- Versatile for varied applications
- Low odour
- Solvent free
- Ease of application

## RECOMMENDED USES

- As a metal primer for metal mezzanine areas, bridge decks, loading bays and ramps
- As a metal primer for Resucrete
- As a metal primer for Resuscreed 43 & 50
- As a metal primer for Resuscreed Quartz
- As a metal primer for Resuflor
- As a metal primer for R.S. Terrazzo
- As a metal primer for R.S. Terrain

## PRODUCT INFORMATION

| System thickness (dry) | Solids content by weight | Pack sizes | Pack make up            | Shelf life                     | Storage   |
|------------------------|--------------------------|------------|-------------------------|--------------------------------|---|
| 200 microns            | 100%                     | 5 kg.      | 1x Base<br>1 x Hardener | 12 Months<br>(Base & Hardener) | Keep out of direct Sunlight.<br>Store in a dry place, not below 15° |

## DRYING TIMES & COVERAGE RATES at 20 ° C

| Coverage rate                                    | Pot life               | Recoat time                                | Light traffic | Full traffic | Full chemical cure |
|--|------------------------|--|---------------|--------------|--------------------|
| 5 kg. will cover 20 sq m @ 200 microns thickness | 30 Minutes from mixing | 6 hours or once surface has lost tackiness | 24 Hours      | 34 -36Hours  | Up to 7 Days       |



[www.resinsurfaces.co.uk](http://www.resinsurfaces.co.uk)

## Specification

Product : Resuprime ZP

Finish : Grey Gloss

Thickness : 200 microns

Colour : Grey

## Products required for this system

Prime : Resuprime ZP

System : As specified

Surface Seal : As specified

## Preparation

**Resuprime ZP** provides excellent adhesion both as a tack coat and primer.

All surfaces should be thoroughly cleaned to remove oils and grease, ideally shotblasted to SA 2.5 or better (Bright Steel), or mechanically abraded to remove all rust, mill scale, loose or flaky paint. Compatibility tests should be undertaken prior to overcoating existing paint, please consult RSL's Technical Department.

## Application

The ambient temperatures of the areas should not be allowed to fall below 10°C throughout the application and the curing period, as this could have an adverse effect on the appearance and colour of the system. Surface temperature must be above 5°C.

Where possible it is recommended that the application area is heated to a minimum temperature of 15°C ideally to allow the ambient and substrate temperature to stabilise prior to installation.

**Mixing:** Mix the entire contents of the base with the hardener. If a separate mixing bucket is being used mix thoroughly ensuring all contents of both components are removed from the buckets supplied. Mix using a slow speed electric mixer for approximately two minutes or until the two components have fully combined.

The mixed unit should be applied immediately by roller or brush with a consistent procedure. Floor areas should be cross-rolled to ensure even application and to minimise roller marks.

## Category Guide

FeRFA Category : 2

## Technical Information

The following figures are obtained from laboratory tests and our experience with this product .

|                          |     |     |
|--------------------------|-----|-----|
| Slip Resistance          | Dry | n/a |
| Method BS7976 pt1-3 2002 | Wet | n/a |

The slip resistance of a floor surface can vary as a result of the installation process, conditions at the time of application and subsequent traffic. Inappropriate cleaning or maintenance can adversely affect the performance. For further advice on potential wet areas please consult RSL.

|                           |     |
|---------------------------|-----|
| Abrasion Resistance       | n/a |
| Method BS8204 /ASTM D4060 |     |

|                        |  |
|------------------------|--|
| Temperature Resistance | Tolerant of sustained temperatures of up to 60°C |
|------------------------|--|

|                     |   |
|---------------------|---|
| Chemical Resistance | Good Chemical Resistance<br>Consult RSL on specific materials |
|---------------------|---|

|                      |     |
|----------------------|-----|
| Compressive Strength | n/a |
|----------------------|-----|

|                   |     |
|-------------------|-----|
| Flexural Strength | n/a |
|-------------------|-----|

|                  |     |
|------------------|-----|
| Tensile Strength | n/a |
|------------------|-----|

|     |        |
|-----|--------|
| VOC | 73 g/l |
|-----|--------|

Calculation based on a full mixed unit

|                 |                             |
|-----------------|-----------------------------|
| Life Expectancy | 4 years plus as a seal coat |
|-----------------|-----------------------------|

Subjected to Industrial Traffic  
RSL terms and conditions will apply

## Maintenance and Cleaning

n/a if used as a primer

RSL recommend that **Resuprime ZP** should be cleaned with a regular industrial cleaning regime with a floor scrubber utilising **R.S. Industrial Floor Cleaner** or similar with dirty water being removed. Isolated localised cleaning can be carried out using **R.S. Tyre Mark Remover**, **R.S. Fats & Grease Remover** & **R.S. Oil Remover**. All surfaces should be thoroughly rinsed with clean water after the use of chemical cleaners.

**Please refer to RSL Data Sheet CLNG for Cleaning Advice**

## Health and Safety

**Resuprime ZP** is formulated from materials designed to achieve the highest level of performance as safely as possible. However, specific components require proper handling and suitable equipment, this information is given in the relevant safety data sheets. In all cases, spillages or skin contamination should be cleaned as soon as practically possible, by dry wiping of the affected area, and thorough washing with soap and water.

The information given in this data sheet is derived from tests and experience with the products and is believed to be reliable. The information is offered without guarantee to enable purchasers to determine for themselves the suitability of the product for their particular application. Any specification or advice given by the Resin Surfaces Limited or its agents is based on the information supplied by the purchaser. Resin Surfaces Limited cannot be held accountable for errors or omissions as a result of that information being incorrect or incomplete. No undertakings can be given against infringement of patents. Some materials are derived from natural sources. As such some variation may occur. Site conditions may also contribute to variation in finish and colour.

Resin Surfaces Ltd  
Titan House, Lowick, Close  
Newby Road Industrial Estate  
Stockport  
Cheshire  
SK7 5ED

Tel : + 44 (0) 161 483 1232 Fax: + 44 (0) 161 483 2565  
Email : info@resinsurfaces.co.uk Web : www.resinsurfaces.co.uk  
Registered in England : 1659941 Vat No : GB 373 485 624