



Specialist Construction Supplies for Repair, Maintenance, Building & Infrastructure

Sikafloor Proseal Pro Data Sheet

Specification notes

Product: **Sikafloor Proseal Pro**

Supplier:

Arcon Construction Supplies

19-20 Prestwood Court

Leacroft Road

Warrington

WA3 6SB

Tel: **01925 852225**

Email: mail@arconsupplies.co.uk

Web: www.arconsupplies.co.uk

Call **01925 852225** or visit [Arcon Construction Supplies](http://www.arconconstruction.com)
... for more information on our flooring and construction products

[Industrial Flooring](#) | [Concrete Repairs](#) | [Protective and Waterproof Coatings](#)
[Jointing and Paving Mortars](#) | [Anti-slip Floor Paints](#) | [Concrete Repair Mortars](#)

Sikafloor®-ProSeal Pro

Curing compound for concrete floors

Product Description

Sikafloor®-ProSeal Pro is a one part low odour clear acrylic resin polymer solution used to cure, harden and seal fresh or hardened concrete.

Uses

- Sikafloor®-ProSeal Pro is used for curing and sealing of fresh concrete floors.
- Provides curing and sealing for Sikafloor® dry shake hardeners
- Suitable for exterior and interior application

Characteristics / Advantages

- One coat application
- Helps control dusting for both new and existing concrete floor surfaces
- Effectively cures and seals concrete surfaces in a single, economic operation
- Non yellowing
- Easy application by spray or roller

Tests

Approval / Standards

Conforms to the requirements of ASTM C-309 for curing liquids type 1, ASTM C-156 for water retention and ASTM D-4060 for improvement of abrasion resistance

Product Data

Form

Appearance / Colours

Clear liquid, clear when cured.

Packaging

25 l metal cans and 200 l metal drums.

Construction



Storage

Storage Conditions / Shelf Life

12 months from date of production, if stored properly in original, unopened and undamaged sealed containers, in dry conditions at temperatures between +5°C and +30°C. Protect from frost.

Technical Data

Chemical Base

Acrylic resin polymer in solution

Density

~ 0.9 kg/l (at +20°C)

Mechanical / Physical Properties

Resistance

Chemical Resistance

The product is not intended for chemical exposure.

System Information

System Structure

All applications 1-2 coats.

Application Details

Consumption / Dosage

0.1 - 0.2 l / m² / coat. (5 - 10 m² / l / coat)

To conform with ASTM C-309, ensure a total of 0.2 l/m² is applied.

This figure is theoretical and does not include for any additional material required due to surface porosity, surface profile, variations in level and wastage, etc.

Substrate Quality

Fresh concrete:

Surface must be free of bleed water and of sufficient strength to withstand finishing operations.

Hardened / old concrete:

Surfaces must be sound, open textured, clean, free from frost, laitance, surface water, oil, grease, coatings, all loosely adhering particles and other surface contaminants.

If in doubt apply a test area first.

Substrate Preparation

Fresh concrete:

The concrete must be prepared by suitable power or manual floating/tamping techniques.

Hardened / old concrete:

The substrate must be prepared by suitable mechanical preparation techniques such as high-pressure water or abrasive blast cleaning equipment.

All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush and/or vacuum.

Application Conditions / Limitations

Substrate Temperature	+5°C min. / +30°C max.
Ambient Temperature	+5°C min. / +30°C max.
Relative Air Humidity	80% r.h. max.
Dew Point	Beware of condensation! The substrate and uncured floor must be at least 3°C above dew point to reduce the risk of condensation or blooming on the floor finish.

Application Instructions

Mixing	Sikafloor®-ProSeal Pro is supplied ready for use. Stir thoroughly before use.
Mixing Time	2 minutes.
Mixing Tools	Electric stirrer with low speed (~ 300 rpm).

Application Method / Tools	For fresh concrete, apply immediately after finishing techniques have been completed. Apply in a continuous even film by low-pressure spray unit. The suitability of spraying equipment must be confirmed by trials. Application also possible by brush or roller. To achieve the highest visual aesthetics and performance, a second coat is recommended. Wait for first coat to dry tack free before applying a second coat.
-----------------------------------	---

Cleaning of Tools	Clean all tools and application equipment with Thinners C immediately after use. Hardened / cured material can only be mechanically removed.
--------------------------	--

Waiting Time / Overcoatability	Allow previous coats to become tack free before applying additional coats. Drying will be affected by changing substrate and ambient conditions, particularly temperature and relative humidity.
---------------------------------------	---

Notes on Application / Limitations	In hot weather (above +25°C) store Sikafloor®-ProSeal Pro in a cool place prior to use. In low temperatures (below +5°C) the product may thicken and be difficult to spray, store in a warm place. Do not use sprayers, which have been used to spray silicones or release agents. Do not mix differing formulations of Sika® or other curing membranes. Ensure spraying equipment is cleaned thoroughly before use and residues of previous membranes are removed. Sikafloor®-ProSeal Pro must be removed prior to the application of a coating system. Sikafloor®-ProSeal Pro increases abrasion resistance compared to untreated C25 concrete, but will gradually de-grade and be removed by environmental exposure conditions and trafficking.
---	--

Curing Details

Applied Product ready for use

Substrate temperature	+10°C	+20°C	+30°C
Foot traffic	~ 16 hours	~ 8 hours	~ 6 hours
Full cure	~ 24 hours	~ 20 hours	~ 16 hours

Note: Times are approximate and will be affected by changing ambient and substrate conditions.

Cleaning / Maintenance

Methods To maintain the appearance of the floor after application, Sikafloor® -ProSeal® W must have all spillages removed immediately and must be regularly cleaned using rotary brushes, mechanical scrubbers, scrubber dryers, high pressure washers, wash and vacuum techniques, etc., using suitable detergents and waxes.

Value Base All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Local Restrictions Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

Health and Safety Information For information and advice on the safe handling, storage and disposal of chemical products, users should refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

Legal Notes The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



Sika Limited
 Watchmead
 Welwyn Garden City
 Hertfordshire
 AL7 1BQ
 United Kingdom

Phone +44 1707 394444
 Telefax +44 1707 329129
www.sika.co.uk, email: sales@uk.sika.com

