



Specialist Construction Supplies for Repair, Maintenance, Building & Infrastructure

## SikagROUT 212 Data Sheet

### Specification notes

Product: **SikagROUT 212**

Supplier:

**Arcon Construction Supplies**  
**19-20 Prestwood Court**  
**Leacroft Road**  
**Warrington**  
**WA3 6SB**

Tel: **01925 852225**

Email: [mail@arconsupplies.co.uk](mailto:mail@arconsupplies.co.uk)

Web: [www.arconsupplies.co.uk](http://www.arconsupplies.co.uk)

Call **01925 852225** or visit [Arcon Construction Supplies](http://www.arconconstruction.com)  
... for more information on our flooring and construction products

[Industrial Flooring](#) | [Concrete Repairs](#) | [Protective and Waterproof Coatings](#)  
[Jointing and Paving Mortars](#) | [Anti-slip Floor Paints](#) | [Concrete Repair Mortars](#)

**Product Data Sheet**  
Edition 18/09/2006  
Identification no:  
02 02 01 01 001 0 000002  
SikaGrout® 212

# SikaGrout® 212

## Flowable Shrinkage Compensated Cementitious Grout

### Product Description

SikaGrout 212 is a one part flowable shrinkage compensated cementitious grout.

#### Uses

- Under stanchion plates
- Void filling
- Concrete repairs
- Machine base plates
- For exterior and interior use

#### Characteristics / Advantages

- Excellent flow properties
- Pre batched for quality
- Just add water
- Compatible with **Sika® FerroGard®** corrosion inhibitors
- High compressive strength gain
- Easy to mix and apply
- Excellent bond to concrete
- Contains no chloride admixtures
- Overcoatable with **Sika** reprofiling/levelling mortars and coatings
- Low shrinkage
- Generally more durable than equivalent class of concrete
- Does not segregate or bleed
- Fire rating and protection properties comparable to concrete
- Can be pumped or poured
- Good mechanical properties
- Grouting thickness between 10-75 mm

### Product Data

#### Form

**Appearance / Colour** Grey powder

**Packaging** 25 kg bags

#### Storage

**Storage Conditions / Shelf-Life** 9 months from date of production if stored properly in dry conditions in undamaged and unopened original sealed packaging.



## Technical Data

<b>Chemical Base</b>	Cement, selected fillers and aggregates, special additives
<b>Density</b>	~ 2200 kgm <sup>3</sup> (wet density)
<b>Layer Thickness</b>	10 mm min. / 75 mm max.

## Mechanical / Physical Properties

**Compressive Strength** Ambient temperature: +20 °C

1 day	3 days	7 days	28 days
~ 18-20 N/mm <sup>2</sup>	~ 35-40 N/mm <sup>2</sup>	~ 40-45 N/mm <sup>2</sup>	~ 50-55 N/mm <sup>2</sup>

**Early Expansion** 0.25 – 0.50%

## System Information

### Application Details

**Consumption** 2.2 kg/m<sup>2</sup>/mm (2.2 kg/litre) Excluding allowances for loss wastage, surface profile and porosity.

### Substrate Quality

*Concrete, mortar, stone:*

Surfaces must be sound, clean, free from ice, oils, grease, standing water and any loose or friable particles and any other surface contaminants.

The concrete "pull off" (tensile) strength should be > 1.0 MPa.

*Steel, iron:*

Clean, free from oil or grease, rust and scale etc.

*Shutter/Formwork:*

All formwork should be of adequate strength, treated with release agent and sealed to prevent leakage. Sealing can be achieved by using **Sikaflex® -11FC+** sealant beneath or around formwork and between joints. Ensure formwork includes outlets for extraction of the pre-soaking water. A header box/hopper should be constructed on one side of the formwork so that a grout head of 150-200 mm can be maintained during the grouting operation.

### Substrate Preparation

The substrate should be prepared by suitable mechanical preparation techniques such as high pressure water jetting, breakers, blastcleaning, scabblers, etc. The concrete substrates should be pre-soaked with clean water continuously for 2 - 6 hours to ensure a saturated surface dry condition throughout the operation.

Immediately before pouring grout, remove *all* excess or standing water from within any formwork, cavities or pockets.

---

**Application Conditions / Limitations**

---

**Substrate Temperature** +5°C min. / +30°C max.

---

**Ambient Temperature** +5°C min. / +30°C max.

---

**Application Instructions**

---

**Mixing** Measure the appropriate amount of water to achieve the desired grout consistency given in the table below. Heat water if necessary to achieve a temperature between 15-20°C.

Water addition rate per 25 kg bag	
Pourable consistency	2.3 – 3.9 litres
Flowable consistency	

---

**Mixing Time** 2 minutes minimum

---

**Mixing Tools** Place the water into a forced action grout mixer or in a clean drum. Slowly add complete bag of **SikaGrout® 212** into the water and continuously mix for 2 minutes in mixer to achieve a uniform and lump free consistency. Alternatively use a slow speed drill (200-500 rpm) and helical mixer.

Dependent on the desired consistency and flow properties, the mixing ratio can be adjusted.

---

**Application Method** Pour the mixed grout into the header box/hopper ensuring continuous grout flow during the complete grouting operation to avoid trapping air. Use steel banding or chains to assist flow where necessary. For large volume placement, grout pumps are recommended.

---

**Cleaning of Tools** Clean all tools and application equipment with water immediately after use. Hardened/cured material can only be mechanically removed.

---

**Notes on Application / Limitations**

- Do not exceed water addition
- Not to be used for patch repair works
- Do not use vibrating poker
- Use only on clean, sound substrate
- Do not apply when there is a risk of frost
- Pour or pump from one side only
- Keep exposed surfaces to a minimum

---

**Curing Details**

---

**Curing Treatment** After the grout has initially hardened, remove formwork and trim edges while concrete is 'green'. Cure all exposed grout surfaces using **SikaFloor® ProSeal**.

In cold weather apply heat blankets to maintain a constant temperature.

---

**Value Base** All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

---

**Local Restrictions** Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

---

## Health and Safety Information

For information and advice on the safe handling, storage and disposal of chemical products, users should refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

## Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



Sika Limited  
Watchmead  
Welwyn Garden City  
Hertfordshire  
AL7 1BQ  
United Kingdom

Phone +44 1707 394444  
Telefax +44 1707 329129  
[www.sika.co.uk](http://www.sika.co.uk), email: [sales@uk.sika.com](mailto:sales@uk.sika.com)



ISO 14001 ISO 9001