



# New Guard Coatings Group

A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

[www.newguardcoatings.com](http://www.newguardcoatings.com)

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND

# PRODUCT DATA SHEET

# EVERBUILD® ANCHORSET® RED 300

## HIGH PERFORMANCE 2 PART STYRENE BASED RAPID CURING CHEMICAL ANCHORING SYSTEM

### PRODUCT DESCRIPTION

EVERBUILD® ANCHORSET® RED 300 is a styrene based chemical anchor in a new easy to use twin bag system operated by a standard sealant gun, therefore easy to use by a general builder. Perfect for high strength fixing of satellite dish mountings, gate hinges, balcony rails etc.

### USES

- Fixing wall ties
- Bolts and screws into a wide range of building substrates
- Securing machinery into floors
- Fixing studs and starter bars
- For concrete, solid or hollow masonry and solid rock

### CHARACTERISTICS / ADVANTAGES

- Easy mix twin bag system
- Rapid curing system
- Great for concrete, solid or hollow masonry and solid rock
- High chemical resistance
- Complete with mixer nozzle

### APPROVALS / STANDARDS

- ETAG 001 Part 5 Option 7 for threaded bars (M8-M24) in galvanized steel 5.8-8.8 & 10.9 and Stainless Steel A4-70; A4-80 & HCR (1.4529) in C20/25 to C50/60 uncracked concrete
- Tested according to LEED 2009 EQ c4.1, SCAQMD rule 1168 (2005)

### PRODUCT INFORMATION

<b>Chemical Base</b>	Styrene based
<b>Packaging</b>	300ml cartridge
<b>Shelf Life</b>	12 months from date of manufacture.
<b>Storage Conditions</b>	To be stored between +5 minimum and +25°C maximum. Do not expose to direct light.
<b>Density</b>	1.7g/cm <sup>3</sup> when mixed

### TECHNICAL INFORMATION

<b>Compressive Strength</b>	60 N/mm <sup>2</sup> @ 24 hours at 20°C 74 N/mm <sup>2</sup> @ 7 days (ASTM D695 20°C)
<b>Modulus of Elasticity in Compression</b>	3.1 GN/mm <sup>2</sup> @ 24 hours at 20°C (ASTM D695 20°C)
<b>Tensile Strength</b>	11 N/mm <sup>2</sup> @ 24 hours 13 N/mm <sup>2</sup> @ 7 days (ASTM D638 20°C)

## APPLICATION INFORMATION

<b>Mixing Ratio</b>	10:1 by volume as supplied in cartridge				
<b>Consumption</b>	<b>Anchorset (mm)</b>	<b>Hole Diameter/Depth (mm)</b>	<b>Tensile Load (kN)</b>	<b>Shear Load (kN)</b>	<b>Fixings Per Unit 300ml</b>
	8	10 / 64	16	1.4	85
	10	12 / 80	22.6	2.9	58
	12	14 / 96	29	4.0	38
	16	18 / 128	45	-	23
	20	22 / 160	69.4	-	12
	24	26 / 192	102.9	-	8
Tension Figures quoted are tested in approximately 20/25 N/mm <sup>2</sup> concrete.					
<b>Curing Time</b>	<b>Base Material Temperature (°C)</b>	<b>Gel Time (min)</b>	<b>Min Loading Time (min)</b>		
	5-10	12	120		
	10-20	6	80		
	20-25	4	40		
	25-30	3	30		
	30-35	2	20		
	35-40	1.5	15		

## APPLICATION INSTRUCTIONS

### SUBSTRATE QUALITY

Drill hole to the correct diameter and depth (see chart for guide), ideally using a rotary percussion machine. For optimum results the hole must be coarse sided. If the holes are produced by diamond drilling the surfaces should be thoroughly roughened. Remove all dust and debris from the hole using a hand air pump or a stiff rotary brush. All bars should be clean and free from oil or grease and all flaking rust should be removed. Threaded rod or studs should be chisel-ended to prevent them being unscrewed from the cured resin.

### APPLICATION METHOD / TOOLS

Unscrew the lid and cut off the top of the bag under the metal clamp. Attach the mixing nozzle to the cartridge (screw down hand tight). Place cartridge into the dispensing gun. Gradually pressurise the Cartridge by activating the hand trigger a few times until material passes through the mixing nozzle and an even colour is obtained (approximately 5-6 inches of extruded material should be adequate). Once the desired fill is achieved release the pressure by pressing the slide release arm and pulling back the slide rail, wipe off excess material and insert the fixing slowly, with a rotating action, to the desired depth.

### LIMITATIONS

Do not use in non porous substrates i.e. metal, PVC. Do not use on wet surfaces. As the manufacturer cannot know all the uses its products may be put to, it is the users responsibility to determine suitability for use. If in doubt, contact technical services department for advice.

technical services department for advice.

### VALUE BASE

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

### LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

### ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

### LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recom-

mendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

**EVERBUILD BUILDING PRODUCTS LTD**

Site 41, Knowsthorpe Way  
Cross Green Industrial Estate  
Leeds, LS9 0SW  
Tel: 0113 240 3456  
Web: [www.everbuild.co.uk](http://www.everbuild.co.uk)  
Twitter: @everbuild

**SIKA LIMITED**

Watchmead  
Welwyn Garden City  
Hertfordshire, AL7 1BQ  
Tel: 01707 394444  
Web: [www.sika.co.uk](http://www.sika.co.uk)  
Twitter: @SikaLimited

**SIKA IRELAND LIMITED**

Ballymun Industrial Estate  
Ballymun  
Dublin 11, Ireland  
Tel: +353 1 862 0709  
Web: [www.sika.ie](http://www.sika.ie)  
Twitter: @SikaIreland

