

908 DPM



Colour	Product Code	Pack Size	Box Qty
Dries Black	90805	5Ltr	4
	90825	25Ltr	1

Product Description

BLACK JACK DPM is a ready to use, odourless, rubber enriched bitumen emulsion which provides a highly effective sandwich damp-proof membrane for floors. Also acts as a waterproofer for walls, above ground structures and foundations. May be used internally or externally. BLACK JACK DPM is also suitable for use as an adhesive for wood block, mosaic panels, insulation boards, expanded polystyrene, cork and as a plaster bonding agent, even on difficult surfaces.

Benefits

- Forms an impervious water and water vapour barrier on most surfaces.
- Internal or external use.
- May also be used as an adhesive or bonding aid
- Low hazard - Water clean up.

Areas For Use

BLACK JACK DPM is commonly used in the following areas:

- Providing sandwich damp-proof membranes for floors.
- General Waterproofing: - for use on concrete, fibre/cement, render, plaster etc.
- For waterproofing structures such as bridge abutments, retaining walls and culverts.
- For fixing wood blocks and wooden mosaic flooring
- As a bonding agent for plastering difficult substrates such as glazed tiles
- For fixing insulation boards, expanded polystyrene and cork slabs.
- As a curing agent for concrete.

Limitations

- Do not apply when rain is imminent
- Protect from rain and frost until cured (The coating may be assumed to be dry when rubbing with a wet finger does not produce a brown stain).
- Do not use in areas where subsequent solvent contact is likely.
- Allow sufficient drying time between coats.
- Stir well before use.
- The product may bleed through any paints subsequently applied over it. Apply a primer recommended by the paint manufacturer before overpainting.
- This product will not provide a replacement for a DPC. Ideally, it should be used in conjunction.

- Gloss paints and other oil or alkyd based paints must not be used directly over a surface treated with BLACK JACK DPM

Surface Preparation

STIR WELL BEFORE USE. The product is brown in colour but dries black. Before applying, ensure all surfaces are clean, touch dry (free from excess water), sound and free from any contaminants, which may affect adhesion. Base concrete must be finished off with a wooden float to give a smooth surface. Tamped surfaces are not suitable owing to the difficulty of ensuring adequate coating over the high spots. Prime porous surfaces with BLACK JACK DPM diluted 1:6 with water and allow to dry. All phases of the installation should comply with BS Code of Practice 102: 1973 - protection of Buildings from the Ground/Section 3.

Application

Stir well before use.

DAMP-PROOFING FLOORS

Apply by brush, a minimum of 2 coats, each at 0.8litre per m², carrying the treatment up the walls to join the existing wall DPC. Allow the first coat to dry before applying the second coat at right angles to the first. When dry, a sand/cement or concrete screed of approximately 50mm thick is then laid over the BLACK JACK DPM membrane.

WATERPROOFING WALLS

If a condition of rising damp exists, the best form of treatment is the insertion of a damp proof course. Where dampness is due to penetration of the wall, proceed as follows:

a/ Exterior walls:

Level uneven surfaces with cement mortar. Apply three coats of BLACK JACK DPM with a soft bristled brush, each at a rate of 0.5ltr/m²., allowing each coat to dry before applying the next. Allow the final coat to become tacky, then blind with clean, sharp sand.

b/ Interior walls. (moderately damp)

Remove wallpaper, loose emulsion/gloss paint and any dust or grease. Make good any damaged or perished plaster. Lightly dampen the prepared surface and apply 3 coats of BLACK JACK DPM with a soft bristled brush, each at a rate of 0.5ltr/m²., allowing each coat to dry before applying the next. A horizontal strip running 300mm deep should be left uncoated at the top running the whole length of the wall. This permits trapped moisture to escape by evaporation.

c/ Interior walls (very damp)

Wherever possible, very damp walls should receive an external treatment such as waterproof render/masonry paint etc. If it is not possible, the following procedure may benefit although it must be emphasised that only adequate external treatment will cure the most severe conditions. Hack away old plaster from the entire area and damage to joints or brickwork must be made good with cement mortar. When the mortar has dried, apply 3 coats of BLACK JACK DPM with a soft bristled brush, each at a rate of 0.5ltr/m²., allowing each coat to dry before applying the next. When the final coat has thoroughly dried, the wall should be re-plastered.

DECORATING

Gloss paints and other oil or alkyd based paints must not be used over a surface treated with BLACK JACK DPM.

Where BLACK JACK DPM has been used over plaster, it is recommended that a lining paper, fixed with cellulose paste should be hung. This will provide a suitable surface for emulsion paints and for wallpapering. NOTE: Vinyl coated papers or paper backed vinyls should NOT be hung over BLACK JACK DPM.

WATERPROOFING STRUCTURES

BLACK JACK DPM will provide a waterproof membrane on bridge abutments, retaining walls, culverts, concrete or brick foundations. It also acts as a curing membrane when applied to green concrete.

The surface should be sound and free from dust, dirt and grease. Hot, very dry or absorbent surfaces should be dampened with water. Apply two coats of BLACK JACK DPM each at a rate of 0.5litre/m².

FIXING WOOD BLOCKS AND MOSAICS

For fixing wood blocks of 12mm thickness and above, dip the bottom face of each block into the material and place into position immediately. Coverage is approximately 1.1litres/m².

For fixing wood mosaic panels, spread BLACK JACK DPM onto the surface at 0.8litres/m². and place the panels into position immediately. A minimum of 24 hours should be allowed before sanding/trafficking.

Where under floor heating is incorporated into the sub floor, the heating must be turned off for at least 48 hours before and after tiling.

NOTE: On low porosity or non-porous surfaces, allow the BLACK JACK DPM film to partially dry before placing the wood mosaics/blocks into position. In most circumstances, a period of 30-40mins will suffice, but do not allow to dry off completely.

Under no circumstances, should such floorings be laid on existing floor coverings.

PLASTER/RENDER BONDING/KEYING

When a "keyed" surface is required (plastering onto glazed tiles, gloss painted walls and bricks, or to bond sand/cement renders) apply two coats of BLACK JACK DPM each at a minimum rate of 0.25litres/m². Allow the first coat to dry before applying the second and blind the second coat with clean sharp, dry, sand. Allow at least 48 hours before plastering or rendering (at least 6mm thickness) NOTE if gloss or alkyd paints are to be used as a decorative finish, the plaster over the BLACK JACK DPM must be applied in two coats to give a minimum total thickness of 15mm.

FIXING INSULATION BOARD, EXPANDED POLYSTYRENE AND CORK SLABS.

Surfaces should be clean, level and free from dust or loose matter. A coat of BLACK JACK DPM should be applied to the porous base and the insulation material placed whilst the BLACK JACK DPM is still wet. If necessary, the boards should be supported until the BLACK JACK DPM has set Coverage approx. 0.4-0.6litres/m².

CLEANING TOOLS

Clean tools immediately after use with water. Once cured, dried product can be removed with Kerosene (paraffin) or white spirit.

Specific Data

Type Of Solvent	Water based emulsion (non flammable)
Flashpoint	Non flammable
Specific Gravity @ 20°C	1.0
Coverage	See specific sections: 6 – 10m ² / 5ltr tin as approximation
Drying Time	4 -6 hours depending on drying conditions
Service Temps	-10 to +85c.
Application Temps	+5 to +50°C. DO NOT APPLY BELOW 5°C
Fire Resistance	Wet product: Non flammable Dry product: Will support combustion

SBS Content	14% w/w minimum
Chemical And Water Resistance	Resistant to: most salt solutions, dilute acids and alkalis, water. Not resistant to: Oils, solvents and some detergent solutions.

Health & Safety

Consult MSDS for full list of hazards.

Storage

Store in original container in cool, dry conditions. PROTECT FROM FROST.

Shelf Life

24 months from date of manufacture when stored according to manufacturers instructions.

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.