



Specialist Construction Supplies for Repair, Maintenance, Building & Infrastructure

## Cebex 100 Data Sheet

### Specification notes

Product: **Cebex 100**

Supplier:

**Arcon Construction Supplies**  
**19-20 Prestwood Court**  
**Leacroft Road**  
**Warrington**  
**WA3 6SB**

Tel: **01925 852225**

Email: [mail@arconsupplies.co.uk](mailto:mail@arconsupplies.co.uk)

Web: [www.arconsupplies.co.uk](http://www.arconsupplies.co.uk)

Call **01925 852225** or visit [Arcon Construction Supplies](http://www.arconconstruction.com)  
... for more information on our flooring and construction products

[Industrial Flooring](#) | [Concrete Repairs](#) | [Protective and Waterproof Coatings](#)  
[Jointing and Paving Mortars](#) | [Anti-slip Floor Paints](#) | [Concrete Repair Mortars](#)

## Expanding and plasticising grout admixture

### Uses

Cebex 100 is an admixture for site batched cementitious grouts where a reduced water/cement ratio and positive expansion is required. Applications include bed grouting, duct grouting, non-shrink infilling and jointing.

### Advantages

- Gaseous expansion system compensates for plastic shrinkage and settlement in properly designed cementitious grout.
- Reduced water/cement ratio in the grout mix ensures low permeability and long term durability in service.
- Gives high grout fluidity with low water/cement ratio, thus making placement or injection of the grout easy.
- No metallic iron content to corrode and cause staining or deterioration due to rust expansion in the grout.
- Composition allows high early strength development in grouts, without the use of chlorides.

### Standard compliance

Cebex 100 is a suitable pre-stressing grout admixture when complying with BS 8110 Part 1, 1997, Annex A.

### Description

Cebex 100 is supplied as a powder admixture. The material is a combination of a plasticising agent and a gas producing expansion medium. The plasticising agent allows the use of a reduced water/cement ratio with consequent increased strengths and durability. The expansive medium counteracts the natural settlement and plastic shrinkage of the grout and aids stability and cohesion.

Sufficient restrained expansion is developed to ensure a high degree of interfacial contact.

### Specification clauses

#### Supplier specification

All grouting (specify details and areas of application) must be carried out using a cement based grout, incorporating Cebex 100 manufactured by Fosroc and applied strictly in accordance with the manufacturer's technical data sheet.

## Properties

Chloride content:	Nil to BS 5075
Compressive Strength:	The plasticising action of Cebex 100 allows reduction of the water/cement ratio of cementitious grouts whilst maintaining flow properties. This gives improvement in strength and long term durability when cured under restraint.
Setting times:	Cebex 100 does not significantly affect the setting times of cement based grouts.
Expansion Character:	The controlled positive expansion in unset grouts incorporating Cebex 100 overcomes plastic settlement when measured in accordance with ASTM C827. An unrestrained expansion of up to 4% is typical.
Time for: expansion:	15 minutes to 2 hours. Temperatures over 20°C may slightly reduce these times.
Compatibility:	Cebex 100 is compatible with all types of Portland cement.  Cebex 100 may be used in mixes containing certain other Fosroc admixtures. Consult Fosroc for further information.

## Instructions for use

### Mixing

For best results a mechanically powered grout mixer must be used. For quantities up to 50 kg a slow speed drill fitted with a Conbextra mixing paddle is suitable. Larger quantities will require a high shear vane mixer. It is essential that machine mixing capacity and labour availability is adequate to enable the grouting operation to be carried out continuously. This may require the use of a holding tank with provision for gentle agitation to maintain fluidity. The selected water content should be accurately measured into the mixer. Slowly add the cement (and sand if required) and Cebex 100. Mix continuously for 5 minutes, making sure that a smooth even consistency is obtained.

# Fosroc® Cebex 100

## Application

Areas to be grouted should be prepared to ensure substrates are clean, sound, and then pre-wetted. The unrestrained surface area of the grout must be kept to a minimum. Place the grout within 20 minutes of mixing to gain the full benefit of the expansion process. Adopt usual placing or pumping procedures ensuring a continuous operation.

## Curing

On completion of the grouting operation, any exposed areas which are not to be cut back should be thoroughly cured by means of water application, Concre curing membrane or wet hessian.

## Cleaning

Grouts mixed with Cebex 100 should be removed from tools and equipment with clean water immediately after use. Remove cured material mechanically or with Fosroc Acid Etch.

## Estimating

### Packaging

Cebex 100 is supplied in packs containing 24 x 227g units.

### Dosage

OPC	Concreting sand	Water	Cebex 100	Approx yield
50 kg	--	20 to 22 litres	227 g	36 litres
50 kg	50 kg	22 to 24 litres	227 g	57 litres

Note: For grout, mortar or concrete mixes with an aggregate/cement ratio more than 1, use 4 x 227 g units of Cebex 100 per 100 kg of cement.

## Effects of overdosing

Drastic overdosing of Cebex 100 increases expansion and may cause frothing.

## Storage

Cebex 100 has a shelf life of 18 months if kept in a dry store in its original packaging. High temperature and humidity storage may reduce this period.

## Precautions

### Health and safety

For further information refer to appropriate Product Safety Data Sheet.

Fosroc and Cebex are trademarks of  
Fosroc International Limited



### Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification of information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it.

## Fosroc Limited

Drayton Manor Business Park,  
Coleshill Road, Tamworth,  
Staffordshire B78 3XN. UK

[www.fosroc.com](http://www.fosroc.com)

telephone:  
+44 0 (1827) 262222

fax:  
+44 0 (1827) 262444

email:  
enquiryuk@fosroc.com



Certificate number FM 610