



Specialist Construction Supplies for Repair, Maintenance, Building & Infrastructure

## E70 Data Sheet

### Specification notes

Product: E70

Supplier:

**Arcon Construction Supplies**  
19-20 Prestwood Court  
Leacroft Road  
Warrington  
WA3 6SB

Tel: 01925 852225

Email: [mail@arconsupplies.co.uk](mailto:mail@arconsupplies.co.uk)

Web: [www.arconsupplies.co.uk](http://www.arconsupplies.co.uk)

Call 01925 852225 or visit [Arcon Construction Supplies](http://www.arconconstruction.com)  
... for more information on our flooring and construction products

[Industrial Flooring](#) | [Concrete Repairs](#) | [Protective and Waterproof Coatings](#)  
[Jointing and Paving Mortars](#) | [Anti-slip Floor Paints](#) | [Concrete Repair Mortars](#)

## E70 EPOXY GROUT

### Product codes

TG 70, TG31 Packaging listed overleaf.

### Description

E70 Epoxy Grout is an epoxy resin based grout with high flow properties capable of placing in gaps between 35mm to 75mm. The epoxy resin formulation enables E70 Epoxy Grout to be used in the most demanding situations giving exceptional mechanical strength. The volume stable mix design ensures complete fill of the grouted area and contact with the work piece.

The formulation gives good chemical resistance to most chemicals. Stable to sea water, petroleum products, resists freeze thaw cycles. For cold weather working E33 Winter Additive will improve low temperature strength development.

**Uses include:** Machinery base plates  
Crane rail tracks  
Bridge Bearings  
Compressors, pumps and turbines  
Reciprocating machinery  
High impact loads

### Typical Grout Properties @ 20°C

#### Compressive Strengths

1 Day	3 Days	7 Days
63N/mm <sup>2</sup>	74N/mm <sup>2</sup>	79N/mm <sup>2</sup>

Tensile Strength 10N/mm<sup>2</sup> @ 7 Days  
Flexural Strength 22N/mm<sup>2</sup> @ 7 Days  
Youngs Modulus 11.9kN/mm<sup>2</sup> @ 7 days  
Density: 2000kg/m<sup>3</sup>  
Usable Life: 30 minutes after mixing  
Flow Properties Result from 50mm concentric Ring test = 200mm.  
Flow result of 50mm represents nil flow.

### Standards:

E70 Epoxy Grout has been tested in accordance with the appropriate parts of BS 6319

### Specification Outline

Grouting shall be carried out using E70 Epoxy Grout as manufactured by Parex Ltd. The product must be stored, handled and used strictly in accordance with the manufacturer's instructions.

### Quality Assurance

Parex Ltd is a firm of Assessed Capability. The Company's quality system conforms to BS EN ISO 9001:2008 and is assessed by UK CARES LTD.

### Instructions For Use

#### Preparation

Remove laitance and all loose material including dust, oil and grease to achieve a sound substrate. Steel surfaces should be free of mill scale and rust. Surfaces to be grouted should be free of standing water and in a surface dry condition. Formwork must be designed with sufficient hydrostatic head to ensure grout flow into and across the grouting area and should be made grout tight. Apply a silicone based release agent to the formwork surfaces which will effect release after grout has hardened. Alternatively use thick polythene sheet firmly fixed to the formwork

#### Mixing

E70 Epoxy Grout has 4 containers per pack. **All containers must be used to complete the mix.** Pour all of the resin and hardener into a clean mixing vessel. Mix with a slow speed drill (200-300rpm) and Mortar Stirrer (MR4) until homogeneous. Slowly add the filler to the mixed resin and hardener. When all the filler has been added, mix for a further two minutes until an even colour is achieved. Add the aggregate and mix for further minute until the aggregate is well dispersed throughout the mix. Try and ensure that air entrainment is kept to a minimum by keeping the mixing head below the surface level of the grout at all times. Larger volume may be mixed using a forced action mixer such as the Creteangle.

## E70 EPOXY GROUT

### Instructions For Use

#### Placing

Allow mixed grout to stand for 5 minutes prior to placing to allow entrained air from mixing to be released. Place grout continuously into the work area from one side only. Where further mixes are required to fill the void, these should be prepared in sequence such that pouring is continuous. Place mixed grout within 30 minutes after start of mixing. Place in gap widths between 35mm and 75mm. For thicker sections use E140 variant. Do not disturb the grouted section until the grout has hardened. Tools and mixing equipment should be cleaned with Solvent before grout has hardened. Set grout can only be removed mechanically.

E70 Epoxy Grout may be placed at temperatures between 5°C and 45°C. For placing outside this range contact the Technical Service Department.

#### Curing

No special curing is required.

#### Precautions

#### Health and Safety

E70 Epoxy Grout is a resin based product. Resins and solvents may cause allergic reactions in some people. Wear gloves, use barrier cream on unprotected skin areas and wear eye protection when mixing, using and cleaning. Ensure adequate ventilation to prevent inhalation of vapours. If skin contact occurs remove resin immediately with cleansing cream and wash with soap and water. Do not use Solvent. Should eye contact occur rinse immediately with plenty of clean water and seek medical advice. If swallowed do not induce vomiting. Seek medical advice immediately.

Full health and safety data are given in Product Safety Data Sheet.

#### Fire

E70 Epoxy Grout is classified as non-flammable. Solvent is flammable. Should fire occur extinguish with CO<sub>2</sub> or foam.

#### Storage And Shelf Life

E70 Epoxy Grout will have a storage life of 12 months in unopened containers when kept in dry conditions at a temperature between 5°C and 45°C. Storage at higher temperatures and high humidity may reduce shelf life.

#### Yield

Each 33.8kg pack will yield approximately 16.75 litres of mixed material.

#### Packaging And Ordering

E70 Epoxy Grout is supplied in:  
33.8kg pack      Product Code: TG70.

Solvent is supplied in:

5 litre tin      Product Code: TM 02  
1 litre tin      Product Code: TM 08

E33 Winter Additive is supplied in 100 gram units  
100g units      Product Code: TG 31

For further information and sales please contact your local Parex Office as listed below.

Parex Ltd products are guaranteed against defective materials and manufacture. Products are sold subject to the Parex Ltd Terms and Conditions of Sale, copies of which are forwarded on invoice and are available on request. Parex Ltd endeavours to ensure that the above data and any further advice is correct, however, it cannot accept any direct or indirect liability for the use of its products as such usage is beyond its control.