



New Guard Coatings Group

A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

www.newguardcoatings.com

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND

Two-part epoxy resin mortars

Uses

For use in exceptionally wet conditions and for underwater applications.

Advantages

- Possesses outstanding strength and adhesive powers
- Resistant to physical damage
- Excellent chemical resistance
- Can be used underwater

Description

Nitomortar UA is recommended for fixing slip bricks and for reinstating structures exposed to heavy battering from the sea, such as sea walls and concrete jetties and for repairing submerged steelwork and concrete. Mixed mortar may be transported underwater in polythene bags.

Properties

Form:	Two-part compounds — Base: firm putty Hardener: soft putty
Solids content:	100%
Fresh wet density:	2000 kg/m ³
Colour:	Base: off-white Hardener: black Mixed colour: dark grey
Pot life:	30 to 45 minutes at 20°C
Water immersion:	Nitomortar UA may be applied and cured underwater.
Cure time:	Initial cure: 24 hours at 20°C Final cure: 7 days at 20°C After 48 hours at 20°C Nitomortar UA will have achieved between 60% to 70% of its final compressive strength
Compressive strength (BS 6319, Pt 2):	After 1 week at 20°C — 65 N/mm ²
Flexural strength (BS 6319, Pt 3):	After 1 week at 20°C — 35 N/mm ²
Tensile strength (BS 6319, Pt 7):	After 1 week at 20°C — 12 N/mm ²
Thermal expansion:	Coefficient of linear expansion: –25°C to +25°C — 3.0 x 10 ⁻⁵ per°C

Application instructions

Mixing Nitomortar UA

The 1.5 litre pack of Nitomortar UA is suitable for hand mixing (wearing protective gloves) on a flat, clean surface. The mixing surface should be wetted and the whole of the base material spread out approximately 10 to 20 mm thick. All of the hardener should be emptied out onto the middle of the base and the base folded over the hardener and kneaded until the resultant mortar is of an even consistency and uniform colour.

Underwater application

Surfaces must be mechanically cleaned, free of weak or loose material, marine growth, rust, scale, etc. Mixed Nitomortar UA should be carried in plastic bags to work area and small quantities, approximately 5 mm thick, pressed into position ensuring that all water is expelled from between the repair surface and the Nitomortar UA. Mixed mortar should be applied within 30 minutes of mixing. Contact between the mixed mortar and water should be avoided until the point of application. Uncured material should be protected from scouring and displacement by moving water until cured.

Fixing of slip bricks, tiles, etc

The concrete surface should be scabbled, wire brushed and washed with clean water. Scrub bond face of brick or tile with clean water and shake to remove excess water. Rub Nitomortar UA into the wetted bond surfaces. Apply 25 mm thick sausage of Nitomortar UA to the tile. Firmly press tiles onto concrete with twisting action to ensure complete material bed of required thickness (usually 6 to 12 mm). Very thick beds should be made up by previous application of Nitomortar UA to the prepared concrete surface. The tiles should be supported for 12 to 48 hours until the Nitomortar UA has cured sufficiently to prevent slipping. The use of Nitomortar UA is recommended as it allows the surfaces of the bricks and concrete to be thoroughly washed down immediately prior to fixing.

Cleaning

Nitomortar UA should be removed whilst uncured using water or detergent solution. Cured mortar can only be removed by mechanical means.

Estimating

Nitomortar UA is supplied in 6 x 1.5 litre packs containing base and hardener in separate plastic buckets. Coverage rate is 1 litre/m² per mm thickness.

Fosroc® Nitomortar UA

Limitations

Nitomortar UA should not be used when the temperature is below 5°C and falling. Never mix part packs.

Storage

All products have a shelf life of 18 months at between 5°C and 20°C and kept in a dry store in the original, unopened packs. Storage at higher temperature may reduce shelf life.

Precautions

Health and safety

For further information refer to appropriate Product Safety Data Sheet.

Fosroc and Nitomortar are trademarks of
Fosroc International Limited



Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification of information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it.

Fosroc Limited

Drayton Manor Business Park,
Coleshill Road, Tamworth,
Staffordshire B78 3XN. UK

www.fosroc.com

telephone:
+44 0 (1827) 262222

fax:
+44 0 (1827) 262444

email:
enquiryuk@fosroc.com



Certificate number FM 610