



New Guard Coatings Group

A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

www.newguardcoatings.com

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND

Fosroc® Nitoprime Zincrich Plus



constructive solutions

Single component zinc primer for use with Renderoc repair system

Uses

Nitoprime Zincrich Plus is the recommended anti-corrosion primer for exposed steel reinforcement for use with Fosroc concrete repair mortars.

It is fully compatible with all Renderoc mortars and fluid micro-concretes.

Advantages

- 'Active' zinc-rich system combats corrosion by electro-chemical means
- Formulated for use with Renderoc repair products
- Single component product — easy to use with no restrictive pot-life
- Economical - single component ensures almost no waste

Description

Nitoprime Zincrich Plus is supplied as a single component grey-coloured liquid based on metallic zinc.

Specification clause

The exposed steel surfaces shall be prepared to a minimum of ST3 standard prior to application of Nitoprime Zincrich Plus, a single-component zinc-rich coating compliant with BS EN 1504-7. An unbroken 40 microns thick coating shall be applied in one or two applications as required to provide 'active' galvanic protection in accordance with the manufacturer's written instructions. It shall have a suitable viscosity to enable the coating to penetrate imperfections and pits within the surface of corrosion-damaged steel bars. The formulation shall be such that it allows the application of the repair mortar to proceed as soon as the coating is touch dry (generally after 1 hour at 20°C.) It shall be fully compatible with the Fosroc system of concrete repair products.

Standards compliance

Nitoprime Zincrich Plus complies with LU Standard 1-085 'Fire Safety Performance of Materials'.


BS EN 1504-7: Reinforcement corrosion protection method 11.1

Properties

Test method	Typical result
Specific gravity:	2.5
Recommended thickness per coat:	40 microns (dry)
Application thickness per coat:	100 microns (wet)
Drying times —	@ 20°C
Touch dry:	1 hours
Fully dry/recoatable:	2 hours

Note: at temperatures below 20°C, the drying times will be slower.



 0370	
Fosroc International Limited Drayton Manor Business Park, Coleshill Road, Tamworth, B78 3XN, UK 09 DOP: UK9-48 0370-CPR-0845	
Nitoprime Zincrich Plus	
BS EN 1504-7: Reinforcement corrosion protection method 11.1	
Corrosion protection	Pass
Dangerous substances	Conforms to 5.3

Application instructions

Preparation

Expose fully any corroded steel in the repair area and remove all loose scale and corrosion deposits. Steel should be cleaned to a minimum of ST3 standard, paying particular attention to the back of exposed steel bars. This should be achieved by suitable mechanical means, e.g. powered wire-brushing, high pressure jetting or alternative equivalent.

Where corrosion has occurred due to the presence of chlorides, the steel should be high-pressure washed with clean water immediately after preparation to remove corrosion products from pits and imperfections within its surface.

Application

The application of Nitoprime Zincrich Plus must take place as soon as possible to a dry steel surface after completion of the preparation work but always within 3 hours. The material should be stirred thoroughly before use in order to redisperse any settlement.

Apply one full and unbroken coat of Nitoprime Zincrich Plus by suitable brush, making sure that the back of exposed

Fosroc® Nitoprime Zincrich Plus

steel reinforcing bars are properly coated. A small brush is generally more suitable for this purpose. Allow to dry fully before continuing. If any doubt exists about having achieved an unbroken coating, a second application should be made as soon as the first coat is fully dry (generally after 2 hours).

The application of concrete repair materials may proceed as soon as the Nitoprime Zincrich Plus is touch dry (generally 1 hour — see Properties).

The primed surfaces should not be left exposed to the elements for longer than necessary before overcoating or application of the repair material. Nitoprime Zincrich Plus will, however, protect steel under clean interior exposure conditions for a period of several months. In non-aggressive exterior environments, a maximum interval of 14 days will be tolerated but in industrial and/or marine environments this interval should be reduced to the practical minimum. If the 14 days in an external environment has been exceeded, inspect the coating for signs of damage, remove any dust by vacuuming or utilising oil free compressed air. If damage is detected, remove the affected areas and re-apply Nitoprime Zincrich Plus, lapping onto adjacent areas by a minimum of 20mm.

Low temperature working

The minimum application temperature is 5°C. The material should not be applied when the substrate and/or air temperature is 5°C and falling, or is less than 3°C above the dew point. At 5°C static temperature or at 5°C and rising, the application may proceed.

Cleaning

Nitoprime Zincrich Plus should be removed from tools, equipment and mixers with Fosroc Solvent 102 immediately after use.

Estimating

Supply

Nitoprime Zincrich Plus:	1.9 litre and 800ml cans
Fosroc Solvent 102 :	5 and 25 litre tins

Coverage

Nitoprime Zincrich Plus:	8 m ² / litre
--------------------------	--------------------------

Note: this coverage figure is theoretical — due to wastage factors and the variety and nature of possible steel substrates, practical coverage figures will be reduced.



Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification of information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation or information given by it. All Fosroc datasheets are updated on a regular basis. It is the user's responsibility to obtain the latest version.

Fosroc International Limited

Drayton Manor Business Park
Colleshill Road, Tamworth,
Staffordshire B78 3XN. UK

www.fosroc.com

telephone:
+44 0 (1827) 262222

fax:
+44 0 (1827) 262444

email:
enquiryuk@fosroc.com



Limitations

Nitoprime Zincrich Plus should not be applied when the temperature is below 5°C or is 5°C and falling. If any doubts arise concerning temperature or application conditions, consult the local Fosroc office.

Storage

Store in dry conditions in the original containers. Nitoprime Zincrich Plus and Fosroc Solvent 102 have a shelf life of 12 months if kept in a dry store in the original, unopened containers.

If stored at high temperatures and/or high humidity conditions the shelf life may be reduced.

Precautions

Health and safety

For further information refer to the appropriate Product Safety Data Sheet

Fire

Nitoprime Zincrich Plus and Fosroc Solvent 102 are flammable. Keep away from sources of ignition. No smoking. In the event of fire, extinguish with CO₂ or foam. Do not use a water jet.

Flash points

Nitoprime Zincrich Plus:	41°C
Fosroc Solvent 102:	33°C

For further information, refer to the Product Material Safety Data Sheet.

Additional information

Nitoprime Zincrich Plus is the approved reinforcing steel primer for use with the Renderoc, Patchroc, Paveroc and Nitomortar systems of concrete repair.