



# New Guard Coatings Group

A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

[www.newguardcoatings.com](http://www.newguardcoatings.com)

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND

# Fosroc® Nitoseal MS300

## One part, floor and pavement joint sealant

### Uses

Nitoseal MS300 is suitable for sealing saw-cut and movement joints in internal floors, and external joints where abrasion resistance is required. It can also be used for external facade joints where a tougher seal is required.

- Factory floors
- Sports stadia terracing
- Shopping centres
- Warehouse and distribution depots
- Concrete hardstanding areas
- Prisons

### Advantages

- Suitable for forklift truck traffic
- Suitable for saw cut and perimeter joints
- Abrasion resistant
- Withstands vehicular traffic
- Single component
- Fast rate of cure
- Easy to apply at low temperature
- Can be applied to damp substrates
- Primer-less for most applications (see "Priming" section)
- Hard, but flexible sealant; resists picking and vandalism

### Description

Nitoseal MS300 is a one part, high modulus sealant based on hybrid silyl modified polyether technology. It has a rapid rate of cure and forms a tough elastomer capable of supporting heavy wheel loads.

Nitoseal MS300 may be applied between 6mm and 20mm wide, for internal trafficked flush joints and up to 40mm wide, for non-trafficked / recessed trafficked joints. In most cases it is recommended to form a sealing slot with a square cross-section, subject to a minimum 10mm depth. To ensure the sealant operates within its stated movement accommodation capacity the sealing slot widths should be designed in accordance with the recommendations of BS6093.

### Standard compliance


ISO11600 Type F 25HM: Classification of sealants for building construction

ASTM C920 Type S, Grade NS, Class 25

ASTM D2203-93: Standard test method for staining

BSEN 140-3:1995: Acoustics measurement of sound insulation in buildings



 2538	
Fosroc Ltd, Drayton Manor Business Park, Coleshill Road, Tamworth, Staffs, B78 3XN 14 DoP UK 9-82	
Fosroc® Nitoseal MS300 EN 14188:2:2004 Sealants for concrete pavements	
Extrudability @ 23°C and 5°C	> 70ml/min.
Full immersion cure	14 days
Tack free time	2-3 hours
Resistance to flow at 50°C & 5°C	≤ 2mm
Change in volume	≤ 5%
Resistance to hydrolysis	Shore A ≤ ± 50%
Resistance to flame	No flow, cracking, flaking, hardening, ignition
Adhesion/Cohesion properties at variable temperatures	No failure
Tensile properties at maintained extension	No failure at 23°C and -20°C
Elastic recovery	≥ 70 %
Artificial weathering by UV irradiation	≤ ± 20%

# Fosroc® Nitoseal MS300

## Properties

### Nitoseal MS300

Form	Paste
Flash point	>65°C
Colour	Grey (special colours available on request)
Movement accommodation factor	Butt joints 25% Lap joints 50%
Skinning time	up to 2 hours depending on ambient conditions
E-Modulus (ISO 8339)	>0.8N/mm <sup>2</sup>
Cure rate at 20°C, 50% RH	
24 hours	3 mm
48 hours	6 mm
72 hours	8 mm
Application temperature	5°C to 50°C
Typical hardness	
Shore "A" at 20°C	45
Trafficking time at 20°C	
Light traffic	24 hours
Heavy traffic	4 days
Modulus	High
UV resistance	Excellent
Service temperature range	-20°C to 70°C
LEED EQc4.1	Passes
SCAQMD Rule 1168	
BAAQMD Reg 8 Rule 51	

## Application instructions

### Preparation

Joints in concrete should preferably be sawn. After sawing all saw slurry must be flushed away and the joint allowed to dry.

When resealing the existing sealant should be removed from the joint and the arris cleaned back to sound clean concrete. Remove all debris. The joint surfaces must be dry, clean and frost free. Remove all contaminants by rigorous wire brushing, grinding or grit blasting.

Any expansion joint filler must be checked to ensure it is tightly packed and no gaps or voids exist at the base of the sealing slot before positioning a bond breaker.

Note: The use of a bond breaker is not required in expansion joints containing Hydrocell XL cellular polyethylene expansion joint filler. For construction or contraction joints a bond breaker tape or back-up strip should be used.

Where a particularly neat finish is required, mask the face edges of the joint before priming/sealing and remove immediately after tooling is completed.

## Priming

Fosroc Primer MS2 is required for joints that are to be intermittently or permanently immersed, or where the substrate is likely to be saturated (for example, externally).

When using a primer, empty the entire contents of the hardener tin into the base tin and replace the base tin lid. Mix thoroughly by shaking for at least 2 minutes. Prime the joint face using a clean, dry brush. Avoid over application of primer causing puddles in the bottom of the joint.

Nitoseal MS300 should be applied between 30 minutes and 4 hours after priming.

If a joint is left unsealed for more than 4 hours, the primer should be removed by grit blasting or grinding and the joint re-primed.

Do not split packs of Fosroc Primer MS2.

## Application and finishing

Cut end off sachet and place in Fosroc GX Gun. Fit nozzle and cut at 45° to a suitable size. Extrude the sealant firmly into the joint. Tool to the required finish (flush or recessed) within 5 minutes of application to ensure good contact between the sealant and the substrate.

## Cleaning

Clean tools immediately after use with Fosroc Equipment Cleaner.

## Estimating

### Guide to sealant and primer quantities

Joint size in mm	Litre per metre run	Metre per 600ml sachet
6 x 10	0.06	10.00
12 x 12	0.144	4.17
20 x 20	0.40	1.50
25 x 20	0.50	1.20
30 x 20	0.60	1.00
40 x 25	1.00	0.60

### Guide to Nitoseal MS2 Primer coverage

Linear metres per pack of primer	
Joint depth mm	Nitoseal MS2 Primer 0.75 litre pack
10	500 - 600
15	333 - 400
20	250 - 300
25	200 - 240
30	166 - 200
40	125 - 150
50	100 - 120

# Fosroc® Nitoseal MS300

## Packaging

Nitoseal MS300 - 600 ml sachets. 10 no. sachets per box.  
Fosroc Primer MS2 – 0.75 litre packs

## Limitations

- Do not apply at temperatures below 5°C.
- Not suitable for contact with bituminous materials.
- Whilst Nitoseal MS 300 has excellent adhesion to many types of residual sealant its use should not be considered a substitute for a good standard of joint preparation.
- In large joints ensure sealant is sufficiently cured before trafficking. In 40 mm joints this could be up to 10 days.
- Flush finished joints should not be used in locations where significant thermal movement may occur during service (e.g. external locations, particularly areas subject to direct sunlight) as this can result in the sealant bulging above the joint surface when the joints contract.

## Storage

Shelf life of 12 months if kept in a dry store at 10 – 20°C in original unopened packaging. If stored at high temperatures and / or high humidity, the shelf life may be significantly reduced.

## Precautions

### Health and safety

Nitoseal MS300: This product is non-hazardous in normal use. For further information refer to appropriate Product Safety Data Sheet.

Fosroc Primer MS2 is highly flammable, see Product Safety Data Sheet for details.

Fosroc and Nitoseal are trademarks of  
Fosroc International Limited



## Fosroc Limited

Drayton Manor Business Park  
Coleshill Road, Tamworth,  
Staffordshire B78 3XN. UK

[www.fosroc.com](http://www.fosroc.com)

### Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification of information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it. All Fosroc datasheets are updated on a regular basis. It is the user's responsibility to obtain the latest version.

telephone:  
+44 0 (1827) 262222

fax:  
+44 0 (1827) 262444

email:  
[enquiryuk@fosroc.com](mailto:enquiryuk@fosroc.com)



Certificate number FM 610