



# New Guard Coatings Group

A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

[www.newguardcoatings.com](http://www.newguardcoatings.com)

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND

# Fosroc® Nitoseal MS60

constructive solutions

## One part, general purpose building sealant

### Uses

Nitoseal MS60 is suitable for sealing joints in concrete, brickwork, blockwork, perimeter sealing around doors and windows, and non-trafficked floor joints.

### Advantages

- Adhesion to most common building materials
- Single component with fast rate of cure
- Easy to apply
- Can be applied to damp substrates
- Primerless for most applications (see "Priming")
- UV resistant and colour stable
- Performs as an acoustic sealant
- Available in a range of colours
- Environmentally friendly

### Description

Nitoseal MS60 is a one part, low modulus sealant based on hybrid silyl modified polyether ("MS") technology.


### Standards compliance

ISO 11600 Type F25LM

ASTM C920 Type S, Grade NS, Class 25

BS EN ISO 140-3:1995 Laboratory measurement of air-borne sound insulation of building elements

BS EN ISO 717-1:1997 Rating of sound insulation in buildings and of building elements. Airborne Sound Insulation.

 <b>2538</b>	
<b>Fosroc Ltd</b> Drayton Manor Business Park, Coleshill Road, Tamworth, B78 3XN, UK <b>14</b> <b>DOP: UK9-83</b>	
Nitoseal MS60	
EN 15651-1:2012: Sealants for façade elements	
Resistance to flow for non-sagging sealants	≤ 3mm

### Joint Design

Nitoseal MS60 may be applied to joints between 5 and 35mm wide. To minimise stress imposed on the joint sealant, all moving joints should be designed to an optimum width to depth ratio of 2:1 with an overriding minimum depth of 5mm for non-porous surfaces and 10mm for porous surfaces. Joint width should be sufficient to ensure the MAF of the

sealant is not exceeded.

For joint widths exceeding 35mm, please contact your local Fosroc Technical Service Department.

### Properties

Form	Smooth, non-slumping paste
Colours	White, Grey and Black (additional colours available, see local Fosroc office)
Skinning time	up to 2 hours depending on ambient conditions
Cure rate at 20°C/ 50% RH	24 hours 2mm
Application temperature	5°C to 50°C
Hardness at 23°C	Shore "A" >20
E-Modulus ISO 8339	<0.4N/mm <sup>2</sup>
Movement accommodation factor (MAF)	25%
UV resistance	Very Good
Colour stability	Very Good
Service temperature range	-20°C to 70°C
LEED EQc4.1	Passes
SCAQMD Rule 1168	
BAAQMD Reg 8 Rule 51	

### Application instructions

Joint surfaces must be clean, dry and free from frost.

Remove all dirt, laitance, loose material and foreign matter. Remove all rust, scale and protective lacquers from metal surfaces.

Removal can be achieved by grinding, grit blasting or wire brushing.

When resealing, the existing sealant should be removed from the joint and the arris cleaned back to sound, clean concrete. All debris must be removed.

Any expansion joint filler must be checked to ensure it is tightly packed and no gaps or voids exist at the base of the sealing slot before positioning a bond breaker.

The use of a bond breaker is not required in expansion joints containing cellular polyethylene joint filler such as Hydrocell or Expandafoam. For construction or contraction joints a bond breaker tape or back-up strip must be used.

Where a particularly neat finish is required, mask the face edges of the joint before sealing and remove immediately after tooling is completed.

### Priming

A primer is not normally required. In joints subjected to high movement or where intermittently immersed during service Fosroc Primer MS2 is recommended.

Prime the joint face using a clean, dry brush. Avoid over-application of primer, to prevent causing puddles in the bottom of the joint.

# Fosroc® Nitoseal MS60

Nitoseal MS60 should be applied between 30 minutes and 4 hours after priming.

If a joint is left unsealed for more than 4 hours, the primer should be removed by grit blasting or grinding and the joint re-primed.

For further advice on priming please contact your local Fosroc Technical Service Department.

## Application and finishing

### Sachets

Cut and remove the end of the sachet and place sachet in the Fosroc GX gun. Fit the nozzle and cut at 45 degrees to a suitable size for sealing the joint.

### Cartridges

Cut and remove the end of threaded stub on cartridge. Fit the nozzle and cut at 45 degrees to a suitable size for sealing the joint. Using a proprietary skeleton cartridge gun, extrude the sealant firmly in to the joint. Tool flush within 5 minutes of application to ensure good contact between the sealant and the substrate.

### Cleaning

Clean tools immediately after use with Fosroc Equipment Cleaner or Fosroc Solvent 102.

### Estimating

#### Guide to quantities

#### Sealant

Joint size mm	Litres/ metre run	Metres / 380ml cartridge	Metres/ 600ml sachet
10 x 6	0.06	6.3	10.0
12 x 10	0.12	3.2	5.0
20 x 10	0.20	1.9	3.0
25 x 12	0.30	1.3	2.0
30 x 15	0.45	0.8	1.3

## Packaging

Nitoseal MS60	600ml sachets x 10 per box 380ml cartridges x 20 per box
Fosroc Primer MS2	0.75 litre packs

## Limitations

- Should not be applied at temperatures below 5°C.
- Not suitable for water immersed conditions. Nitoseal MS600 should be used for this application.
- Not suitable for contact with bituminous materials
- Not suitable for trafficked floor joints. Nitoseal MS300 should be used for this application.
- May cause staining to decorative stone. For a non-staining sealant use Nitoseal MS100.
- Not suitable for contact with solvents, oil or petrol
- Should only be over-coated with a compatible, flexible coating capable of accommodating the expected movement in the joint. Over-coating may reduce the movement capability of the sealant.
- Confirm compatibility with coating if applied to painted surfaces

## Storage

Shelf life of 12 months if kept in a dry store at 10 – 20°C in original unopened packaging. If stored at high temperatures and / or high humidity, the shelf life may be significantly reduced.

## Precautions

### Health and safety

For further information refer to appropriate Product Safety Data Sheet.

Fosroc Primer MS2 is flammable. See Material Safety Data Sheet for details.

Fosroc and Nitoseal are trademarks of Fosroc International Limited



#### Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification of information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it. All Fosroc datasheets are updated on a regular basis. It is the user's responsibility to obtain the latest version.

## Fosroc Limited

Drayton Manor Business Park  
Colleshill Road, Tamworth,  
Staffordshire B78 3XN. UK

[www.fosroc.com](http://www.fosroc.com)

telephone:  
+44 0 (1827) 262222

fax:  
+44 0 (1827) 262444

email:  
enquiryuk@fosroc.com



Certificate number FM 610