



Specialist Construction Supplies for Repair, Maintenance, Building & Infrastructure

Nugrout Superflow Concrete Data Sheet

Specification notes

Product: **Nugrout Superflow
Concrete**

Supplier:

**Arcon Construction Supplies
19-20 Prestwood Court Leacroft
Road
Warrington
WA3 6SB**

Tel: **01925 852225**

Email: mail@arconsupplies.co.uk

Web: www.arconsupplies.co.uk

Call 01925852225 or visit [Arcon Construction Supplies](http://www.arconconstruction.com) website

...for technical, specification & application advice;

or

...for more information on our other repair, maintenance,
engineering and construction specialist products.

[Industrial Flooring](#) | [Concrete Repairs](#) | [Protective and Waterproof Coatings](#)

[Jointing and Paving Mortars](#) | [Anti-slip Floor Paints](#) | [Non-shrink Grouts &](#)

[Mortars](#)

Nugrout Superflow Concrete Data Sheet

Nugrout Superflow Concrete

Free Flowing Cementitious Micro Concrete

Description

A high strength free flowing cementitious, self-compacting concrete, based on non-reactive aggregates, low alkali, shrinkage compensated Portland cements with selected admixtures to produce a chloride free concrete which contains no corrosive metallic additives. Nugrout Superflow Concrete is designed for structural repair situations and complies with the requirements of BS EN1504 Part 3 Class R4.

Contains a 6mm aggregate and is designed for sections greater than 50mm.

Advantages

- Has controlled expansion and is non-shrink.
- Excellent early compressive and flexural strength.
- Material can be pumped, poured & vibrated.
- Excellent bond strength to steel and concrete.
- Requires only addition of clean water.
- Excellent flow and placement characteristics.
- Resistant to vibration and impact.
- Complies with requirements of EN1504 Part 3 Class R4.

Applications


- Production of bearing plinths.
- Crane rail bedding and alignment.
- Grouting of starter bars, holding down bolts, etc.
- Bedding of precast concrete beams.
- Repairs to spalled and cracked concrete.
- Grouting of machinery and turbines, etc.

Based on Portland Cement complying with DTp Specification of Highway Works Part 5.

Aggregate is non-reactive for Alkali-Silica Reaction, complying with the requirement of DTp Clause 1704.

Flow (DTp flow trough) flows 750mm in less than 30 seconds, in accordance with BD27/86.

Nugrout Superflow Concrete is non-shrink in accordance with Clause 2601.4(vii), DTp Specification for Highway Work Part 6.

 0086	
Nufins, Kingston House, 3 Walton Road, Pattinson North, District 15, Washington, Tyne & Wear. NE38 8QA 13 0086-CPD-594215	
EN 1504-3 Concrete repair product for structural repair CC Mortar (based on hydraulic cement)	
Compressive strength	Class R4 (>45 MPa)
Chloride ion content	≤0.05 %
Adhesive bond strength	>2.0 MPa
Adhesion after freeze/thaw (50 cycles with salt)	>2.0 MPa
Carbonation resistance	Passes
Elastic modulus	>20 GPa
Reaction to fire	Class A1
Dangerous substances	Complies with 5.4

Surface Preparation

Surfaces should be clean and free from loose and unsound material. Oil and grease should be removed using *Desolve*. Concrete should be roughened and all laitance removed mechanically. Surfaces should be thoroughly wetted for a minimum of two hours and any surplus water removed before placement. Allow surface to become dry thus obtaining a saturated, surface dry condition.



Technical properties of Nugrout Superflow Concrete.

Properties	Standard	Performance Requirement	Declared Value
Appearance			Grey Powder
Chloride-ion content	EN1015-17	≤0.05%	<0.05%
Cement Content			> 400 kg/m ³
Free Water/Cement Ratio			0.39
Equivalent Sodium Oxide			<3kg/m ³
Maximum aggregate size			6mm
Minimum Layer thickness			50mm
Working time			2 Hours
Hardening Time			6-18 Hours
Density			2250-2350 kg/m ³
Water Addition			3.8 litres per 25kg pack
Application temperatures			Between +5°C & +35°C
Compressive Strength	EN 12190	≥ 45 MPa	22 MPa @ 24 Hr 42 MPa @ 3 Days 50 MPa @ 7 Days 66 MPa @ 28 Days
Tensile Strength	BS6319-7		>4.0 MPa
Modulus of Elasticity, In Compression	EN13412	≥ 20 GPa	>20 GPa
Adhesion - concrete	EN1542	≥ 2.0 MPa	≥ 2.0 MPa
Adhesion after freeze/thaw (50 cycles with salt)	EN13687-1	≥ 2.0 MPa	≥ 2.0 MPa
Adhesion after thunder showers (30 cycles)	EN13687-2	≥ 2.0 MPa	≥ 2.0 MPa
Adhesion after dry cycling (30 cycles)	EN13687-4	≥ 2.0 MPa	≥ 2.0 MPa
Skid Resistance	EN13036-4		Class 1
Carbonation resistance	EN13295	$d_k \leq \text{ref. concrete}$	$d_k < \text{ref. concrete}$
Capillary absorption	EN13057	$\leq 0.5 \text{ kg/m}^2/\text{h}^{0.5}$	$\leq 0.5 \text{ kg/m}^2/\text{h}^{0.5}$
Cracking tendency	Coutinho Ring Test		No cracking after 180 days
Electrical Resistivity			13412 ohm/cm

Note: Results are based on 3.8 litres water addition, cured at 20°C. Unless otherwise stated.

Technical data shown are statistical results and do not correspond to guaranteed minima.

Tolerances are those described in appropriate performance standards.



Mixing

Mixing may be carried out in a standard barrel mixer or forced action mixer of a size suitable to produce the quantity of material required and without leaving any residual unmixed material. The mixing of part bags is not recommended.

The mixer drum is to be clean and free from the remains of the previous mixes. Thoroughly wet the inside of the mixer drum and drain off any excess water.

Measure out the mixing water and place approximately two thirds of this into the mixer drum. With the mixer rotating, add the full contents of the pack and allow to mix till a stiff consistency is obtained. This is necessary to eliminate any unmixed material. Add all or part of the remainder of the water to achieve the desired consistency and allow to mix for a further 1-2 minutes, depending upon mixer. Pour the mix into containers and allow to de-air for 2-3 minutes.

This will not be necessary if pumping. Use mix as required.

Pouring Nugrout Superflow Concrete

Nugrout Superflow Concrete should be placed by pouring, remembering flowability decreases with time and temperature. Always mix enough material to complete placing in one uninterrupted pour.

Place the product from one side only, so as to avoid entrapped air and to ensure continual free flow of the material.

Where formwork is involved it is essential that it is thoroughly sealed to prevent concrete loss and it should be coated with *Chemlease* to obtain an easier release.

Pumping Nugrout Superflow Concrete

The addition of excess water to "aid flowability" should be avoided as this could cause segregation of the mix and inhibit pumping. To aid pumping, the water addition may be reduced slightly by an experienced operator. Please contact Nufins technical department for further information regarding specific applications.

Low Temperature Working

Concreting should not take place in temperatures below 5°C unless steps have been taken to protect grouted areas in these conditions. At temperatures below 10°C it is advised Nugrout Superflow Concrete is stored at 15-20°C for a minimum of 24 hours and that the mixing water should be warm, 20-25°C.

Curing

The placed concrete must be cured immediately after finishing using good concreting practise. Several methods may be employed including the application of Nufins *Chemcure R90*.

Packaging

Nugrout Superflow Concrete is supplied in a 25kg lined bag. Approximate yield is 12.7 litres.

Storage

Shelf life of Nugrout Superflow Concrete is 6 months when stored in cool dry conditions and in sealed packaging.

Health & Safety

Product Safety Data Sheets (SDS) are available from Nufins. SDS sheets are provided to help customers satisfy their safe handling, use and disposal needs as well as assist with any conformance requirements made locally by health and safety regulations.

SDS are continually updated to provide the latest information to our customers. We therefore recommend contacting our head office to obtain the most recent and accurate SDS before handling and using any product.

Limitations

Excessive water additions will reduce strengths and can cause segregation within the mix which may limit the flow.

Technical Support

Through our technical department and laboratories we can offer a comprehensive service to specifiers and contractors. Technical contacts are available to provide further information and arrange demonstrations.

