



Specialist Construction Supplies for Repair, Maintenance, Building & Infrastructure

## Proofex 3000 MR Data Sheet

### Specification notes

Product: **Proofex 3000 MR**

Supplier:

**Arcon Construction Supplies**  
**19-20 Prestwood Court**  
**Leacroft Road**  
**Warrington**  
**WA3 6SB**

Tel: **01925 852225**

Email: [mail@arconsupplies.co.uk](mailto:mail@arconsupplies.co.uk)

Web: [www.arconsupplies.co.uk](http://www.arconsupplies.co.uk)

Call **01925 852225** or visit [Arcon Construction Supplies](http://www.arconconstruction.com)  
... for more information on our flooring and construction products

[Industrial Flooring](#) | [Concrete Repairs](#) | [Protective and Waterproof Coatings](#)  
[Jointing and Paving Mortars](#) | [Anti-slip Floor Paints](#) | [Concrete Repair Mortars](#)

# Proofex 3000MR

constructive solutions

High performance methane, radon and CO<sub>2</sub> resisting waterproof membrane for basements and structures

## Uses

A high performance self adhesive membrane for resisting methane, radon and CO<sub>2</sub>, and preventing water entering buildings. Proofex 3000MR also provides a vapour and waterproof membrane to water excluding structures and protects concrete from attack by aggressive ground salts.

## Advantages

- Aluminium film provides methane, radon and CO<sub>2</sub> resistance, protection against damage and gives dimensional stability
- Combines toughness with flexibility for detailing around corners, pipes, etc.
- Self adhesive layer system makes installation quick, simple and reliable
- Resistant to ground water, soluble sulphates and chlorides
- Suitable for waterproofing basements grades 2, 3 and 4 as defined in BS 8102:1990, 'Protection Of Structures Against Water From The Ground'

## Description

Proofex 3000MR is a cold applied, flexible, methane resisting and waterproof high performance membrane incorporating an aluminium layer and a polymer modified bitumen compound on a high strength polymer backing film.

Where methane, radon or CO<sub>2</sub> is present, a comprehensive site survey must be carried out and the building constructed accordingly. Refer to Building Research Establishment Report 212 and CIRIA Guide 149 for further information.

Proofex 3000MR should be laid in accordance with the provisions of BS 8102:1990.

## Typical properties

<b>Membrane thickness:</b>	1.2 mm
<b>Methane gas resistance:</b>	<5cm <sup>3</sup> /m <sup>2</sup> 24h bar
<b>Radon permeability (SP Sweden):</b>	0.56 10 <sup>-12</sup> m <sup>2</sup> /s
<b>Adhesion to primed concrete (ASTM D1000):</b>	4.9 N/mm <sup>2</sup>
<b>Tensile strength (BS EN 12311-1):</b>	
<b>Longitudinal:</b>	230 N/50mm
<b>Transverse:</b>	235 N/50mm
<b>Elongation (BS EN 12311-1)</b>	
<b>Longitudinal:</b>	33 %
<b>Transverse:</b>	37 %
<b>Hydrostatic test (BS EN 1928):</b>	≥60 kPa
<b>Water vapour permeability (BS EN 1931):</b>	Impermeable to ISO 12572

## Application instructions

### Surface preparation

All concrete surfaces must be a wood float or shutter finish and free from cavities or projections.

Masonry surfaces must be flush pointed.

All surfaces must be clean, dry and free from contamination, ice and frost.

### Priming

Vertical and suspended slab surfaces shall be primed with Proofex Primer. Ensure complete coverage and allow to dry. Only prime an area to which the Proofex 3000MR can be applied the same day. Very porous surfaces may require more than one coat of primer.

### Angle and corner details

Use Proofex Angle Fillet strips fixed using 6 mm beads of Plastiseal at all wall to floor junctions.

All internal and external angles should be reinforced with Proofex Engage Detail Strip or a 300 mm wide strip of Proofex 3000MR. Where possible, a 25 mm chamfer should be provided to external angles.

### Application

Application temperature range 5°C to 35°C.

#### Vertical application:

Cut the Proofex 3000MR to length allowing 150 mm for the end laps and position by peeling back the release paper and applying the self adhesive face to the prepared surface.

Start at the top of the wall and work down by progressively removing the release paper in stages. Proofex 3000MR should be applied to ensure that all end laps are weathered.

In cold weather temporary batten support of the Proofex 3000MR membrane is recommended.

#### Horizontal application:

Completely unroll the Proofex 3000MR membrane and place against a chalk line. One half of the roll should then be rolled up to the mid point, the release paper carefully cut without damaging the Proofex 3000MR membrane and progressively removed from the mid point out to the end of the roll.

This process should be repeated on the other half of the roll. The Proofex 3000MR membrane should be brushed onto the surface to ensure good bonding.

The next roll or length is aligned against the previously applied piece allowing for the 50 mm minimum (or as specified) edge laps and 150 mm end laps and applied as stated previously. The edge and end laps should be rolled to ensure complete adhesion and continuity between the layers.

# Proofex 3000MR

## Penetrations

Penetrations e.g. pipe entries through the Proofex 3000MR membrane require special attention to detail. Proofex Top Hats are recommended and should be stuck to membrane using Proofex Total Tape and sealed to pipe with Nitoseal MS50

## Protection

Proofex 3000MR membrane should be protected from physical damage and weathering as soon as possible after application. Surfaces should be protected from damage by Proofex Protection Board.

Proofex 3000MR can also be covered with Proofex Sheetdrain to give both protection and a drainage layer.

## Ancillary products

### Proofex Protection Board

Bitumen impregnated board, designed to protect membranes from damage through backfilling and trafficking.

### Proofex Engage Detail Strip

A reinforced, double sided waterproof adhesive tape for use as reinforcing at all floor and wall junctions. It consists of a strong synthetic fibre fabric impregnated and coated both sides with a bitumen rubber adhesive. Each side of the tape is protected by a removable siliconised paper.

### Proofex Top Hat

MDPE sheathing, which encapsulates an aluminium foil layer.

### Proofex Angle Fillet

Strips fixed at all floor and wall junctions with a 6mm bead of Plastiseal.

## Estimating

### Proofex 3000MR

<b>Roll size:</b>	1 m x 20 m
<b>Roll area:</b>	20 m <sup>2</sup>
<b>Edge laps:</b>	50 mm minimum
<b>End laps:</b>	150 mm minimum
<b>Roll weight:</b>	25 kg

### Proofex Primer

<b>Storage life:</b>	2 years
<b>Coverage:</b>	6 to 8 m <sup>2</sup> /litre
<b>Minimum installation temperature:</b>	+4°C rising
<b>Drying time @ 20°C:</b>	1 to 2 hours
<b>Pack size:</b>	5 ltr and 25 ltr drums

### Proofex Engage Detail Strip

<b>Thickness:</b>	1.5 mm
<b>Roll size:</b>	200 mm x 10 m

### Proofex Protection Board

<b>2.0 mm Thickness:</b>	1000 mm x 2000 mm
<b>3 mm Thickness:</b>	1000 mm x 2000 mm
<b>Coverage:</b>	2.0 m <sup>2</sup>

## Storage

Proofex 3000MR must be stored in dry conditions, away from sunlight, in an upright position at a temperature between 5°C and 40°C.

## Precautions

### Health and safety

For information on Proofex Primer refer to Product Safety Data Sheet.

Proofex Primer is flammable. Keep away from sources of ignition. No smoking. In the event of fire, extinguish with CO<sub>2</sub> or foam. Do not use a water jet.

### Flash Point

<b>Proofex Primer:</b>	>39°C
------------------------	-------



Fosroc Limited  
Drayton Manor Business Park  
Coleshill Road, Tamworth,  
Staffordshire B78 3TL. UK

[www.fosroc.com](http://www.fosroc.com)

### Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification of information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it.

Proofex is the trade mark of Fosroc International Limited

**telephone:**  
+44 (0) 1827 262222

**fax:**  
+44 (0) 1827 262444

**email:**  
uk@fosroc.com



Certificate number FM 610