



Specialist Construction Supplies for Repair, Maintenance, Building & Infrastructure

Resujoint V Data Sheet

Specification notes

Product: **Resujoint V**

Supplier:

Arcon Construction Supplies
19-20 Prestwood Court
Leacroft Road
Warrington
WA3 6SB

Tel: **01925 852225**

Email: mail@arconsupplies.co.uk

Web: www.arconsupplies.co.uk

Call 01925852225 or visit [Arcon Construction Supplies](http://www.arconsupplies.co.uk) website

...for technical, specification & application advice;
or

...for more information on our other repair, maintenance,
engineering and construction specialist products.

[Industrial Flooring](#) | [Concrete Repairs](#) | [Protective and Waterproof Coatings](#)

[Jointing and Paving Mortars](#) | [Anti-slip Floor Paints](#) | [Non-shrink Grouts &](#)

[Mortars](#)

Resujoint V Data Sheet



Resujoint V

Revised 09/2017—Issue 1 : EPJV 2016

DESCRIPTION

Resujoint V is a high performance flexibilized two component epoxy joint sealant. It is a thixotropic compound which is designed to accommodate low level movement in vertical as well as horizontal joints.

Resujoint V is specifically suitable for stable expansion jointing in self-smoothing and screed floor coating systems.

ADVANTAGES

- Tough but flexible
- Good adhesion
- Accommodates movement and maintains a seamless finish
- Ease of cleaning
- Chemical resistance

RECOMMENDED USES

- Low movement expansion joint sealant
- Granolithic screeds
- Concrete and asphalt
- Polyurethane screeds
- Polymer screeds
- Epoxy substrates

PRODUCT INFORMATION

Recommended thickness (DFT)	Solids content	Pack sizes	Pack make up	Shelf life	Storage
6 -10mm	100%	2.5 Kg	1 X Base 1 X Hardener	12 Months (Base & Hardener)	Keep out of direct sunlight/store in a dry place between 15-30 °C

APPLICATION INFORMATION at 20°C

Coverage rate	Pot life	Recoating Intervals	Light traffic	Full traffic	Full chemical cure
2.5 Kg will fill 21 linear metres 10mm wide and 10mm deep	45 - 65 minutes	24 Hours	48 Hours	72 Hours	Up to 7 Days

Specification

Product : Resujoint V

Finish : Mid sheen

Recommended thickness range : 6-10mm

Colour : See RSL / S-W Flooring Colour Chart

Products required for this system

System : Resujoint V

Primer : Resuprime on dry substrates, or use RS Dampshield FH on damp surfaces, where the moisture level is an issue.

Surface Seal : n/a



Preparation

Remove all laitance, old mastic and other filler media by cutting or grinding. Ensure the joint is clean, dry, sound and free from dust. The joint should be formed to the correct depth/profile by placing a bond breaker or debonding film at the base of the joint to form a uniform cross section with a minimum depth of 6mm and width to depth aspect ratio of 2-1 to 1-1. Where high loads are to be applied then a minimum depth of 10mm should be used.

Priming

Prime the walls of the joint with **Resuprime** or **RS Dampshield**, by brush ensuring all the sides and base are covered with the primer.

Application

Mixing: Pre-mix the coloured base component to a uniform consistency then add the entire contents of the hardener to the base and mix thoroughly using a slow speed electric mixer for approximately two minutes until the two components have fully combined.

The mixed unit should be applied immediately by trowel, spreading knife or spatula to fill the joints and smoothing the surface.

For joints over 10mm wide, a firm backing should be used, ensure that all joint fillers are well compacted. It is important to ensure that the backing stop/bond breaker is tight fitting in the joint to retain the **Resujoint V** in the correct position.

Care should be taken when placing the backing strip to ensure that it is not stretched on installation as this can result in leakage at the ends of the joint/strip as it shrinks back.


Category Guide

FeRFA Category : n/a

Technical Information

The following figures are obtained from laboratory tests and our experience with this product.

Temperature Resistance	Tolerant of sustained temperatures of up to 60°C
Chemical Resistance	Consult Technical Team for Further details
VOC	22 g/l Calculation based on a full mixed unit
Life Expectancy	2-5 years for low monument joints subject to application condition and level of traffic. RSL terms and conditions will apply


Resin Surfaces Ltd Titan House, Lowick Close, Newby Road Industrial Estate Hazel Grove, Stockport, SK7 5ED
13
BSEN 13813 SR B 2 - AR 0.5 - IR >4 Resin coating/screed for use inside buildings as per RSL data sheet Wear resistance: AR 0.5 Bond strength: B 2 Impact resistance: IR > 4

Maintenance and Cleaning

It is recommended that **Resujoint V** should be cleaned with a regular industrial cleaning regime with a floor scrubber utilising **R.S. Industrial Floor Cleaner** or similar with dirty water being removed. Isolated localised cleaning can be carried out using **R.S. Tyre Mark Remover**, **R.S. Fats & Grease Remover** & **R.S. Oil Remover**. All surfaces should be thoroughly rinsed with clean water after the use of chemical cleaners.

Please refer to our Guide to Cleaning of Resin Floors

Health and Safety

Resujoint V is formulated from materials designed to achieve the highest level of performance as safely as possible. However, specific components require proper handling and suitable equipment, this information is given in the relevant safety data sheets. In all cases, spillages or skin contamination should be cleaned as soon as practically possible, by dry wiping of the affected area, and thorough washing with soap and water.

The information given in this data sheet is derived from tests and experience with the products and is believed to be reliable. The information is offered without guarantee to enable purchasers to determine for themselves the suitability of the product for their particular application. Any specification or advice given by Resin Surfaces Limited or its agents is based on the information supplied by the purchaser. Resin Surfaces Limited cannot be held accountable for errors or omissions as a result of that information being incorrect or incomplete. No undertakings can be given against infringement of patents. Some materials are derived from natural sources. As such some variation may occur. Site conditions may also contribute to variation in finish and colour.