



New Guard Coatings Group

A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

www.newguardcoatings.com

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND



**PROTECTIVE
&
MARINE
COATINGS**

**Resuprime OT
PRODUCT TECHNICAL DATA**

PRODUCT DESCRIPTION

Resuprime OT is a two-component epoxy resin floor membrane that is tolerant of residual oil contamination in concrete substrates. It is essential that all surface and gross contamination is removed by cleaning with R.S. Oil Remover and R.S. Industrial Floor Cleaner prior to application of Resuprime OT.

ADVANTAGES

- Ease of application
- Damp and moisture tolerant
- Application onto substrates with hygrometer readings up to 85% ERH
- Low odour
- Excellent adhesion
- Solvent free
- Tolerant of residual oil contamination

RECOMMENDED USE

- Substrates with oil contamination
- Concrete substrates with no DPM
- Factory Floors
- Polymer screeds
- Cementitious underlayments
- Automotive Workshops

PRODUCT DATA

Volume Solids:	~100%	Application at 20°C	
VOC:	84 g/l calculated per full mixed unit	Recoating Intervals:	6-8 hours or once surface has lost tackiness
Colours:	Clear	Light Traffic:	18 – 24 hours
Finish:	Smooth gloss	Full Traffic:	48 – 72 hours
Flash Point:	N/A	Full Chemical Cure	7 days
Cleanser/Thinner:	N/A	Pot Life:	25 – 30 minutes from mixing, based on 5 kg pack size
Pack Size:	5 kg and 15 kg	<i>The pot life may be shorter for larger pack sizes if the paint is not used within the pot life limit.</i>	
Pack Weights:	3.33 kg base/1.67 kg hardener (5 kg) 9.99 kg base/5.01 kg hardener (15 kg)	Note: All mixed paint must be used within the pot life time limit, if the paint is left in the container after mixing and not used, it may release hazardous fumes due to exothermic reaction.	
Mixing Ratio:	2 parts base to 1 part hardener by weight only	Coverage Rate:	5 kg will cover 23 m ² @ 200 µm WFT
Mixed Density:	Approximately 1.08 g/cm ³	<i>Coverage rate is calculated based on a sealed and smooth surface and may vary based on the substrate roughness and other conditions.</i>	
Shelf Life:	36 months (Base and Hardener)	System Thickness:	200 – 250 µm
Storage:	Keep out of direct sunlight. Store in a dry place, between 15°C – 30°C	(Recommended)	
Recommended Application Methods:	Brush, roller or squeegee	<i>The suggested thickness range is calculated based on average volume solid as a general recommendation for the specified condition and for each application may vary.</i>	



Resuprime OT

SURFACE PREPARATION

New Concrete Floors: New concrete must be clean, sound, dry, fully cured and surface laitance removed by vacuum enclosed shot blasting or mechanical grinding, a minimum strength of 25N/mm² is required.

Existing Concrete Floors: Remove all dirt, oil, grease, old paint or any other surface contaminants by vacuum enclosed shot blasting, scarifying or mechanical grinding. Fats, oils or greases must be removed by mechanical means and detergent washing and making sure all residue of detergent is washed and removed by rinsing with clean water. Local repairs should be carried out using **Resuscreed PA**.

Existing Floors (previously coated): All previous coatings and loose floor paints must be removed by mechanical preparation as described in the above section and primed as specified. If the old resin flooring cannot be removed then please consult with our technical team for advice on intercoat adhesion and suitability, as it may not be compatible with the existing floor coating. Where **Resuprime OT** is applied to masonry/concrete surfaces, care must be taken to ensure that surface preparation is thorough but does not disfigure the surface.

Contaminated Substrates: Contaminated substrates require thorough cleaning prior to surface preparation and priming. **R.S. Oil Pretreatment** can be used to help remove any oil contamination. This must then be thoroughly washed off using **R.S. Industrial Floor Cleaner**. Please refer to the product datasheets for information on proper use of these.

PRIMING

See Sherwin-Williams System Sheets for recommended floor systems.

Resuprime OT is suitable on concrete with Relative Humidity readings up to 85% ERH. Where the Relative Humidity of a substrate exceeds 85% ERH **Resuprime MVT** should be specified and selected on the basis of hygrometer readings in accordance with BS 8203:2017. The number of coats to be applied is chosen in accordance with the following table:

ERH%	Required Coating Thickness
75-85	1 coat of Resuprime MVT at 200 µm per coat
85-92	2 coats of Resuprime MVT at 200 µm per coat
92-97	3 coats of Resuprime MVT at 200 µm per coat

For further information please refer to recommended individual product data sheets.

MIXING

Mixing: Mix the entire contents of the **Resuprime Base** with the **Resuprime OT Hardener**. If a separate mixing bucket is being used mix thoroughly ensuring all contents of both components are removed from the buckets supplied. Mix using a slow speed electric mixer for approximately two to three minutes until the two components are fully combined. The mixed unit should be applied immediately by roller, brush or squeegee with a consistent procedure. Floor areas should be cross-rolled to ensure even application and to minimise roller marks.

APPLICATION CONDITIONS

The ambient temperatures of the areas should not be allowed to fall below 15°C throughout the application and the curing period, as this could have an adverse effect on the appearance and colour of the system. Surface temperature must be above 10°C. Where possible it is recommended that the application area is heated to a minimum temperature of 15°C ideally to allow the ambient and substrate temperature to stabilise prior to the installation.

TECHNICAL INFORMATION

The following figures are obtained from laboratory tests and our experience with this product.

Category Guide:	FerFA Category 2
Bond Strength:	>3 N/mm ² (Substrate failure)
Temperature Resistance:	Tolerant of temperatures up to 60°C

WARRANTY

Any person or company using the product without first making further enquiries as to the suitability of the product for the intended purpose does so at their own risk, and Sherwin-Williams can accept no liability for the performance of the product, or for any loss or damage arising out of such use.

The information detailed in this datasheet is liable to modification from time to time in the light of experience and normal product development, and before using, customers are advised to check with Sherwin-Williams, quoting the reference number, to ensure that they possess the latest issue.

DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.

HEALTH AND SAFETY

Consult Product Health and Safety Datasheet for information on safe storage, handling and application of this product.

www.sherwin-williams.com/protectiveEMEA

This datasheet is specifically subject to the disclaimer which can be found at: <http://protectiveemea.sherwin-williams.com/Home/Disclaimer>