



Specialist Construction Supplies for Repair, Maintenance, Building & Infrastructure

RS Oil Tolerant Primer Data Sheet

Specification notes

Product: **RS Oil Tolerant Primer**

Supplier:

Arcon Construction Supplies
19-20 Prestwood Court
Leacroft Road
Warrington
WA3 6SB

Tel: **01925 852225**

Email: mail@arconsupplies.co.uk

Web: www.arconsupplies.co.uk

Call **01925 852225** or visit [Arcon Construction Supplies](http://www.arconconstruction.com)
... for more information on our flooring and construction products

[Industrial Flooring](#) | [Concrete Repairs](#) | [Protective and Waterproof Coatings](#)
[Jointing and Paving Mortars](#) | [Anti-slip Floor Paints](#) | [Concrete Repair Mortars](#)



REF : PROT 2011 05

R.S. Oil Tolerant Primer

DESCRIPTION

R.S. Oil Tolerant Primer is a two-component epoxy resin floor membrane that is tolerant of residual oil contamination in concrete substrates. It is essential that all surface and gross contamination is removed by cleaning with R.S. Oil Remover and R.S. Industrial Floor Cleaner.

ADVANTAGES

- Easy application
- Application onto substrates with engineering oil contamination
- Application onto substrates with Hygrometer readings up to 85%
- Solvent free
- Low odour
- Excellent adhesion
- Suitable for all RSL systems as subsequent floor finish

RECOMMENDED USES

- Concretes with oil contamination
- Where a dpm is ineffective
- Polymer screeds
- Certain underlayment screeds
- Factory floors
- As a non-dusting seal for contaminated concrete

PRODUCT INFORMATION

System thickness (dry)	Solids content by weight	Pack sizes	Pack make up	Shelf life	Storage
200 microns	100%	4 kg. & 8 kg.	1 x Base 1 x Hardener	12 Months (Base & Hardener)	Keep out of direct Sunlight. Store in a dry place, not below 15°

DRYING TIMES & COVERAGE RATES at 20 ° C

Coverage rate	Pot life	Recoat time	Light traffic	Full traffic	Full chemical cure
4 Kg. will cover 16 sq m @ 220 microns thickness	30 Minutes from mixing	8 hours or once surface has lost tackiness	24 Hours	72 Hours	Up to 7 Days



www.resinsurfaces.co.uk

Specification

Product : R.S.Oil Tolerant Primer

Finish : Semi Gloss

Thickness : 220 Microns

Colour : Clear

Products required for this system

Prime: R.S. Oil Tolerant Primer

System : As RSL specification

Surface Seal : As RSL specification

Preparation

R.S. Oil Tolerant Primer is used in conjunction with **R.S. Oil Pre-Treatment** and **R.S. Industrial Floor Cleaner**. The surface should be mechanically prepared to remove as much as possible of the contaminated surface. Apply **R.S. Oil Pre-treatment** in accordance with the Data Sheet, and allow to work for not less than 20 min. Agitate with a scrubber and then wash off from the surface with **R.S. Industrial Floor Cleaner**. Several cleaning cycles may be required to achieve the necessary level of cleanliness. Rinse the surface thoroughly with clean water to remove any residues and allow surface to dry.

Inspect the surface to ensure that there is sufficient surface key and that there is no free oil contamination remaining (or that oily material has not risen from the underlying concrete).

Concrete surfaces must be prepared by scarifying, vacuum shot-blasting, planing or other suitable method. All traces of concrete hardeners or other contaminants must be removed. The surface must be thoroughly vacuumed to remove concrete dust and then protected against further contamination by suitable means. Surfaces must be free from liquid water and atmosphere must not be condensing.

The product may also be applied to polymers, screeds and certain types of smoothing underlayments, provided these are well bonded. Such underlayments must be stable to the effects of water. If not the concrete floor must contain an integral damp-proof membrane to prevent further ingress of water from the ground.

Where laid onto a concrete surface where there is no DPM or where damage may have rendered the DPM ineffective due consideration must be given to the possible presence of hydrostatic pressure, and the consequences of creating a barrier layer resulting in the pressure /water flow being directed elsewhere.

IMPORTANT: Oil tolerant primer will not bond to grossly contaminated surfaces and surface cleaning and preparation is an essential part of this process.

Application

The ambient temperatures of the areas should not be allowed to fall below 10°C throughout the application and the curing period, as this could have an adverse effect on the system. Surface temperature must be above 5°C at all times.

Where possible it is recommended that the application area is heated to a minimum temperature of 15°C ideally to allow the ambient and substrate temperature to stabilise prior to installation.

Mixing: Mix the entire contents of the base with the hardener. If a separate mixing bucket is being used mix thoroughly ensuring all contents of both components are removed from the buckets supplied. Mix using a slow speed electric mixer for approximately two minutes or until the two components have fully combined.

The mixed unit should be applied immediately by roller or brush with a consistent procedure. Floor areas should be cross-rolled to ensure even application and to minimise roller marks.

Category Guide

FeRFA Category : 2

Technical Information

The following figures are obtained from laboratory tests and our experience with this product .

Slip Resistance Dry > n/a

Method BS7976 pt1-3 2002 Wet > n/a

The slip resistance of a floor surface can vary as a result of the installation process, conditions at the time of application and subsequent traffic. Inappropriate cleaning or maintenance can adversely affect the performance. For further advice on potential wet areas please consult RSL.

Abrasion Resistance n/a

Method BS8204 /ASTM D4060

Temperature Resistance Tolerant of sustained temperatures of up to

Chemical Resistance Chemical Resistance
Consult RSL on specific materials

Compressive Strength n/a

Flexural Strength n/a

Tensile Strength n/a

VOC 91 g/l

Calculation based on a full mixed unit

Life Expectancy 4 years plus

Subjected to Industrial Traffic
RSL terms and conditions will apply

Maintenance and Cleaning

n/a if used as a primer .

RSL recommend that **R.S. Oil Tolerant Primer** should be cleaned with a regular industrial cleaning regime with a floor scrubber utilising **R.S. Industrial Floor Cleaner** or similar with dirty water being removed. Isolated localised cleaning can be carried out using **R.S. Tyre Mark Remover**, **R.S. Fats & Grease Remover** & **R.S. Oil Remover**. All surfaces should be thoroughly rinsed with clean water after the use of chemical cleaners.

Please refer to RSL Data Sheet CLNG for Cleaning Advice

Health and Safety

R.S. Oil Tolerant Primer is formulated from materials designed to achieve the highest level of performance as safely as possible. However, specific components require proper handling and suitable equipment, this information is given in the relevant safety data sheets. In all cases, spillages or skin contamination should be cleaned as soon as practically possible, by dry wiping of the affected area, and thorough washing with soap and water.

The information given in this data sheet is derived from tests and experience with the products and is believed to be reliable. The information is offered without guarantee to enable purchasers to determine for themselves the suitability of the product for their particular application. Any specification or advice given by the Resin Surfaces Limited or its agents is based on the information supplied by the purchaser. Resin Surfaces Limited cannot be held accountable for errors or omissions as a result of that information being incorrect or incomplete. No undertakings can be given against infringement of patents. Some materials are derived from natural sources. As such some variation may occur. Site conditions may also contribute to variation in finish and colour.

Resin Surfaces Ltd
Titan House, Lowick, Close
Newby Road Industrial Estate
Stockport
Cheshire
SK7 5ED

Tel : + 44 (0) 161 483 1232 Fax: + 44 (0) 161 483 2565
Email : info@resinsurfaces.co.uk Web : www.resinsurfaces.co.uk
Registered in England : 1659941 Vat No : GB 373 485 624