



New Guard Coatings Group

A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

www.newguardcoatings.com

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND

PRODUCT DATA SHEET

Sika®-1 Pre-bag Spritz Mortar

PRE-BAGGED SPRITZ AND BONDING MORTAR

PRODUCT DESCRIPTION

Sika®-1 Pre-bag Spritz Mortar is part of the Sika® 1 Pre-Bagged Structural Waterproofing System. These special mortars are pre-bagged kiln dried blends of specially graded aggregates and cements, with waterproofing admixtures, packaged in 4 grades at the appropriate mix ratios for optimum application performance and durability. When mixed with water they provide the multicoat components for the structural waterproofing systems

USES

- Internal waterproofing of below ground structures to meet the requirements of BS8102:2009 Grades 1 - 3
- Waterproofing of swimming pools and other water retaining structures
- Waterproofing of basements, cellars and vaults
- Waterproofing of tunnels

CHARACTERISTICS / ADVANTAGES

- Type A waterproofing system according to BS8102:2009
- Proven resistance to hydrostatic back pressure
- Fully bonded waterproofing barrier
- Can be applied to wet substrates
- For use on concrete, brick and structural blockwork
- Can be used internal and externally
- Can be applied to wall, floors and soffits
- Quality controlled system
- Used for negative or positive water pressure situations

PRODUCT INFORMATION

Packaging	Supplied in 25kg Packs with a coloured Majenta Band	
Appearance / Colour	Graded kiln dried aggregates, OPC and waterproofing admixtures	
Shelf Life	Minimum 6 months in original unopened sealed packs	
Storage Conditions	Stored in dry condition at temperatures between +10°C and +30°C	
Density	2150 kg/m ³	
Compressive Strength	50 N/mm ²	(EN 12190)
Flexural Strength	7.3 N/mm ²	(EN 196-1)
Capillary Absorption	0.362	(EN 13057)
Consumption	Mix each 25 kg bag of Sika®-1 Pre-bag Spritz Mortar with 5.5L of clean water. A mixed 25kg bag of Sika®-1 Pre-bag Spritz Mortar will yield ~12.3L of mortar which is sufficient to cover ~2m ² at 6mm thick.	

APPLICATION INSTRUCTIONS

WALLS/BRICK:

All existing treatments shall be completely removed and the exposed surfaces roughened by mechanical or water blasting techniques, followed by washing down and brushing to ensure full removal of all loose material. Mortar joints should be bonded and sound. Any defective mortar joint should be raked out to a depth of 12.0mm and repointed using Sika®-1 Pre-bag Finishing Mortar made up with clean water.

WALLS/CONCRETE:

All laitance shall be removed to expose coarse aggregate by mechanical or water blasting techniques. On new concrete walls a retarder can be applied to the face of the shuttering followed by wire brushing and washing of concrete surfaces.

SUBSTRATE QUALITY / PRE-TREATMENT

The substrate must be structurally sound and generally brickwork, dense concrete block and concrete normally provide satisfactory substrates. All surfaces should be clean and free from surface contaminants

MIXING

Place the correct amount of water into a mixer, add the mortar and mix until the water has been fully combined, approximate 3 minutes. The Sika®-1 Pre-bag Spritz Mortar should be mechanically mixed using a forced action mixer or drill and paddle mixer to limit the amount of air entrapment. A tumble mixer is not suitable for mixing.

APPLICATION

Refer to Sika-1 Waterproofing system datasheet for full limitations methods

LIMITATIONS

Refer to Sika-1 Waterproofing system datasheet for full limitations.

VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA LIMITED

Watchmead
Welwyn Garden City
Hertfordshire, AL7 1BQ
Tel: 01707 394444
Web: www.sika.co.uk
Twitter: @SikaLimited

SIKA IRELAND LIMITED

Ballymun Industrial Estate
Ballymun
Dublin 11, Ireland
Tel: +353 1 862 0709
Web: www.sika.ie
Twitter: @SikaIreland



Product Data Sheet
Sika®-1 Pre-bag Spritz Mortar
April 2019, Version 01.01
020701010010000296

Sika-1Pre-bagSpritzMortar-en-GB-(04-2019)-1-1.pdf

