



New Guard Coatings Group

A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

www.newguardcoatings.com

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND

SIKA-4 RAPID SETTING



Colour	Product Code	Pack Size	Box Qty
Brown	SK4RAP5	5ltr	4

Product Description

Sika®-4 Rapid Setting is used to aid the quick setting of cement based renders and concretes where low water pressure or slow moving water exists.

Sika®-4 Rapid Setting is a ready to use quick setting leak stopping liquid which is mixed with water and ordinary portland cement to produce a paste for leak stopping against **low** water pressure infiltration.

Benefits

- Ready to use.
- Quick setting
- Prevents cement wash out.
- Does not contain chlorides
- Excellent resistance to backwater pressure.

Areas for Use

- Rendering or concreting against low water pressures.
- For rendering or concreting in wet areas.
- Leak stopping against low water pressure infiltration.

Limitations

- Where high water pressures are experienced, use - **Sika®-4a Waterstop**.
- Setting times will be affected by ambient temperature, water and **Sika®-4** temperature, supplier and age of ordinary Portland cement. Trials are recommended varying the **Sika®-4**/Water dosage, temperature and type of ordinary Portland cement until the required performance is achieved.
- Use only fresh ordinary Portland cement.
- Wear suitable protective clothing, gloves and eye protection.

Surface Preparation

Prepare surfaces by removing all loose material, dirt, moss and contaminants. Mechanically roughen surfaces to provide a key.

Application

Renders – Dilute **Sika-4 Rapid Setting** with clean water according to setting speed required for the application and water pressure/movement. Trials are always recommended.

Concrete – The concreting installation should be arranged to suit rapid placing. The concrete mix should contain a minimum of 400kg cement per cubic metre.

Specific Data

TEST	RESULT
Appearance	Brown liquid
SG @ 20°C	1.22-1.26g/cm ³ (approx.)
Consumption	1 part Sika 4 to 3-6 parts clean water
Solids Content	28.0-29.0%
Application Temperature	+5°C min +35°C max

Health & Safety

Consult MSDS for full list of hazards.

Storage

Protect **Sika-4 Rapid Setting** from frost and store between 5°C and 20°C

Shelf Life

12 months from date of manufacture when stored according to manufacturer's instructions.

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.