



New Guard Coatings Group

A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

www.newguardcoatings.com

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND

PRODUCT DATA SHEET

Sikadur®-52 Injection Normal

EPOXY LOW VISCOSITY INJECTION RESIN - NORMAL POT LIFE

PRODUCT DESCRIPTION

Sikadur®-52 Injection Normal is a 2-part, epoxy, low viscosity, normal pot life, injection resin specially formulated for crack injection work by either pressure injection or gravity feed techniques.

USES

Sikadur®-52 Injection Normal may only be used by experienced professionals.

- Crack injection resin
- Fills and seals voids and cracks in structures such as bridges, civil engineering structures, industrial and residential buildings, e.g. columns, beams, foundations, walls, floors and water retaining structures.
- Structural bonding
- Preventing ingress of water and infiltration of reinforcement corrosion promoting substances

CHARACTERISTICS / ADVANTAGES

- Injection temperature range +5 °C to +30 °C
- Good adhesion to concrete, masonry, stone, steel and wood substrates
- Suitable for both, dry and damp conditions
- Maximum crack width 5,0 mm
- Good mechanical properties
- Two grades for different climatic conditions
- High mechanical and adhesive strengths
- Hard but not brittle
- Low viscosity
- Injectable with single component pumps

APPROVALS / STANDARDS

- CE Marking and Declaration of Performance to EN 1504-5 - Concrete injection
- Fire Testing DIN EN 13501-1, Sikadur®-52 Injection Normal, MPA Braunschweig, Test report No. K-3604/805/13-MPA BS

PRODUCT INFORMATION

| | | |
|---|--|--|
| Packaging | Parts A+B | 1 kg pre-batched unit Box of 10 units |
| | Bulk | On request |
| Refer to current price list for packaging variations. | | |
| Colour | Part A | Transparent |
| | Part B | Brownish |
| | Part A+B mixed | Yellowish-brownish |
| Shelf Life | 24 months from date of production | |
| Storage Conditions | The product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +35 °C. Always refer to packaging. | |

| | | | |
|---------|----------------|------------|-----------------|
| Density | Part A | 1,121 kg/l | (EN ISO 2811-1) |
| | Part B | 1,006 kg/l | |
| | Part A+B mixed | 1,1 kg/l | |

all values at +22 °C

| | | | |
|-----------|--------------------|-----------------------|---------------|
| Viscosity | Temperature | Part A+B mixed | (EN ISO 3219) |
| | +10 °C | ~1200 mPa·s | |
| | +20 °C | ~430 mPa·s | |
| | +30 °C | ~220 mPa·s | |

TECHNICAL INFORMATION

| | | | | | |
|----------------------|-------------|----------------------|----------------------|----------------------|----------------|
| Compressive Strength | Time | +5 °C | +23 °C | +30 °C | (ASTM D695-96) |
| | 1 day | - | 32 N/mm ² | 43 N/mm ² | |
| | 3 days | 11 N/mm ² | 52 N/mm ² | 51 N/mm ² | |
| | 7 days | 53 N/mm ² | 55 N/mm ² | 55 N/mm ² | |

| | | | | | |
|--------------------------------------|-------------|------------------------|------------------------|------------------------|----------------|
| Modulus of Elasticity in Compression | Time | +5 °C | +23 °C | +30 °C | (ASTM D695-96) |
| | 1 day | - | 700 N/mm ² | 650 N/mm ² | |
| | 3 days | 650 N/mm ² | 1100 N/mm ² | 1000 N/mm ² | |
| | 7 days | 1500 N/mm ² | 1250 N/mm ² | 1000 N/mm ² | |

| | | | | | |
|-------------------|-------------|----------------------|----------------------|----------------------|-------------|
| Flexural Strength | Time | +5 °C | +23 °C | +30 °C | (DIN 53452) |
| | 1 day | - | 36 N/mm ² | 51 N/mm ² | |
| | 3 days | 11 N/mm ² | 59 N/mm ² | 60 N/mm ² | |
| | 7 days | 38 N/mm ² | 63 N/mm ² | 67 N/mm ² | |

| | | | | | |
|--------------------|-------------|------------------------|------------------------|------------------------|-------------|
| Flexural E-Modulus | Time | +5 °C | +23 °C | +30 °C | (DIN 53452) |
| | 1 day | - | 850 N/mm ² | 1450 N/mm ² | |
| | 3 days | 700 N/mm ² | 1400 N/mm ² | 1600 N/mm ² | |
| | 7 days | 1500 N/mm ² | 1600 N/mm ² | 1750 N/mm ² | |

| | | | | | |
|------------------|-------------|----------------------|----------------------|----------------------|-----------|
| Tensile Strength | Time | +5 °C | +23 °C | +30 °C | (ISO 527) |
| | 1 day | - | 23 N/mm ² | 26 N/mm ² | |
| | 3 days | 5 N/mm ² | 35 N/mm ² | 39 N/mm ² | |
| | 7 days | 30 N/mm ² | 37 N/mm ² | 37 N/mm ² | |

| | | | | | |
|-------------------------------|-------------|------------------------|------------------------|------------------------|-----------|
| Tensile Modulus of Elasticity | Time | +5 °C | +23 °C | +30 °C | (ISO 527) |
| | 1 day | - | 1250 N/mm ² | 1400 N/mm ² | |
| | 3 days | 550 N/mm ² | 1800 N/mm ² | 1900 N/mm ² | |
| | 7 days | 1800 N/mm ² | 1800 N/mm ² | 1800 N/mm ² | |

| | | | | | |
|---------------------|-------------|--------------|---------------|---------------|-----------|
| Elongation at Break | Time | +5 °C | +23 °C | +30 °C | (ISO 527) |
| | 1 day | - | 21 % | 16 % | |
| | 3 days | 57 % | 16 % | 9 % | |
| | 7 days | 22 % | 8 % | 7 % | |

| | | |
|---------------------------|---|-------------------------------------|
| Tensile adhesion strength | Concrete: > 4 N/mm ² (failure in concrete) (after 7 days at + 23 °C) | (acc. to DafStb-Richtlinie, Part 3) |
|---------------------------|---|-------------------------------------|

| | | |
|----------------------------------|---|---------------|
| Coefficient of Thermal Expansion | ~8,9×10 ⁻⁵ 1/K (linear expansion between -20 °C and +40 °C) | (EN ISO 1770) |
|----------------------------------|---|---------------|

APPLICATION INFORMATION

Mixing Ratio

Part A : Part B = 2 : 1 parts by weight

Consumption

| | | |
|---|--|--------------|
| Yield | 1 kg of injection resin: ~0,93 L | |
| Substrate Temperature | +5 °C min. / +30 °C max | |
| Substrate Moisture Content | Dry or damp (SSD - Saturated Surface Dry: no standing water) | |
| Pot Life | Temperature | 1 kg |
| | +5 °C | ~120 minutes |
| | +10 °C | ~80 minutes |
| | +23 °C | ~25 minutes |
| | +30 °C | ~10 minutes |
| <p>The potlife begins when Parts A+B are mixed. It is shorter at high temperatures and longer at low temperatures. The greater the quantity mixed, the shorter the potlife. To obtain longer workability at high temperatures, the mixed adhesive may be divided into smaller quantities. Another method is to chill Parts A+B before mixing (not below +5 °C).</p> | | |

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

Substrate surfaces along the line of the crack capping sealer i.e. Sikadur®-31 CF Rapid, must be sound, clean, dry or matt damp. Free from standing water, ice, dirt, oil, grease, coatings, laitance, efflorescence, old surface treatments, all loose particles and any other surface contaminants that could affect adhesion. Cracks must be clean.

SUBSTRATE PREPARATION

After inserting or bonding injection ports, cap the crack with a capping sealer, allow to cure then purge cracks with resin until the resin runs clean and contaminant free.

MIXING

Add all of Part B to Part A. Mix with a mixing spindle attached to a slow speed electric (max. 250 rpm) for at least 3 minutes. Over mixing must be avoided to minimise air entrainment. Mix full units only.

APPLICATION METHOD / TOOLS

Reference must be made to further documentation where applicable, such as relevant method statement, application manual and installation or working instructions.

Preliminary trials must be carried out by a competent applicator experienced in crack injection using injection equipment and appropriate injection pressures.

CLEANING OF TOOLS

Clean all tools and application equipment using the Sika® Injection Cleaning System in accordance with the Product Data Sheet. Hardened material can only be mechanically removed.

LIMITATIONS

- Do not inject into wet or saturated cracks.
- Do not add solvent to the product.
- Do not inject cracks under hydrostatic pressure.

- Do not inject crack widths >5,0 mm.
- At higher temperatures pot life will be shortened.
- At lower temperatures pot life will be increased but product will become more difficult to inject and take longer to harden.
- Trials should be carried out to establish suitability of resin, spacing of injection ports, injection equipment and pressures.

VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The

user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA LIMITED

Watchmead
Welwyn Garden City
Hertfordshire, AL7 1BQ
Tel: 01707 394444
Web: www.sika.co.uk
Twitter: @SikaLimited

SIKA IRELAND LIMITED

Ballymun Industrial Estate
Ballymun
Dublin 11, Ireland
Tel: +353 1 862 0709
Web: www.sika.ie
Twitter: @SikaIreland



Product Data Sheet
Sikadur®-52 Injection Normal
July 2020, Version 01.01
020707030010000004

Sikadur-52InjectionNormal-en-GB-(07-2020)-1-1.pdf

