



Specialist Construction Supplies for Repair, Maintenance, Building & Infrastructure

Thioflex 600 Data Sheet

Specification notes

Product: **Thioflex 600**

Supplier:

Arcon Construction Supplies
19-20 Prestwood Court
Leacroft Road
Warrington
WA3 6SB

Tel: **01925 852225**

Email: mail@arconsupplies.co.uk

Web: www.arconsupplies.co.uk

Call **01925 852225** or visit [Arcon Construction Supplies](http://www.arconconstruction.com)
... for more information on our flooring and construction products

[Industrial Flooring](#) | [Concrete Repairs](#) | [Protective and Waterproof Coatings](#)
[Jointing and Paving Mortars](#) | [Anti-slip Floor Paints](#) | [Concrete Repair Mortars](#)

Thioflex 600



Multi-component, gun and pouring grade, polysulphide sealant

Uses

Sealing movement joints in building and civil engineering structures, including superstructures, reservoirs, floors, basements and subways.

Advantages

- Meets key international standards
- Forms a tough, elastic, rubber-like seal
- Accommodates continuous and pronounced cyclic movement
- Excellent adhesion to most common substrates, including primed concrete, glass, aluminium and stainless steel
- High resistance to ageing reduces physical damage due to climatic extremes

Standards compliance

British Standard BS 4254 :1983.

British Standard BS 6920 :1996 (gun grade grey) - Water Regulations Advisory Service.

U.S. Federal Specification TT-S-00227E November 1969 (amended 1970).

DTp specification for Highway Works December 1991 series 1000 clause 1017.

ASTM C920-87: Type M, Grade NS, Class 25.

Drinking Water Inspectorate Regulation 25(1)b of the Water Supply (Water Quality) Regulations 1989.

Description

Thioflex 600 is available in gun and pouring grades. The gun grade is ideal for general application, and is available in a range of colours. It is packed in a ready to mix, 2.5 litre tin containing the base and curing agent in the correct proportions. The pouring grade for joints in horizontal surfaces is supplied in grey only in 5 litre packs with the base and curing agent in separate tins.

Thioflex 600 is particularly recommended for use in high-rise buildings and other applications where access for subsequent maintenance will be difficult and the risk of early movement failure must be minimised. It is also suitable for sealing joints in brickwork, retaining walls, reservoirs, basements and subways.

Thioflex 600 pouring grade is recommended for sealing expansion joints and stress relief joints in floors or other horizontal surfaces.

Design criteria

Thioflex 600 may be applied to joints between 5 and 50 mm wide. Joints which are expected to experience cyclic movements should be designed to an optimum width : depth ratio of 2 : 1, subject to the overriding recommended minimum sealant depths set out below:

5 mm for metals, glass and other non-porous surfaces;

10 mm for all porous surfaces;

20 mm for trafficked joints and those subject to hydrostatic pressures.

To ensure that the sealant remains within its stated movement capacity (25% MAF), sealing slot widths should be designed in accordance with the recommendations of BS 6093.

The use of a surface primer is always required on porous surfaces. On non-porous surfaces a primer is not normally required except where glass or glazed surfaces are to be permanently immersed in water.

Properties

Form:	Multi-part, paste compound
Colours:	Gun grade: grey, stone, off white, black, mahogany, brick red Pouring grade: grey
Movement accommodation factor (BS 6093):	25% butt joints 50% lap joints
Physical or chemical change:	Chemical cure
Pot life:	2 hours @ 25°C



Setting time:	72 hours at 5°C 36 hours at 15°C 18 hours at 25°C																								
Cure time:	Grey, black, mahogany, brick red: 4 weeks at 5°C 2 weeks at 15°C 1 week at 25°C Off white, stone: 8 weeks at 5°C 4 weeks at 15°C 2 weeks at 25°C																								
Application temperature:	5°C to 50°C																								
Operating temperature:	-20°C to +60°C																								
Hardness shore 'A' 25°C:	Gun grade: grey, black, mahogany, brick red: 20 to 25 Stone, off white: 28 to 33 Pouring grade: 15 to 23																								
Water immersion:	Thioflex 600 must be fully cured before permanent immersion in water																								
Chemical resistance to occasional spillage:	<table border="0"> <tr><td>Dilute acids</td><td>resistant</td></tr> <tr><td>Dilute alkalis</td><td>resistant</td></tr> <tr><td>Petrol</td><td>resistant</td></tr> <tr><td>Aviation fuels</td><td>resistant</td></tr> <tr><td>Diesel fuel</td><td>resistant</td></tr> <tr><td>Kerosene</td><td>resistant</td></tr> <tr><td>Lubricating oils</td><td>resistant</td></tr> <tr><td>Skydrol</td><td>resistant</td></tr> <tr><td>White spirit</td><td>resistant</td></tr> <tr><td>Chlorinated solvents</td><td>not resistant</td></tr> <tr><td>Aromatic solvents</td><td>not resistant</td></tr> <tr><td>Dilute oxidising acids</td><td>not resistant</td></tr> </table>	Dilute acids	resistant	Dilute alkalis	resistant	Petrol	resistant	Aviation fuels	resistant	Diesel fuel	resistant	Kerosene	resistant	Lubricating oils	resistant	Skydrol	resistant	White spirit	resistant	Chlorinated solvents	not resistant	Aromatic solvents	not resistant	Dilute oxidising acids	not resistant
Dilute acids	resistant																								
Dilute alkalis	resistant																								
Petrol	resistant																								
Aviation fuels	resistant																								
Diesel fuel	resistant																								
Kerosene	resistant																								
Lubricating oils	resistant																								
Skydrol	resistant																								
White spirit	resistant																								
Chlorinated solvents	not resistant																								
Aromatic solvents	not resistant																								
Dilute oxidising acids	not resistant																								
Biological resistance:	Thioflex 600 has been evaluated in microbiologically active situations and has been shown to have resistance to aerobic conditions																								
Solids content:	100%																								
Density:	1.62 to 1.73 kg/litre according to colour																								
Flash point:	Over 65°C																								
Flammability:	Burns but does not readily support combustion																								

Maintenance

No special requirements, any damage identified during normal building inspections should be repaired or replaced as appropriate.

Application instructions

Joint preparation

The joint surfaces must be thoroughly dry, clean and frost free. Remove all dust and laitance by rigorous wire brushing, grinding or grit blasting. Remove all rust, scale and protective lacquers from metal surfaces. Remove any oil or grease with Fosroc Joint Cleaner.

Any expansion joint filler must be checked to ensure it is tightly packed and no gaps or voids exist at the base of the sealing slot before positioning a bond breaker.

Note: The use of a bond breaker is not required in expansion joints containing Hydrocell or Expandafoam cellular polyethylene expansion joint fillers. For construction or contraction joints a bond breaker tape or back-up strip should be used. Where hydrostatic pressure exists, only bond breaking tapes must be used, not foamed back-up strips.

Where a particularly neat finish is required, mask the face edges of the joint before priming and remove immediately after tooling is completed.

Priming

When Fosroc Primers 4 or 7 are required, these should be used as follows:

Fosroc Primer 4: For use on glass and ceramics which are to be permanently immersed in water. It is a one part chemically active clear liquid for brush or pad application. One thin coat should be applied and allowed to dry for 2 to 5 minutes prior to sealant application.

Fosroc Primer 7: It is a one part chemically active clear liquid for brush application to concrete, stone, brickwork, timber and unglazed edges of ceramic tiles. One thin coat should be applied using a clean, dry brush, ensuring complete coverage. Avoid over priming resulting in an excess of primer in the base of the joint or application beyond faces. The mixed Thioflex 600 must be applied when the primer is tack free, that is after the evaporation of the solvent but before the primer film has completely reacted. After 3 hours the surfaces must be re-primed before applying the sealant.

Iron and steel must be protected with an anti-corrosion primer prior to sealing.

Mixing

Gun grade: The base component and curing agent are supplied ready for mixing in a single tin. Mix thoroughly using a slow speed drill (300 to 500 rpm) fitted with a

Fosroc Paddle Stirrer for 5 minutes. Only thorough mixing, including material right at the bottom of the tin, will result in proper curing. In cold weather Thioflex 600 mixes more easily if stored overnight at room temperature.

Immediately after mixing, load the sealant into a Fosroc 'G' Gun using the follower plate, and apply to the joint.

Pouring grade: Thioflex 600 pouring grade is supplied in two separate containers. The small container contents should be transferred to the other tin, and mixed as per the gun grade instructions. The pouring grade may be poured directly into horizontal joints or for application to horizontal joints less than 15 mm wide loaded into a Fosroc 'G' Gun. For quantity application, a Fosroc 1.5 litre gun is available.

Finishing

Thioflex 600 should be tooled to a smooth finish. A minimum of surface lubricant such as dilute detergent solution may be used to assist the process. Any masking tape should be removed immediately after tooling.

Cleaning

Clean equipment immediately after use with Fosroc Equipment Cleaner.

Contract application

The designer or contractor may wish to use the services of a specialist sub-contractor for joint sealing work. Names of preferred sub-contractors are available from Fosroc.

Limitations

Over-painting of sealants is not recommended because of the inability of paint films to accept movement. However, if definitely required, trials should be carried out to determine compatibility.

Thioflex 600 should not be used in direct contact with materials containing pitch or bitumen.

Only Thioflex 600 gun grade grey should be used in vertical or horizontal joints in reservoirs or other water retaining structures.

Estimating

Packaging

Thioflex 600 gun grade is supplied in 2.5 litre tins in cartons of four.

Thioflex 600 pouring grade is supplied in a 5 litre tin.

Guide to quantities

Joint size in mm	Litres per metre run	Metre run per 2.5 litre pack	Metre run per 5 litre pack
5 x 5	0.025	100.00	200.00
5 x 10	0.050	50.00	100.00
10 x 10	0.100	25.00	50.00
20 x 10	0.200	12.50	25.00
20 x 15	0.300	8.33	16.67
20 x 20	0.400	6.25	12.50
40 x 20	0.800	3.12	6.25
40 x 25	1.000	2.50	5.00
40 x 30	1.200	2.00	4.00
40 x 40	1.600	1.56	3.12
50 x 25	1.250	2.00	4.00
50 x 30	1.500	1.67	3.33
50 x 40	2.000	1.25	2.25
50 x 50	2.500	1.00	2.00

1 litre of Fosroc Primer 4 to 300 litres of Thioflex 600.

1 litre of Fosroc Primer 7 to 30 litres of Thioflex 600.

These are theoretical yields. No allowance has been made for variation in joint width or wastage.

Storage

Storage life of 12 months in original containers when kept in dry conditions between 5°C and 27°C.

Precautions

Health and safety

Thioflex 600: Harmful if swallowed. The curing agent consists of a heavy metal based oxide. Avoid contact with skin and eyes. Wear suitable protective gloves and eye/face protection. In case of contact with skin, wash immediately with soap and water. In case of contact with eyes, rinse immediately with plenty of clean water and seek medical advice. Hands should be thoroughly washed with soap and water before eating or smoking. Cured sealant should not be burned off due to generation of toxic fumes. Empty containers should be disposed of in accordance with waste disposal regulations.

**Fosroc Limited**

Coleshill Road
Tamworth
Staffordshire B78 3TL
Tel 01827 262222
Fax 01827 262444
www.fosrocuk.com

Thioflex is the trade mark of Fosroc International Limited

Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation or information given by it.